

PRODUCT DATA SHEET

SikaLevel®

Durable, cementitious, self-leveling underlayment

PRODUCT DESCRIPTION

SikaLevel® Self Leveling Underlayment is a one-component, durable and versatile cementitious underlayment for interior concrete, and cementitious substrates. It can be applied manually or by pump to produce a self-smoothing, rapid-setting, flat and economical substrate prior to the application of a final floor finish. Typical application thickness is 1/8 to 2 inches* (3 to 50 mm).

* in localized areas

USES

Interior floor leveling and smoothing applications where floor coverings are to follow, such as:

Institutional - schools, colleges, hospitals, clinics, libraries, galleries, museums

Commercial - offices, corridors, hallways, canteens, cafeterias, stores, hotels, restaurants

Residential - domestic properties, condominiums and high rise construction

PRODUCT INFORMATION

Chemical Base	Cement-based, polymer-modified binder system and fillers
Packaging	50 lb. (22.7 kg) bag
Appearance / Color	Concrete gray
Shelf Life	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage Conditions	<ul style="list-style-type: none"> ▪ Store dry at 41 to 86 °F (5 to 30 °C). ▪ Condition material to 65 to 75 °F (18 to 24 °C) before using. ▪ Protect from moisture. If damp, discard material.

Product Data Sheet

SikaLevel®

August 2020, Version 01.05

020815030010000003

Density 133 lbs/ft³

(ASTM C348)
Tested at:
73 °F (23 °C)
50 % R.H.

TECHNICAL INFORMATION

Compressive Strength		50 °F (10 °C)	73 °F (23 °C)	86 °F (30 °C)	(ASTM C-109) Tested at: 73 °F (23 °C) 50 % R.H.
	24 hours	1,000 psi	1,250 psi	1,390 psi	
	7 days	1,625 psi	2,500 psi	2,600 psi	
	28 days	2,875 psi	3,750 psi	3,120 psi	
Flexural Strength	1,150 psi (8 MPa) (28 days)				(ASTM C348) Tested at: 73 °F (23 °C) 50 % R.H.
Tensile Adhesion Strength	Pull-Out Strength 3/16" (5 mm) thickness with SikalLevel® Primer > 290 psi (2 MPa)				(ACI 503)
Thermal Resistance	Suitable for use with underfloor heating systems				

APPLICATION INFORMATION

Mixing Ratio	1 gallon (3.79 L) of water per 50 lb. (22.7 kg) bag				
Coverage	Depth	Sq. Ft.			
	1/8" (3.2mm)	42 ft ²			
	1/4" (6.3mm)	21 ft ²			
	1/2" (12.5mm)	11 ft ²			
	1" (25mm)	5.3 ft ²			
	(Coverage figures do no include allowance for surface profile and porosity or material waste)				
Layer Thickness	<ul style="list-style-type: none">▪ 1/8" up to 2" (3 up to 50 mm)▪ Can be extended with pre-washed 3/8" pea-gravel up to 2.5" (64 mm)				
Ambient Air Temperature	41–86 °F (5–30 °C)				
Substrate Temperature	For application, between 41–86 °F (5–30 °C)				
Maturing time	Initial Set: 45–90 min. Final Set: 70–100 min.				(ASTM C-191) Tested at: 73 °F (23 °C) 50 % R.H.
Pot Life	Approx. 25 minutes				
Waiting / Recoat Times	Foot Traffic: 2–3 hours for foot traffic				
	Ready for Covering: <ul style="list-style-type: none">▪ Tile/Stone/non-moisture sensitive flooring: 2–3 hours▪ PVC/ Carpet/Vinyl/Rubber flooring: 1 day▪ Hardwood/Engineered Wood flooring: 3 days				
	For coatings (ex. epoxy): <ul style="list-style-type: none">▪ 1/8" depth: 3 to 4 days▪ 1/2" depth: 7 to 8 days▪ Over 1/2" depth: 14 to 15 days				

Please consult coating manufacturers for recommendations. It is always important to check the moisture content of the floor/slab before applying a coating. Meeting the specifications of the manufacturer. This can be done with a moisture meter.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

All substrate must be dry, stable, sound and free of all contaminants such as grease, oil, paint, wax, dust, curing and sealing compounds that will interfere with the penetration the primer and the adhesion of SikaLevel®.

Careful consideration should be given to the selection of the method of mechanical surface preparation and the timing of application of primer and underlayment. Immediately following mechanical preparation on some excessively porous substrates, outgassing will increase for a short period of time (approx. 48 hours) until equilibrium in slab vapor pressure and the ambient environment is reached. Consult Sika Technical Service for recommendations.

Concrete & Cement Substrates: Prepare concrete, cement and dense substrates, including ceramic, quarry and vinyl tiles by mechanical means, such as shot blasting, sandblasting, water-jetting, scarifying, or other appropriate methods, to achieve an open-textured, fine-gripping surface (ICRI - CSP 3 minimum). Weak surfaces should be removed. All cracks and holes should be similarly filled to prevent seepage. Repair with Sika® Level Skim Coat prior to priming and levelling. The compressive strength of the concrete substrate should be at least 2,900 psi (20 MPa) at 28 days with a minimum tensile strength of 200 psi (1.4 MPa).

Cutback Adhesive: Old water-soluble adhesives should be removed completely. Old water-resistant adhesives should be mechanically removed as far as possible. The complete mechanical removal of cutback (i.e. grinding, sanding and blasting) can be hazardous as old cutback adhesive may contain asbestos. Do not sand or grind adhesive residue. Harmful dust may result. Inhalation of asbestos dust may cause asbestosis or other serious bodily harm. Please consult the adhesive manufacturer and all applicable government agencies for rules and regulations concerning the removal of flooring and adhesives that contain asbestos.

Priming

Prime standard absorbent substrates such as concrete and cement with SikaLevel® Primer.

This product is not a vapor barrier and will allow free passage of moisture. Follow the directions of the floor covering manufacturer regarding the maximum allowable substrate moisture content and test the substrate prior to installing SikaLevel®.

MIXING

Pour 1 gallon (4 quarts) of cool potable water (70 °F) into a suitably sized and clean mixing container, using a calibrated measuring jug, or similar, to ensure strict control of the water content (do not over-watering). If available water is not at this temperature, then consideration should be given to cooling/heating the water. Add SikaLevel® to the water, while slowly stirring, adding the complete contents of the 50 lb. bags.

Mix with a high-speed drill (more than 650 rpm) and an egg beater style mixing paddle to blend water and powder for approximately 3 minutes, until a lump-free and uniform mix has been produced. Do not overmix or allow the paddle to rise above the level of material as this will introduce and entrap air into the mix, potentially shortening the working life or causing pinholing in the underlayment. Let the mixed material stand until the majority of air bubbles have dispersed.

APPLICATION

Pour the mix and spread using a smoothing trowel. Even surfaces are easily achieved using a pin leveler. In higher thickness using a spike roller is recommended. Avoid contact to vertical structures by putting in an edge strip such as foam tape.

If a second layer of leveling compound has to be applied, prime the first layer with Sika® Level Primer when the first layer is walkable. The maximum layer thickness must not be exceeded in case of two layer applications. The second layer must not exceed the layer thickness of the first layer.

Protect curing SikaLevel® layers from high ambient temperatures, direct sunlight and ensure an adequate air circulation.

The cured surface of SikaLevel® must be protected from any type of contamination by installing a suitable coating. Always install an adequate number of properly located test areas, to include the finish flooring, to determine the suitability of the product for its intended use. As floor coverings vary, always contact and rely upon the floor covering manufacturer for specific directions such as maximum allowable moisture content, adhesive selection, and intended end use of the product. Low substrate temperatures and/or high ambient humidity require longer drying times for primers. SikaLevel® is not intended to be use as a wear layer.

All cement based products have the potential for

Product Data Sheet

SikaLevel®

August 2020, Version 01.05

020815030010000003

cracking. Cracking, such as hair line cracking cannot be considered as a product defect or installation failure.

For large scale areas that require deeper applications, the following recommendations can be used to minimize material cost:

1. The material can be extended by adding up to 30 % of 20/30 grade sand during mixing to achieve up to 2" in one lift. A reduction in flow, approximately 15 %, can be expected. The final layer should be neat to allow for a smooth finished floor. When adding aggregate, expect coverage to increase by approximately .16 cu.ft. per 25 lbs of aggregate.

2. Pre-washed 3/8" pea-gravel can be pre-placed into the area being leveled allowing for up to 2" in one lift. Applicator must be aware that the aggregate can cause voids in the underlayment if not filled correctly. When adding aggregate, expect coverage to increase by approximately .16 cu.ft. per 25 lbs of aggregate. Multiple lifts can also be applied to achieve greater depths, making sure to prime with Sika® Level Primer in between lifts. If necessary, further detailed recommendations can be obtained by calling Sika Corporation's Technical Service Department. Over large areas, application by conventional piston, rotor-stator or underlayment type pumps is more appropriate. Thoroughly spike roll in two directions (90 °) to remove installation marks and any entrapped air, but avoid overworking.

CLEANING OF TOOLS

Clean tools in water immediately.

Disposal:

Empty packaging and dispose of in accordance with federal, state and local waste disposal regulations.

LIMITATIONS

- For interior use only. Not suitable for slopes or inclines > 0.5 %
- Do not apply SikaLevel® onto based, chipboard, particle board, hardboard, metal, gypsumbased floors or dimensionally unstable substrates.
- Always prime concrete and cement substrates with Sika® Level Primer.
- Protect SikaLevel® from excessive heat and moving air

by turning off radiant heating and forced air ventilation for 24 hours before installation and while the underlayment is curing.

- Do not exceed the recommended water dosage and use clean potable water.
- Temperature variations will affect working time, with low temperatures extending drying times.
- Protect newly applied SikaLevel® from condensation and water for at least 24 hours.
- Prevent contaminants, dust and dirt from coming into contact with the underlayment for at least 4 hours and do not expose to rolling dynamic loads for 2 days (at 73 °F, 50 % R. H.).
- If subsequent layers of SikaLevel® are installed on existing, cured SikaLevel®, mechanical preparation and re-priming is required.
- As the thickness of the underlayment will influence the time at which it can be overcoated or overlaid with stones, tiles, or coverings, the manufacturer of such materials must be consulted for guidance regarding substrate moisture content and other characteristics.
- SikaLevel® does not provide an aesthetic finish and is intended to receive a final floor covering.
- For adhesives other than SikaBond®, we recommend a test application prior to use.
- All cement based products have the potential for cracking. Cracking, such as hair line cracking cannot be considered as a product defect or installation failure.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

SikaLevel®
August 2020, Version 01.05
020815030010000003

SikaLevel-en-US-(08-2020)-1-5.pdf

