

PRODUCT DATA SHEET

Sikaflex® WS-242 FK + SikaBooster® AN-1M

(formerly WS-242FK + AN-1M)

Accelerated curing adhesive for plastic panel bonding

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base		Polyurethane
Color (CQP001-1)		Black
Cure mechanism		Moisture-curing ^A
Density (uncured)	Adhesive	1.27 kg/l
	SikaBooster® AN-1M	1.27 kg/l
Booster content	by weight	10.0 %
Viscosity (JASO M338-89)	Adhesive	80 Pa·s
	SikaBooster® AN-1M	18 Pa·s
Application temperature	Adhesive	20 – 40 °C
	SikaBooster® AN-1M	20 – 35 °C
	ambient	10 – 40 °C
Tack-free time (JASO M338-89)		15 minutes ^B
Shore A hardness (JASO M338-89)		48
Tensile strength (JASO M338-89)		5.2 MPa
Elongation at break (JASO M338-89)		350 %
Tensile lap-shear strength (JASO M338-89)		3.8 MPa
Shelf life	Adhesive	6 months ^C
	SikaBooster® AN-1M	6 months ^C
Mixer		MIXPAC™ ME 13-24T

CQP = Corporate Quality Procedure

^A) moisture provided by SikaBooster® AN-1M ^B) 20 °C / 65 % r.h.^C) stored below 25 °C in unopened container
DESCRIPTION

Sikaflex® WS-242 FK + SikaBooster® AN-1M is an accelerated adhesive system for plastic bonding and glazing applications. With the use of SikaBooster® AN-1M, it cures largely independent of atmospheric moisture. Suited for bonding materials relevant for panel bonding such as plastics, paints, glass, ceramic frits and e-coated systems in commercial vehicle production.

PRODUCT BENEFITS

- Accelerated curing and adhesion build-up
- Very good working characteristics
- Suitable for automated application
- Good adhesion to plastic materials without Primer

AREAS OF APPLICATION

Sikaflex® WS-242 FK + SikaBooster® AN-1M is suitable for automated panel bonding and glazing as well as elastic bonding in the automotive industry. Sikaflex® WS-242 FK + SikaBooster® AN-1M bonds well to numerous substrates. Common substrates are pre-treated ceramic frits and glasses with corresponding UV protection as well as cleaned e-coated and painted surfaces and plastic panels.

Seek manufacturer's advice and perform tests on original substrates before using Sikaflex® WS-242 FK + SikaBooster® AN-1M on materials prone to stress cracking.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex® WS-242 FK + SikaBooster® AN-1M

Version 01.01 (05 - 2026), en_US

012001233330243630

CURE MECHANISM

Sikaflex® WS-242 FK + SikaBooster® AN-1M cures by reaction with moisture provided by SikaBooster® AN-1M and largely independent from atmospheric moisture. For typical strength build up data see table below.

Time [min.]	Tensile lap-shear strength at 25 °C [MPa]
20	0.5
30	1.2
60	2.5

Table 1: Strength build-up of Sikaflex® WS-242 FK + SikaBooster® AN-1M

CHEMICAL RESISTANCE

Sikaflex® WS-242 FK + SikaBooster® AN-1M is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond.

All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

Application

Sikaflex® WS-242 FK + SikaBooster® AN-1M can be processed between 10 °C and 40 °C (ambient) but changes in reactivity and application properties have to be considered.

Consider that the viscosity will increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use.

To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

Sikaflex® WS-242 FK + SikaBooster® AN-1M can be processed with pump equipment.

The open time is significantly shorter in hot and humid climate. The glass must always be installed within the open time. Never join bonding parts if the adhesive has built a skin.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

For transparent substrates, bond faces must be fully UV protected by suitable design or means.

Removal

Uncured Sikaflex® WS-242 FK + SikaBooster® AN-1M may be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- General Guideline Bonding and Sealing with 1-component Sikaflex®

PACKAGING INFORMATION

Sikaflex® WS-242 FK

Pail	4 gal (US)
Drum	54 gal (US)

SikaBooster® AN-1M

Pail	20 kg
------	-------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by contacting SIKA's Technical Service Department via email at tsmh@us.sika.com. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling +1 800-933-7452.

PRODUCT DATA SHEET

Sikaflex® WS-242 FK + SikaBooster® AN-1M
Version 01.01 (05 - 2026), en_US
012001233330243630

Sika Corporation

30800 Stephenson Highway
Madison Heights, MI 48071
U.S.A.
Telephone: +1 248-577-0020
Email: tsmh@us.sika.com
www.sikausa.com

