

# PRODUCT DATA SHEET

## Sika® Duoflex NS

### TWO-COMPONENT, NON SAG, POLYSULFIDE SEALANT

#### PRODUCT DESCRIPTION

Sika® Duoflex NS is a two-component, non-sag, premium-quality polysulfide sealant, specifically designed for vertical and overhead surfaces. USDA accepted. Sika® Duoflex NS meets - ASTM C-920, Type M, Grade NS, Class 25, Use I, NT, M, G, A and O.

#### USES

Sika® Duoflex NS is suitable for either exterior or interior use to seal both static and dynamic joints:

- Joints in precast concrete.
- Joints in glass and metal curtain wall construction.
- Expansion and control joints in concrete and masonry walls.
- Joints in metal siding.
- Perimeters of aluminum window frames and metal panels.
- Joints located in gas stations /refueling environments.

#### CHARACTERISTICS / ADVANTAGES

- Tough, elastic, rubber-like seal.
- Remains flexible with expansion and contraction of building component without adhesive or cohesive failure, based on good joint design.
- Stays resilient within a wide temperature range.
- Excellent resistance to water, oils, grease, most solvents, mild acids and alkalis.
- Tenacious adhesion to concrete, metal, wood, glass, stone, ceramic and masonry surfaces in any combination, typically without the need for priming with Sika® Duoflex Primer-5050.
- Effective under constant immersion or saturated conditions, when suitably primed.

#### PRODUCT INFORMATION

<b>Packaging</b>	1.5 gallon (5.7 liter) unit
<b>Color</b>	Bronze
<b>Shelf Life</b>	1 year in original, unopened packaging.
<b>Storage Conditions</b>	Store dry between 40 and 95 °F (4 and 35 °C). Condition material to 40 to 100 °F before application. Preconditioning units to approximately 70 °F (21 °C) is necessary when working at the far ends of the application range.

## TECHNICAL INFORMATION

Shore A Hardness	25–30	(73 °F (23 °C) 50 % R.H.) (ASTM D-2240)
Abrasion Resistance	Excellent	
Tensile Strength	150–200 psi (1.03–1.38 psi)	(73 °F (23 °C) 50 % R.H.) (ASTM D-412)
Elongation at Break	500–550 %	(73 °F (23 °C) 50 % R.H.) (ASTM D-412)
Movement Capability	±25 %	(73 °F (23 °C) 50 % R.H.)
Resistance to Static Puncture	Excellent	
Chemical Resistance	(see Sika Duoflex chemical resistance chart)	
UV Exposure	Very good	
Colour Stability	Very good	
Service Temperature	-40 to 170 °F (-40 to 77 °C)	

## APPLICATION INFORMATION

Coverage	<b>1 gallon: Yield in Linear feet</b>			
	<b>Width/Depth</b>	<b>1/4"</b>	<b>3/8"</b>	<b>1/2"</b>
	1/4"	307.9		
	3/8"	205.3	136.8	
	1/2"	153.9	102.6	77.0
	3/4"	102.6	68.4	51.3
	1"			38.5
	1.25"			30.8
	1.5"			25.7
Ambient Air Temperature	40 to 100 °F (4 to 38 °C) Sealant should be installed when joint is at mid-range of its anticipated movement.			
Substrate Temperature	40 to 100 °F (4 to 38 °C) Sealant should be installed when joint is at mid-range of its anticipated movement.			
Pot Life	1 hour			(73 °F (23 °C) 50 % R.H.)
Cure Time	7 days			(73 °F (23 °C) 50 % R.H.)
Tack Free Time	6 hours			(73 °F (23 °C) 50 % R.H.)

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

All joint surfaces must be clean, sound, dry and frost-free. Joint walls must be free of oils, grease, paints, coatings, sealers, curing compound residues, and any other foreign matter that might prevent adhesion. Ideally this should be accomplished by mechanical means (e.g. sandblasting, abrasive grinding, etc.). Bond breaker tape or backer rod must be used in bottom of joint to prevent bond.

**Joint Design:** Proper joint design for moving joints is 2:1 width to depth ratio, with a recommended 1/4" (6 mm) minimum and 1/2" (13 mm) maximum depth of sealant.

For non-moving joints, the width to depth ratio can vary.

**Priming:** For maximum adhesion, including in submerged or immersed applications, the use of Sika® Duoflex Primer-5050 is necessary. Consult your Sika Technical Service Representative if unsure if primer is necessary. A uniform glossy sheen after priming indicates adequate primer. Some surfaces, such as porous concrete, may require two coats. Primer must be tack-free before applying sealant. Sealant must be applied same day as primer. Primed areas left overnight should be re-primed.

### MIXING

Pour entire contents of Component B into pail of Component A and mix using a low speed drill (100–300

rpm) and Sika mixing paddle. Mix for 3–5 minutes to achieve uniform color and consistency. Scrape down sides of pail periodically. Avoid entrapment of air during mixing. Mixed material must be used within the pot life parameters given. Do not attempt to thin or use material that has started to harden. The individual components are formulated, manufactured and shipped to be used together.

When mixed in cold weather (<50 °F), do not force the mixing paddle to the bottom of the pail. After adding Component B in Component A, mix the top 1/2 to 3/4 of the pail in the first minute of mixing. After scraping down the sides of the pail, mix again for another minute. The paddle should reach the bottom of the pail between the first and second minute of mixing. Scrap down the sides of the pail a second time and then mix for an additional 2-3 minutes until sealant is well blended.

### APPLICATION METHOD / TOOLS

Recommended application temperatures 40 to 100 °F (4 to 38 °C). Pre-conditioning units to approximately 70 °F (21 °C) is necessary when working at the far ends of the application range. Move pre-conditioned units to work areas just prior to application. Apply sealant only to clean, sound, dry, and frost-free substrates. Sika® Duoflex NS should be applied into joints when joint slot is at mid-point of its designed expansion and contraction. To place, load directly into bulk gun or use a follower plate loading system. Place nozzle of gun into bottom of joint and fill entire joint. Keeping the nozzle deep in the sealant, continue with a steady flow of sealant preceding nozzle to avoid air entrapment. Also, avoid overlapping of sealant since this also entraps air. Dry tool as required.

### LIMITATIONS

- Do not use the B component from NS with the A component for SL and vice versa.
- The ultimate performance of Sika Duoflex NS depends on good joint design and proper application
- Primary and secondary immersion applications; Sika® Duoflex Primer-5050 must be used
- Do not apply when moisture vapor transmission exists since this can cause bubbling within the sealant.
- When overcoating, an on-site test is recommended to determine actual compatibility.

Not suitable for:

- Joint movement more than ± 25 %.
- Structural glazing applications.
- Improperly prepared or contaminated surfaces.
- Joints involving adhesion to painted surfaces (Consult your Sika Technical Service Representative).

### BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual

site conditions and curing conditions.

### OTHER RESTRICTIONS

See Legal Disclaimer.

### ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792



Product Data Sheet  
Sika® Duoflex NS  
April 2019, Version 01.02  
02051507000000024

SikaDuoflexNS-en-US-(04-2019)-1-2.pdf

