

PRODUCT DATA SHEET

DRYLOK® E1

Semi-gloss, latex-base, 1-part epoxy concrete floor paint

DESCRIPTION

DRYLOK® E1 is a semi-gloss high-performance coating for both commercial and residential use, DRYLOK® E1 is a latex based, 1-part epoxy concrete floor paint that utilizes an advanced epoxy ester resin fortified formulation to deliver greater protection and durability.

USES

Specially formulated to protect and beautify:

- interior/exterior concrete floors
- garage floors
- basement floors
- walkways
- patios

CHARACTERISTICS / ADVANTAGES

- Resists hot tire pick-up, chemicals, oil, grease, and gasoline stains
- Formulated using Advanced Epoxy Ester Resin for a durable finish
- Easy to maintain
- Semi-gloss finish
- Apply by brush or roller

PRODUCT DATA SHEET

DRYLOK® E1

September 2025, Version 01.01
020811020020000329

PRODUCT INFORMATION

Composition	Latex base				
Packaging	<u>Size</u>	<u>PC/Case</u>	<u>Color</u>	<u>Order No.</u>	<u>Old Order No.</u>
	1 gal	2	Tint Base	832394	28413
	1 gal	2	Gray	832392	23713
	1 gal	2	Platinum	832393	23813
Shelf life	2 years in original unopened container				
Storage conditions	Store between 50°F (10°C) and 85°F (29°C). Extreme heat or freezing temperatures can damage the product, causing it to separate or thicken. Avoid Freezing. Keep away from direct sunlight.				
Density	<u>Platinum</u>		<u>9.53 (LBS./US GAL.)</u>		
	<u>Gray</u>		<u>9.62 (LBS./US GAL.)</u>		
	<u>Tint Base</u>		<u>9.49 (LBS./US GAL.)</u>		
Wet Film Thickness	4-5 wet mils per coat				
pH-Value	8.0-9.0				
Solid content	<u>Platinum</u>		<u>42.76% (by weight)</u>		
	<u>Gray</u>		<u>43.51% (by weight)</u>		
	<u>Tint Base</u>		<u>42.46% (by weight)</u>		
Viscosity	80 ± 3 KU				
Appearance	Semi-gloss finish Surface appearance depends upon condition and porosity of concrete/masonry surface. Highly porous masonry/concrete may require additional coats to achieve full gloss.				

TECHNICAL INFORMATION

Freeze thaw resistance	Freeze/Thaw stable
------------------------	--------------------



APPLICATION INFORMATION

Number of Coats	Max. 2	
Coverage	300–400 ft² (27.87–37.16 m²) per gallon (Recommended film thickness/coat: 4-5 wet mils/coat)	
Ambient air temperature	50-90°F (10-32°C) during application and for a minimum of 4 hrs after application.	
Substrate temperature	50-90°F (10-32°C) during application and for a minimum of 4 hrs after application.	
Curing time	Open Up To Light use (foot traffic)	4 hours
	Open Up To Heavy use (foot traffic)	24 hours
	Open Up To Vehicular traffic	5-7 days
	Max. Resistance Properties Reached	3-5 days
Drying time	To touch	30 minutes-1 hour
	To recoat	4 hours

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

DRYLOK® E1 is recommended for light commercial, industrial, and residential floors not coated with a 2-part epoxy.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data

Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

FIRST AID

EYES: Flush immediately with large amounts of water for at least 15 minutes. Consult a physician if irritation persists.

SKIN: Wash affected areas with soap and water. Consult a physician if irritation persists.

INGESTION: Give 1 or 2 glasses of water. If individual is drowsy or unconscious do not give anything by mouth. Consult a physician, medical facility, or poison control center for advise about whether to induce vomiting.

INHALATION: Remove to fresh air.

PRODUCT DATA SHEET

DRYLOK® E1

September 2025,

Version 01.01

020811020020000329

DRYLOK®

BUILDING TRUST



APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

General Surface Preparation:

Surfaces must be thoroughly cleaned and free from dirt, dust, grease, oil, soap, wax, concrete curing membranes, and the oily film left by sweeping compounds. Stains on the surface should be removed using a heavy duty detergent until the surface is clean. Rinse thoroughly with clean water and allow to dry completely. If using a pressure washer, do not use a setting above 1750 PSI to avoid damaging the concrete. Surface must be completely dry before painting. To verify the surface is completely dry and free of residual trapped moisture, tape a 1ft. by 1ft. square piece of plastic onto the surface and let stand for 24 hours. If moisture is present on the concrete side of the plastic, the surface has not dried sufficiently. Allow additional drying and retest. Surface porosity is important for proper product adhesion. Before application, test concrete porosity by sprinkling a few drops of water onto the surface in several areas. If water is readily absorbed, you are ready to paint. If it beads or lays on the surface, additional cleaning and etching is required. Refer to "ACID ETCHING INSTRUCTIONS" below.

Old/Weathered, or Previously Painted Surfaces Preparation:

Remove peeling paint and clean (see "General Surface Preparation" above). Mildew should be removed using a suitable mildew remover. Allow to dry completely. Glossy painted surfaces must be dulled or sanded to improve adhesion. Do not apply to floors previously painted with 2 component epoxy paints/coatings. For bare surfaces that are highly troweled or smooth, acid etching is required. Refer to "ACID ETCHING INSTRUCTIONS" below. Do not etch painted surfaces.

New/Unpainted Surfaces, Garage Floors, Exterior Concrete Preparation:

New concrete must cure for 30 days. For best results,

new concrete should be washed and scrubbed thoroughly to remove any surface contaminants. Allow to dry completely. All surfaces subject to vehicle traffic, highly troweled or extremely smooth concrete, must be acid etched. Refer to "ACID ETCHING INSTRUCTIONS" below.

SUBSTRATE QUALITY / PRE-TREATMENT

ACID ETCHING INSTRUCTIONS

Do not etch painted surfaces. Acid etching will dissolve certain minerals in the top layer of concrete, creating a more porous surface for improved adhesion. To etch concrete, predampen the entire surface then use DRYLOK® Concrete and Masonry Etch & Cleaner according to label directions. Apply until the surface has the look and feel of 150-grit sandpaper. The acid etching process may be repeated until the proper texture is achieved.

Test the concrete's porosity by sprinkling a few drops of water on the surface. If the water droplets do not readily penetrate into the prepared concrete, additional acid etching is required. All residual acid must be removed from the surface. Rinse thoroughly and allow to dry (see "To Check for Trapped Moisture" above) prior to application of the DRYLOK® E1.

On areas that have had efflorescence (saltlike deposit) problems or exposure to excess levels of salt compounds, it is recommended that DRYLOK® Concrete Protector be applied according to label directions prior to application of the DRYLOK® E1.

WARNING

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and

PRODUCT DATA SHEET

DRYLOK® E1

September 2025,

Version 01.01

020811020020000329

DRYLOK®

BUILDING TRUST



your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

MIXING

Mix two gallons of the same color paint together to ensure uniform color and avoid shade variations.

APPLICATION

STIR THOROUGHLY BEFORE AND DURING APPLICATION. Air and surface temperature must be between 50°-90°F (10°-32°C) during application and for a minimum of 4 hours after application.

For exterior surfaces, do not apply if rain is expected within 24 hours. Wait for a dry, rain-free period. DO NOT THIN. Apply an even coat using a 3/8" (9.525 mm) nap roller or nylon/polyester brush. Do not paint in direct sunlight or apply to a hot surface. Provide good ventilation for normal drying. Allow first coat to dry 4 hours prior to applying the second coat. High humidity and low temperatures may require longer drying times. The second coat should be applied in a cross direction to the first coat to achieve color uniformity. Do not apply more than 2 coats. When using 2 or more containers of the same color of DRYLOK® E1, mix together to assure color uniformity.

NOTE: Painted surfaces may become slippery when wet. If a slip resistant surface is desired add 2-4 oz. (59-118 mL) of DRYLOK® Non-Skid Texture Additive per gallon to DRYLOK® E1.

IMPORTANT

Floors that are subjected to hydrostatic pressure (water seeping from underneath the floor) or are continually damp cannot be satisfactorily painted with any paint or coating. Moisture on basement floors caused by water seeping through masonry walls or through floor-wall joints or cracks must first be eliminated. Use DRYLOK® Fast Plug®, a quick setting hydraulic cement, to fill floor-wall joints or cracks. If the basement floor is subjected to hydrostatic pressure, use DRYLOK® Floor & Wall Masonry Waterproofer to control water. Then, apply DRYLOK® E1 per label directions. In addition, outside work may be required to eliminate water infiltration.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at www.drylok.com or by calling SIKA's Technical Service Department at 1-800-272-3235, option 2. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and

PRODUCT DATA SHEET

DRYLOK® E1

September 2025,

Version 01.01

020811020020000329

DRYLOK®

BUILDING TRUST



Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-272-3235, option 2.

DRYLOKE1-en-USDRYLOK-(09-2025)-1-1.pdf

PRODUCT DATA SHEET

DRYLOK® E1

September 2025,

Version 01.01

020811020020000329

DRYLOK®

BUILDING TRUST

