



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

SECTION 1. IDENTIFICATION

Product name SikaBond-620 slate Formerly MWeld 620 SLATE

000000000050438626 Product code

Manufacturer or supplier's details

Company name of supplier Sika MBCC US LLC

Address 201 POLITO AVE

Lyndhurst NJ 07071

Emergency telephone ChemTel: +1-813-248-0585

Recommended use of the chemical and restrictions on use

Recommended use Product for construction chemicals

Restrictions on use Reserved for industrial and professional use.

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with 29 CFR 1910.1200

Skin corrosion/irritation

Serious eye damage/eye

irritation

: Category 2B

Carcinogenicity 1B

Specific target organ toxicity

- single exposure

Specific target organ toxicity : 2 (Auditory organ)

- repeated exposure

Short-term (acute) aquatic

hazard

: 2

Long-term (chronic) aquatic

hazard

3

GHS label elements

Hazard pictograms





Signal Word Danger

SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Hazard Statements : H320 Causes eye irritation.

H315 Causes skin irritation.

H335 May cause respiratory irritation.

H350 May cause cancer.

H373 May cause damage to organs (Auditory organ) through

prolonged or repeated exposure.

H412 Harmful to aquatic life with long lasting effects.

H401 Toxic to aquatic life.

Precautionary Statements

Prevention:

P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

P201 Obtain special instructions before use.

P271 Use only outdoors or in a well-ventilated area.

P273 Avoid release to the environment.

P202 Do not handle until all safety precautions have been read

and understood.

P260 Do not breathe dust or mist.

P264 Wash face, hands and any exposed skin thoroughly after

handling.

Response:

P308 + P311 IF exposed or concerned: Call a POISON

CENTER/ doctor.

P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do Continue ringing

to do. Continue rinsing.

P314 Get medical advice/ attention if you feel unwell.

P304 + P340 IF INHALED: Remove person to fresh air and

keep comfortable for breathing.

P303 + P352 IF ON SKIN (or hair): Wash with plenty of soap

anu water.

P332 + P313 If skin irritation occurs: Get medical advice/ atten-

tion.

P337 + P311 If eye irritation persists: Call a POISON CENTER

or doctor/physician.

P362 + P364 Take off contaminated clothing and wash it before

reuse.

Storage:

P403 + P233 Store in a well-ventilated place. Keep container

tightly closed.

P405 Store locked up.

Disposal:

P501 Dispose of contents/container to appropriate hazardous

waste collection point.

Other hazards

No data available.

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Chemical nature : adhesive

Components

Chemical name	CAS-No.	Concentration (% w/w)
xylene	1330-20-7	>= 15 - < 20
ethylbenzene	100-41-4	>= 10 < 25
Silicon dioxide	7631-86-9	>= 3 - < 5
Limestone	1317-65-3	>= 1 - < 5
Titanium dioxide	13463-67-7	>= 1 - < 3
White mineral oil (petroleum)	8042-47-5	>= 1 - < 3
Lubricating oils (petroleum), C20-50,	72623-87-1	>= 1 - < 3
hydrotreated neutral oil-based;		
Baseoil — unspecified; [A complex		
combination of hydrocarbons ob-		
tained by treating light vacuum gas		
oil, heavy vacuum gas oil and solvent		
deasphalted residual oil with hydro-		
gen in the presence of a catalyst in a		
two stage process with dewaxing		
being carried out between the two stages. It consists predominantly of		
hydrocarbons having carbon num-		
bers predominantly in the range of		
C20 through C50 and produces a		
finished oil with a viscosity of approx-		
imately 32cSt at 40 oC. It contains a		
relatively large proportion of saturat-		
ed hydrocarbons.]		
Lubricating oils (petroleum), C15-30,	72623-86-0	>= 1 - < 3
hydrotreated neutral oil-based;	72020 00 0	7-1 10
Baseoil — unspecified; [A complex		
combination of hydrocarbons ob-		
tained by treating light vacuum gas oil		
and heavy vacuum gas oil with hy-		
drogen in the presence of a catalyst		
in a two stage process with dewaxing		
being carried out between the two		
stages. It consists predominantly of		
hydrocarbons having carbon num-		
bers predominantly in the range of		
C15 through C30 and produces a		
finished oil having a viscosity of ap-		
proximately 15cSt at 40 oC. It con-		
tains a relatively large proportion of		
saturated hydrocabons.]		
Lubricating oils (petroleum), C20-50,	72623-85-9	>= 1 - < 3
hydrotreated neutral oil-based, high-		
viscosity; Baseoil — unspecified; [A		
complex combination of hydrocar-		
bons obtained by treating light vacu-		
um gas oil, heavy vacuum gas oil,		
and; solvent deasphalted residual oil		



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

with hydrogen in the presence of a	1	
catalyst in a two stage process with		
dewaxing being carried out between		
the two stages. It consists predomi-		
nantly of hydrocarbons having carbon		
1 2 2		
numbers predominantly in the range		
of C20 through C50 and produces a		
finished oil having a viscosity of ap-		
proximately 112cSt at 40 oC. It con-		
tains a relatively large proportion of		
saturated hydrocarbons.]	0.47.40.77.0	
Distillates (petroleum), hydrotreated	64742-55-8	>= 1 - < 3
light paraffinic; Baseoil — unspeci-		
fied; [A complex combination of hy-		
drocarbons obtained by treating a		
petroleum fraction with hydrogen in		
the presence of a catalyst. It consists		
of hydrocarbons having carbon num-		
bers predominantly in the range of		
C15 through C30 and produces a		
finished oil with a viscosity of less		
than 100 SUS at 100 oF (19cSt at 40		
oC). It contains a relatively large pro-		
portion of saturated hydrocarbons.]		
Distillates (petroleum), hydrotreated	64742-54-7	>= 1 - < 3
heavy paraffinic; Baseoil — unspeci-		
fied; [A complex combination of hy-		
drocarbons obtained by treating a		
petroleum fraction with hydrogen in		
the presence of a catalyst. It consists		
of hydrocarbons having carbon num-		
bers predominantly in the range of		
C20 through C50 and produces a		
finished oil of at least 100 SUS at		
100oF (19cSt at 40 oC). It contains a		
relatively large proportion of saturat-		
ed hydrocarbons.]		
Distillates (petroleum), hydrotreated	64742-53-6	>= 1 - < 3
light naphthenic; Baseoil — unspeci-	5 TI TZ 00 0	
fied; [A complex combination of hy-		
drocarbons obtained by treating a		
petroleum fraction with hydrogen in		
the presence of a catalyst. It consists		
of hydrocarbons having carbon num-		
bers predominantly in the range of		
C15 through C30 and produces a		
finished oil with a viscosity of less		
than 100 SUS at 100 oF (19cSt at 40		
oC). It contains relatively few normal		
paraffins.]		
Distillates (petroleum), hydrotreated	64742-47-8	>= 1 - < 3
light		
Distillates (petroleum), hydrotreated	64742-46-7	>= 1 - < 3





Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

middle; Gasoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C11 through C25 and boiling in the range of approximately; 205oC to 400oC (401 oF to 752 oF).]		
Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C20-40, branched and cyclic	178603-65-1	>= 1 - < 3
Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C15-30, branched and cyclic	178603-64-0	>= 1 - < 3
Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C25-55, branched and cyclic	178603-66-2	>= 1 - < 3
Lubricating oils (petroleum), C15-30, hydrotreated neutral oil-based, contg. solvent deasphalted residual oil	72623-84-8	>=1-<3
bis(2,2,6,6-tetramethyl-4- piperidyl)sebacate	52829-07-9	>= 0.1 - < 0.2

SECTION 4. FIRST AID MEASURES

General advice : Move out of dangerous area.

Show this material safety data sheet to the doctor in attend-

ance.

Do not leave the victim unattended.

If inhaled : If unconscious, place in recovery position and seek medical

advice.

If symptoms persist, call a physician.

In case of skin contact : If skin irritation persists, call a physician.

If on skin, rinse well with water. If on clothes, remove clothes.

In case of eye contact : Immediately flush eye(s) with plenty of water.

Remove contact lenses. Protect unharmed eye.

Keep eye wide open while rinsing.

If eye irritation persists, consult a specialist.

If swallowed : Induce vomiting immediately and call a physician.

Keep respiratory tract clear.

Do not give milk or alcoholic beverages.

Never give anything by mouth to an unconscious person.

SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

If symptoms persist, call a physician. Take victim immediately to hospital.

Most important symptoms and effects, both acute and

delayed

Causes skin and eye irritation.

May cause respiratory irritation.

May cause cancer.

Notes to physician : Treat symptomatically.

SECTION 5. FIRE-FIGHTING MEASURES

Suitable extinguishing media : Water spray

Foam
Dry powder

Carbon dioxide (CO2)

Unsuitable extinguishing

media

High volume water jet

Specific hazards during fire

fighting

Do not allow run-off from fire fighting to enter drains or water

courses.

Further information : Collect contaminated fire extinguishing water separately. This

must not be discharged into drains.

Fire residues and contaminated fire extinguishing water must

be disposed of in accordance with local regulations.

Special protective equipment:

for fire-fighters

Wear self-contained breathing apparatus for firefighting if nec-

essary.

SECTION 6. ACCIDENTAL RELEASE MEASURES

Personal precautions, protec: :

tive equipment and emer-

gency procedures

Use personal protective equipment.

Avoid dust formation. Avoid breathing dust.

Environmental precautions : Prevent product from entering drains.

Prevent further leakage or spillage if safe to do so.

If the product contaminates rivers and lakes or drains inform

respective authorities.

Methods and materials for containment and cleaning up

Keep in suitable, closed containers for disposal.

SECTION 7. HANDLING AND STORAGE

Advice on protection against

fire and explosion

Avoid dust formation.

Provide appropriate exhaust ventilation at places where dust

is formed.

Advice on safe handling : Avoid formation of respirable particles.





Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Do not breathe vapors/dust.

Avoid exposure - obtain special instructions before use.

Avoid contact with skin and eyes. For personal protection see section 8.

Smoking, eating and drinking should be prohibited in the ap-

plication area.

Provide sufficient air exchange and/or exhaust in work rooms. Dispose of rinse water in accordance with local and national

regulations.

Conditions for safe storage : Keep container tightly closed in a dry and well-ventilated

place.

Containers which are opened must be carefully resealed and

kept upright to prevent leakage. Observe label precautions.

Electrical installations / working materials must comply with

the technological safety standards.

Further information on stor-

age conditions

Keep only in the original container in a cool, dry, well-

ventilated place away from ignition sources, heat or flame.

Protect from direct sunlight.

Materials to avoid : Observe VCI storage rules.

Recommended storage tem-

perature

32 °F / 0 °C

Further information on stor-

age stability

Minimum storage temperature:

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
ethylbenzene	100-41-4	TWA value	20 ppm	ACGIHTLV
		STEL value	125 ppm 545 mg/m3	NIOSH
		REL value	100 ppm 435 mg/m3	NIOSH
		PEL	100 ppm 435 mg/m3	29 CFR 1910.1000 (Table Z-1)
		TWA value	100 ppm 435 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		STEL value	125 ppm 545 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		TWA	20 ppm	ACGIH



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

		TWA	100 ppm 435 mg/m3	NIOSH REL
		ST	125 ppm 545 mg/m3	NIOSH REL
		TWA	100 ppm 435 mg/m3	OSHA Z-1
		TWA	100 ppm 435 mg/m3	OSHA P0
		STEL	125 ppm 545 mg/m3	OSHA P0
Limestone	1317-65-3	REL value (Respirable)	5 mg/m3	NIOSH
		REL value (Total)	10 mg/m3	NIOSH
		PEL (Respirable fraction)	5 mg/m3	29 CFR 1910.1000 (Table Z-1)
		PEL (Total dust)	15 mg/m3	29 CFR 1910.1000 (Table Z-1)
		TWA value (Respirable fraction)	5 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		TWA value (Total dust)	15 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		TWA (total dust)	15 mg/m3	OSHA Z-1
		TWA (respirable fraction)	5 mg/m3	OSHA Z-1
		TWA (Total dust)	15 mg/m3	OSHA P0
		TWA (respirable dust fraction)	5 mg/m3	OSHA P0
		TWA (Respirable)	5 mg/m3 (Calcium car- bonate)	NIOSH REL
		TWA (total)	10 mg/m3 (Calcium car- bonate)	NIOSH REL
xylene	1330-20-7	TWA value	100 ppm	ACGIHTLV
		STEL value	150 ppm	ACGIHTLV
		PEL	100 ppm 435 mg/m3	29 CFR 1910.1000 (Table Z-1)
		TWA value	100 ppm 435 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		STEL value	150 ppm 655 mg/m3	29 CFR 1910.1000 (Table Z-1-A)



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

	1	1		1
		REL value	100 ppm 435 mg/m3	NIOSH
		STEL value	150 ppm 655 mg/m3	NIOSH
		TWA	100 ppm 435 mg/m3	OSHA Z-1
		TWA	100 ppm	ACGIH
		STEL	150 ppm	ACGIH
		STEL	150 ppm 655 mg/m3	OSHA P0
		TWA	100 ppm 435 mg/m3	OSHA P0
Silicon dioxide	7631-86-9	REL value	6 mg/m3	NIOSH
		TWA value	6 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		TWA value	20 millions of particles per cubic foot of air	29 CFR 1910.1000 (Table Z-3)
		TWA value	0.8 mg/m3	29 CFR 1910.1000 (Table Z-3)
		TWA (Dust)	20 Million parti- cles per cubic foot (Silica)	OSHA Z-3
		TWA (Dust)	80 mg/m3 / %SiO2 (Silica)	OSHA Z-3
		TWA (Respirable dust)	0.05 mg/m3 (Silica)	NIOSH REL
		TWA	6 mg/m3 (Silica)	NIOSH REL
White mineral oil (petroleum)	8042-47-5	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
		STEL value (Mist)	10 mg/m3	NIOSH
		REL value (Mist)	5 mg/m3	NIOSH
		PEL (Mist)	5 mg/m3	29 CFR 1910.1000 (Table Z-1)
		TWA value (Mist)	5 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal- able particu- late matter)	5 mg/m3	ACGIH
		TWA (Mist)	5 mg/m3	OSHA P0
		TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

Titanium dioxide	13463-67-7	TWA value	10 mg/m3	ACGIHTLV
	10.000.	PEL (Total	15 mg/m3	29 CFR
		dust)	10 1119/1110	1910.1000
				(Table Z-1)
		TWA value	10 mg/m3	29 CFR
		(Total dust)		1910.1000
		(10000000000000000000000000000000000000		(Table Z-1-A)
		TWA (total	15 mg/m3	OSHA Z-1
		dust)	, a mg, me	
		TWA (Total	10 mg/m3	OSHA P0
		dust)		
		TWA	10 mg/m3	ACGIH
			(Titanium dioxide)	
Distillates (petroleum), hy-	64742-46-7	TWA value	5 mg/m3	ACGIHTLV
drotreated middle; Gasoil —		(Inhalable		
unspecified; [A complex com-		raction)		
bination of hydrocarbons ob-		,		
tained by treating a petroleum				
fraction with hydrogen in the				
presence of a catalyst. It con-				
sists of hydrocarbons having				
carbon numbers predominantly				
in the range of C11 through				
C25 and boiling in the range of				
approximately; 205oC to				
400oC (401 oF to 752 oF).]				
, , ,		STEL value	10 mg/m3	NIOSH
		(Mist)		
		REL value	5 mg/m3	NIOSH
		(Mist)		
		PEL (Mist)	5 mg/m3	29 CFR
				1910.1000
				(Table Z-1)
		TWA value	5 mg/m3	(Table Z-1) 29 CFR
		TWA value (Mist)	5 mg/m3	(Table Z-1) 29 CFR 1910.1000
		(Mist)		(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A)
		(Mist) TWA (Mist)	5 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1
		(Mist) TWA (Mist) TWA (Mist)	5 mg/m3 5 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0
		(Mist) TWA (Mist) TWA (Mist) TWA (Mist)	5 mg/m3 5 mg/m3 5 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL
		(Mist) TWA (Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist)	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL NIOSH REL
Distillates (petroleum), hy-	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL
Distillates (petroleum), hydrotreated light	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL NIOSH REL
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol)	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL NIOSH REL ACGIHTLV
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Desig-	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL NIOSH REL
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA P0 NIOSH REL NIOSH REL ACGIHTLV
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-aerosol)	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon vapor)	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA PO NIOSH REL NIOSH REL ACGIHTLV
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-aerosol) REL value	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon vapor)	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA PO NIOSH REL NIOSH REL ACGIHTLV NIOSH
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-aerosol) REL value TWA (Mist)	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon vapor)	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA PO NIOSH REL NIOSH REL ACGIHTLV NIOSH OSHA Z-1
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-aerosol) REL value	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon vapor) 100 mg/m3 5 mg/m3 200 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA PO NIOSH REL NIOSH REL ACGIHTLV NIOSH
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-aerosol) REL value TWA (Mist)	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon vapor) 100 mg/m3 5 mg/m3 200 mg/m3 (total hydrocarbon	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA PO NIOSH REL NIOSH REL ACGIHTLV NIOSH OSHA Z-1
	64742-47-8	(Mist) TWA (Mist) TWA (Mist) TWA (Mist) ST (Mist) TWA value (Non-aerosol) Skin Designation (Non-aerosol) REL value TWA (Mist)	5 mg/m3 5 mg/m3 5 mg/m3 10 mg/m3 200 mg/m3 (total hydrocarbon vapor) 100 mg/m3 5 mg/m3 200 mg/m3	(Table Z-1) 29 CFR 1910.1000 (Table Z-1-A) OSHA Z-1 OSHA PO NIOSH REL NIOSH REL ACGIHTLV NIOSH OSHA Z-1



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

1	1	TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Distillates (petroleum), hydrotreated light naphthenic; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C15 through C30 and produces a finished oil with a viscosity of less than 100 SUS at 100 oF (19cSt at 40 oC). It contains relatively few normal paraffins.]	64742-53-6	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal- able particu- late matter)	5 mg/m3	ACGIH
		TWA (Mist)	5 mg/m3	OSHA P0
		TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Distillates (petroleum), hydrotreated heavy paraffinic; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C20 through C50 and produces a finished oil of at least 100 SUS at 100oF (19cSt at 40 oC). It contains a relatively large proportion of saturated hydrocarbons.]	64742-54-7	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
		REL value (Mist)	5 mg/m3	NIOSH
		STEL value (Mist)	10 mg/m3	NIOSH
		PEL (Mist)	5 mg/m3	29 CFR 1910.1000 (Table Z-1)
		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal- able particu- late matter)	5 mg/m3	ACGIH
		TWA (Mist)	5 mg/m3	OSHA P0



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

1	1	TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Distillates (petroleum), hydrotreated light paraffinic; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C15 through C30 and produces a finished oil with a viscosity of less than 100 SUS at 100 oF (19cSt at 40 oC). It contains a relatively large proportion of saturated hydrocarbons.]	64742-55-8	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
bono.j		STEL value (Mist)	10 mg/m3	NIOSH
		REL value (Mist)	5 mg/m3	NIOSH
		PEL (Mist)	5 mg/m3	29 CFR 1910.1000 (Table Z-1)
		TWA value (Mist)	5 mg/m3	29 CFR 1910.1000 (Table Z-1-A)
		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal- able particu- late matter)	5 mg/m3	ACGIH
		TWA (Mist)	5 mg/m3	OSHA P0
		TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Lubricating oils (petroleum), C20-50, hydrotreated neutral oil-based, high-viscosity; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating light vacuum gas oil, heavy vacuum gas oil, and; solvent deasphalted residual oil with hydrogen in the presence of a catalyst in a two stage process with dewaxing being carried out between the two stages. It consists predominantly of hydrocarbons having carbon numbers predominantly in the range of C20 through C50 and	72623-85-9	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

produces a finished oil having a viscosity of approximately 112cSt at 40 oC. It contains a relatively large proportion of saturated hydrocarbons.]				
, ,		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal-	5 mg/m3	ACGIH
		able particu-	o mg/mo	7.00111
		late matter)		
		TWA (Mist)	5 mg/m3	OSHA P0
		TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Lubricating oils (petroleum),	72623-86-0	TWA value	5 mg/m3	ACGIHTLV
C15-30, hydrotreated neutral oil-based; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating light vacuum gas oil and heavy vacuum gas oil with hydrogen in the presence of a catalyst in a two stage process with dewaxing being carried out between the two stages. It consists predominantly of hydrocarbons having carbon numbers predominantly in the range of C15 through C30 and produces a finished oil having a viscosity of approximately 15cSt at 40 oC. It contains a relatively large proportion of saturated hydrocabons.]	72023-00-0	(Inhalable fraction)		
		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal-	5 mg/m3	ACGIH
		able particu-		
		late matter)		
		TWA (Mist)	5 mg/m3	OSHA P0
		TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Lubricating oils (petroleum), C20-50, hydrotreated neutral oil-based; Baseoil — unspeci- fied; [A complex combination of hydrocarbons obtained by treating light vacuum gas oil, heavy vacuum gas oil and solvent deasphalted residual oil with hydrogen in the pres- ence of a catalyst in a two stage process with dewaxing being carried out between the two stages. It consists predom- inantly of hydrocarbons having	72623-87-1	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

carbon numbers predominantly in the range of C20 through C50 and produces a finished oil with a viscosity of approximately 32cSt at 40 oC. It contains a relatively large proportion of saturated hydrocarbons.]				
		TWA (Mist)	5 mg/m3	OSHA Z-1
		TWA (Inhal- able particu- late matter)	5 mg/m3	ACGIH
		TWA (Mist)	5 mg/m3	OSHA P0
		TWA (Mist)	5 mg/m3	NIOSH REL
		ST (Mist)	10 mg/m3	NIOSH REL
Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C20-40, branched and cyclic	178603-65-1	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C15-30, branched and cyclic	178603-64-0	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C25-55, branched and cyclic	178603-66-2	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV
Lubricating oils (petroleum), C15-30, hydrotreated neutral oil-based, contg. solvent deasphalted residual oil	72623-84-8	TWA value (Inhalable fraction)	5 mg/m3	ACGIHTLV

Engineering measures : Ensure adequate ventilation.

Personal protective equipment

Respiratory protection : Wear a NIOSH approved (or equivalent) particulate respirator

if ventilation is inadequate to control dust.

Hand protection

Remarks : The suitability for a specific workplace should be discussed

with the producers of the protective gloves.

Eye protection : Eye wash bottle with pure water

Tightly fitting safety goggles

Skin and body protection : Choose body protection according to the amount and con-

centration of the dangerous substance at the work place.

Protective measures : Avoid inhalation of dusts.

Wearing of closed work clothing is required additionally to the

stated personal protection equipment.

Avoid exposure - obtain special instructions before use.

SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Handle in accordance with good building materials hygiene

and safety practice.

Hygiene measures : When using do not eat or drink.

When using do not smoke.

Wash hands before breaks and at the end of workday.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance : paste

Color : various colours

Odor : solvent

Odor Threshold : No data available

pH : not applicable

Melting point : No applicable information available.

Boiling point : No applicable information available.

Flash point : does not flash

Evaporation rate : No applicable information available.

Flammability (solid, gas) : not flammable

Method: Manual of tests and criteria. Test N.1 (United Nations Recommendations on the Transport of Dangerous Goods).

Self-ignition : not self-igniting

Upper explosion limit / Upper

flammability limit

6.7 %(V)

Lower explosion limit / Lower

flammability limit

1.0 %(V)

Vapor pressure : No applicable information available.

Relative vapor density : Heavier than air.

Relative density : No applicable information available.

Density : 0.98 g/cm3

Bulk density : 1,800 - 2,400 kg/m3

Solubility(ies)

SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Water solubility : slightly soluble

Solubility in other solvents : No applicable information available.

Partition coefficient: n-

octanol/water

: not applicable

Autoignition temperature : No data available.

Decomposition temperature : No decomposition if stored and handled as pre-

scribed/indicated.

Viscosity

Viscosity, dynamic : No applicable information available.

Viscosity, kinematic : 454400 mm2/s (104 °F / 40 °C)

Explosive properties : Not explosive

Not explosive

Oxidizing properties : Based on its structural properties the product is not classified

as oxidizing.

Self-heating substances : No data available

Sublimation point : No applicable information available.

Molecular weight : No data available

SECTION 10. STABILITY AND REACTIVITY

Reactivity : No decomposition if stored and applied as directed.

Chemical stability : No decomposition if stored and applied as directed.

Possibility of hazardous reac-

tions

No decomposition if stored and applied as directed.

Conditions to avoid : See SDS section 7 - Handling and storage.

Incompatible materials : Strong acids

Strong bases

Strong oxidizing agents Strong reducing agents

Hazardous decomposition

products

: No hazardous decomposition products if stored and handled

as prescribed/indicated.

SikaBond-620 slate Formerly MWeld 620 SLATE



Version 1.0

Revision Date: 09/17/2020

SDS Number: 000000261033

Date of last issue: -

Date of first issue: 09/17/2020

SECTION 11. TOXICOLOGICAL INFORMATION

Acute toxicity

Not classified based on available information.

Product:

Acute oral toxicity : Remarks: No applicable information available.

Acute inhalation toxicity : Remarks: No applicable information available.

Acute dermal toxicity : Remarks: No applicable information available.

Skin corrosion/irritation

Causes skin irritation.

Product:

Remarks : May cause skin irritation in susceptible persons.

Serious eye damage/eye irritation

Causes eye irritation.

Product:

Remarks : Product dust may be irritating to eyes, skin and respiratory

system.

Respiratory or skin sensitization

Skin sensitization

Not classified based on available information.

Respiratory sensitization

Not classified based on available information.

Germ cell mutagenicity

Not classified based on available information.

Carcinogenicity

May cause cancer.

Reproductive toxicity

Not classified based on available information.

STOT-single exposure

May cause respiratory irritation.

STOT-repeated exposure

Not classified based on available information.

Aspiration toxicity

Not classified based on available information.

Product:

No aspiration hazard expected.

SikaBond-620 slate Formerly MWeld 620 SLATE



Version **Revision Date:** SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Further information

Product:

Remarks No data available

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

No data available

Persistence and degradability

No data available

Bioaccumulative potential

Components:

xylene:

Partition coefficient: nlog Pow: 3.12 - 3.20 (77 °F / 25 °C)

octanol/water Method: other (calculated)

GLP: no

Remarks: Information taken from reference works and the

literature.

ethylbenzene:

Partition coefficient: n-Pow: 4,170 (68 °F / 20 °C) octanol/water

log Pow: 3.6 (68 °F / 20 °C)

pH: 7.8

Method: Partition coefficient

GLP: yes

Silicon dioxide:

Partition coefficient: n-

octanol/water

Remarks: not applicable

Titanium dioxide:

Partition coefficient: n-

octanol/water

Remarks: not applicable

White mineral oil (petroleum):

Partition coefficient: n-

octanol/water

Remarks: not applicable for mixtures

Lubricating oils (petroleum), C20-50, hydrotreated neutral oil-based; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating light vacuum gas oil, heavy vacuum gas oil and solvent deasphalted residual oil with hydrogen in the presence of a catalyst in a two stage process with dewaxing being carried out between the two stages. It consists predominantly of hydrocarbons having carbon numbers predominantly in the range of C20 through C50 and

SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

produces a finished oil with a viscosity of approximately 32cSt at 40 oC. It contains a relatively large proportion of saturated hydrocarbons.]:

Partition coefficient: n- : log Pow: 7.868

octanol/water Method: other (calculated)

Distillates (petroleum), hydrotreated light paraffinic; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C15 through C30 and produces a finished oil with a viscosity of less than 100 SUS at 100 oF (19cSt at 40 oC). It contains a relatively large proportion of saturated hydrocarbons.]:

Partition coefficient: n- : Pow: > 3.5

octanol/water

Distillates (petroleum), hydrotreated heavy paraffinic; Baseoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C20 through C50 and produces a finished oil of at least 100 SUS at 100oF (19cSt at 40 oC). It contains a relatively large proportion of saturated hydrocarbons.]:

Partition coefficient: n- : log Pow: approx. 7 - 25 octanol/water : Method: other (calculated)

Distillates (petroleum), hydrotreated light:

Partition coefficient: n- : log Pow: > 3.0

octanol/water Method: other (calculated)

Distillates (petroleum), hydrotreated middle; Gasoil — unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C11 through C25 and boiling in the range of approximately; 205oC to 400oC (401 oF to 752 oF).]:

Partition coefficient: n- : Remarks: No data available.

octanol/water

Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C20-40, branched and cyclic:

Partition coefficient: n- : Remarks: No data available.

octanol/water

Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C15-30, branched and cyclic:

Partition coefficient: n- : Remarks: No data available.

octanol/water

Gas oils (petroleum), vacuum, hydrocracked, hydroisomerized, hydrogenated, C25-55, branched and cyclic:

Partition coefficient: n- : Remarks: No data available.

octanol/water

SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

Lubricating oils (petroleum), C15-30, hydrotreated neutral oil-based, contg. solvent deasphalted residual oil:

Partition coefficient: n-

octanol/water

Remarks: No data available.

bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate:

Partition coefficient: n- : log Pow: 0.35 (77 °F / 25 °C)

octanol/water pH: 7

Method: Partition coefficient (n-octanol/water), Shake-flask

method

Mobility in soil
No data available

Other adverse effects

Product:

Additional ecological infor-

mation

An environmental hazard cannot be excluded in the event of

unprofessional handling or disposal.

Toxic to aquatic life.

Harmful to aquatic life with long lasting effects.

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Do not contaminate ponds, waterways or ditches with chemi-

cal or used container.

Dispose of in accordance with national, state and local regula-

tions.

Do not discharge into drains/surface waters/groundwater.

Contaminated packaging : Contaminated packaging should be emptied as far as possible

and disposed of in the same manner as the sub-

stance/product.

SECTION 14. TRANSPORT INFORMATION

International Regulations

UNRTDG

Not regulated as a dangerous good

IATA-DGR

Not regulated as a dangerous good

IMDG-Code

Not regulated as a dangerous good

Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code

Not applicable for product as supplied.

SikaBond-620 slate Formerly MWeld 620 SLATE



Version 1.0

Revision Date: 09/17/2020

SDS Number: 000000261033 Date of last issue: -

Date of first issue: 09/17/2020

Domestic regulation

49 CFR

Not regulated as a dangerous good

SECTION 15. REGULATORY INFORMATION

SARA 313 The following components are subject to reporting levels es-

tablished by SARA Title III, Section 313:

xylene 1330-20-7

The following components are subject to reporting levels es-

tablished by SARA Title III, Section 313:

ethylbenzene 100-41-4

US State Regulations

Pennsylvania Right To Know

ethylbenzene	100-41-4
Limestone	1317-65-3
xylene	1330-20-7
Silicon dioxide	7631-86-9
White mineral oil (petroleum)	8042-47-5
Titanium dioxide	13463-67-7
Distillates (petroleum), hydrotreated middle; Gasoil — unspec-	64742-46-7

ified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C11 through C25 and boiling in the range of approximately; 205oC to 400oC (401 oF to 752 oF).1

Distillates (petroleum), hydrotreated light 64742-47-8 Distillates (petroleum), hydrotreated light naphthenic; Baseoil 64742-53-6

- unspecified: [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C15 through C30 and produces a finished oil with a viscosity of less than 100 SUS at 100 oF (19cSt at 40 oC). It contains relatively few normal paraffins.]

Distillates (petroleum), hydrotreated heavy paraffinic; Baseoil 64742-54-7

- unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C20 through C50 and produces a finished oil of at least 100 SUS at 100oF (19cSt at 40 oC). It contains a relatively large proportion of

saturated hydrocarbons.]

Distillates (petroleum), hydrotreated light paraffinic; Baseoil — 64742-55-8 unspecified; [A complex combination of hydrocarbons ob-

tained by treating a petroleum fraction with hydrogen in the





Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C15 through C30 and produces a finished oil with a viscosity of less than 100 SUS at 100 oF (19cSt at 40 oC). It contains a relatively large proportion of saturated hydrocarbons.]

carbon black 1333-86-4

New Jersey Right To Know

ethylbenzene 100-41-4 Limestone 1317-65-3 xylene 1330-20-7 Titanium dioxide 13463-67-7 Distillates (petroleum), hydrotreated light 64742-47-8 Distillates (petroleum), hydrotreated heavy paraffinic; Baseoil 64742-54-7 - unspecified; [A complex combination of hydrocarbons obtained by treating a petroleum fraction with hydrogen in the presence of a catalyst. It consists of hydrocarbons having carbon numbers predominantly in the range of C20 through C50 and produces a finished oil of at least 100 SUS at 100oF (19cSt at 40 oC). It contains a relatively large proportion of saturated hydrocarbons.]

California Prop. 65

WARNING: This product can expose you to chemicals including ethylbenzene, which is/are known to the State of California to cause cancer, and ethyleneglycol, which is/are known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

The ingredients of this product are reported in the following inventories:

TSCA : On the inventory, or in compliance with the inventory

SECTION 16. OTHER INFORMATION

Further information


SikaBond-620 slate Formerly MWeld 620 SLATE



Version Revision Date: SDS Number: Date of last issue: -


1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

NFPA 704:



Special hazard

HMIS® IV:



HMIS® ratings are based on a 0-4 rating scale, with 0 representing minimal hazards or risks, and 4 representing significant hazards or risks. The "*" represents a chronic hazard, while the "/" represents the absence of a chronic hazard.

Full text of other abbreviations

29 CFR 1910.1000 (Table Z- : OSHA - Table Z-1-A (29 CFR 1910.1000)

1-A)

29 CFR 1910.1000 (Table Z- : OSHA - Table Z-1 (Limits for Air Contaminants) 29 CFR

1910.1000

29 CFR 1910.1000 (Table Z- : OSHA Table Z-3 (Mineral Dusts) 29 CFR 1910.1000

3)

ACGIH : USA. ACGIH Threshold Limit Values (TLV)

ACGIHTLV : American Conference of Governmental Industrial Hygienists -

threshold limit values (US)

NIOSH : NIOSH Pocket Guide to Chemical Hazards (US)
NIOSH REL : USA. NIOSH Recommended Exposure Limits

OSHA PO : USA. OSHA - TABLE Z-1 Limits for Air Contaminants -

1910.1000

OSHA Z-1 : USA. Occupational Exposure Limits (OSHA) - Table Z-1 Lim-

its for Air Contaminants

OSHA Z-3 : USA. Occupational Exposure Limits (OSHA) - Table Z-3 Min-

eral Dusts

29 CFR 1910.1000 (Table Z- : Short Term Exposure Limit (STEL):

1-A) / STEL value

29 CFR 1910.1000 (Table Z- : Time Weighted Average (TWA):

1-A) / TWA value

29 CFR 1910.1000 (Table Z- : Permissible exposure limit

1) / PEL

29 CFR 1910.1000 (Table Z- : Time Weighted Average (TWA):

3) / TWA value

ACGIH / TWA : 8-hour, time-weighted average ACGIH / STEL : Short-term exposure limit

ACGIHTLV / Skin Designation: Skin Designation:

tion

ACGIHTLV / STEL value : Short Term Exposure Limit (STEL):
ACGIHTLV / TWA value : Time Weighted Average (TWA):
NIOSH / REL value : Recommended exposure limit (REL):



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

NIOSH / STEL value : Short Term Exposure Limit (STEL):

NIOSH REL / TWA : Time-weighted average concentration for up to a 10-hour

workday during a 40-hour workweek

NIOSH REL / ST : STEL - 15-minute TWA exposure that should not be exceeded

at any time during a workday

OSHA P0 / TWA : 8-hour time weighted average OSHA P0 / STEL : Short-term exposure limit : 8-hour time weighted average OSHA Z-3 / TWA : 8-hour time weighted average

AICS - Australian Inventory of Chemical Substances; ASTM - American Society for the Testing of Materials; bw - Body weight; CERCLA - Comprehensive Environmental Response, Compensation, and Liability Act; CMR - Carcinogen, Mutagen or Reproductive Toxicant; DIN - Standard of the German Institute for Standardisation; DOT - Department of Transportation; DSL - Domestic Substances List (Canada); ECx - Concentration associated with x% response; EHS - Extremely Hazardous Substance: ELx - Loading rate associated with x% response; EmS - Emergency Schedule; ENCS - Existing and New Chemical Substances (Japan); ErCx - Concentration associated with x% growth rate response; ERG - Emergency Response Guide; GHS - Globally Harmonized System; GLP - Good Laboratory Practice; HMIS - Hazardous Materials Identification System; IARC - International Agency for Research on Cancer; IATA - International Air Transport Association; IBC - International Code for the Construction and Equipment of Ships carrying Dangerous Chemicals in Bulk; IC50 - Half maximal inhibitory concentration; ICAO - International Civil Aviation Organization; IECSC - Inventory of Existing Chemical Substances in China; IMDG - International Maritime Dangerous Goods; IMO - International Maritime Organization; ISHL - Industrial Safety and Health Law (Japan); ISO - International Organisation for Standardization; KECI -Korea Existing Chemicals Inventory; LC50 - Lethal Concentration to 50 % of a test population; LD50 - Lethal Dose to 50% of a test population (Median Lethal Dose); MARPOL - International Convention for the Prevention of Pollution from Ships; MSHA - Mine Safety and Health Administration; n.o.s. - Not Otherwise Specified; NFPA - National Fire Protection Association; NO(A)EC - No Observed (Adverse) Effect Concentration; NO(A)EL - No Observed (Adverse) Effect Level; NOELR - No Observable Effect Loading Rate; NTP - National Toxicology Program; NZIoC - New Zealand Inventory of Chemicals; OECD - Organization for Economic Co-operation and Development; OPPTS - Office of Chemical Safety and Pollution Prevention; PBT - Persistent, Bioaccumulative and Toxic substance; PICCS - Philippines Inventory of Chemicals and Chemical Substances; (Q)SAR - (Quantitative) Structure Activity Relationship; RCRA - Resource Conservation and Recovery Act; REACH - Regulation (EC) No 1907/2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals; RQ -Reportable Quantity; SADT - Self-Accelerating Decomposition Temperature; SARA - Superfund Amendments and Reauthorization Act; SDS - Safety Data Sheet; TCSI - Taiwan Chemical Substance Inventory; TSCA - Toxic Substances Control Act (United States); UN - United Nations; UNRTDG - United Nations Recommendations on the Transport of Dangerous Goods; vPvB -Very Persistent and Very Bioaccumulative

Revision Date : 09/17/2020

We support worldwide Responsible Care® initiatives. We value the health and safety of our employees, customers, suppliers and neighbors, and the protection of the environment. Our commitment to Responsible Care is integral to conducting our business and operating our facilities in a safe and environmentally responsible fashion, supporting our customers and suppliers in ensuring the safe and environmentally sound handling of our products, and minimizing the impact of



SikaBond-620 slate Formerly MWeld 620 SLATE

Version Revision Date: SDS Number: Date of last issue: -

1.0 09/17/2020 000000261033 Date of first issue: 09/17/2020

our operations on society and the environment during production, storage, transport, use and disposal of our products.

IMPORTANT: WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE , IT IS PROVIDED FOR YOUR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, WE RECOMMEND THAT YOU MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR YOUR PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. FURTHER, YOU EXPRESSLY UNDERSTAND AND AGREE THAT THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY OUR COMPANY HEREUNDER ARE GIVEN GRATIS AND WE ASSUME NO OBLIGATION OR LIABILITY FOR THE DESCRIPTION, DESIGNS, DATA AND INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT YOUR RISK.

US / EN