



## PRODUCT DATA SHEET

# Sikalastic® P 280 FS

(formerly MSeal P 280FS)

SIKALASTIC® P 280 FS IS AN MMA SOLVENT-FREE, TWO-COMPONENT, 100% REACTIVE, LOW-VIS-COSITY PRIMER.

### PRODUCT DESCRIPTION

Sikalastic® P 280 FS is an MMA solvent-free, two-component, 100% reactive, low-viscosity primer.

### USES

- Stadiums
- Parking Garages
- Plaza Decks
- Loading Docks
- Garbage Rooms
- Commercial Construction
- Building and Restoration

### PRODUCT INFORMATION

<b>Packaging</b>	4.5-Gal (17L) pail; 49-Gal (185.5L) drum
<b>Shelf Life</b>	2 years
<b>Storage Conditions</b>	Store in unopened containers in a cool, dry and clean area.
<b>Solid content by mass</b>	100% (ASTM D 1259)

### CHARACTERISTICS / ADVANTAGES

- Rapid cure allows for quick installation with minimal facility downtime
- Low-temperature cure extends application season

### APPROVALS / STANDARDS

- CSA S413
- ASTM C957

## TECHNICAL INFORMATION

<b>Tensile Strength</b>	3500 psi (24.13 MPa)	(ASTM D 412)																														
<b>Electrical Resistivity</b>	Volume: $2.5 \times 10^{15}$ , Surface: $8 \times 10^{12}$ , ohm/cm	(ASTM D 257)																														
<b>Water Absorption</b>	<0.1% over 24 hours	(ASTM D 570)																														
<b>Mixing Ratio</b>	<p>Mixing Chart shows amount of Sikalastic® 918 FS (in volume ounces) added to one (1) gallon of Sikalastic® P 280 FS mixed 3:1 with Sikalastic®-908 FS. Sikalastic® 918 FS is the catalyst for Sikalastic® P 280 FS at all temperatures.</p> <table border="1"> <thead> <tr> <th>°F (°C)</th> <th>Sikalastic® 918 FS (fl. oz.)</th> </tr> </thead> <tbody> <tr><td>°30 (°-1)</td><td>9</td></tr> <tr><td>°33 (°1)</td><td>8</td></tr> <tr><td>°35 (°2)</td><td>7</td></tr> <tr><td>°40 (°4)</td><td>6.5</td></tr> <tr><td>°45 (°7)</td><td>6</td></tr> <tr><td>°50 (°10)</td><td>6</td></tr> <tr><td>°55 (°13)</td><td>5</td></tr> <tr><td>°60 (°16)</td><td>5</td></tr> <tr><td>°65 (°18)</td><td>5</td></tr> <tr><td>°70 (°21)</td><td>4</td></tr> <tr><td>°76 (°24)</td><td>4</td></tr> <tr><td>°80 (°27)</td><td>4</td></tr> <tr><td>°85 (°29)</td><td>4</td></tr> <tr><td>°90 (°32)</td><td>4</td></tr> </tbody> </table>		°F (°C)	Sikalastic® 918 FS (fl. oz.)	°30 (°-1)	9	°33 (°1)	8	°35 (°2)	7	°40 (°4)	6.5	°45 (°7)	6	°50 (°10)	6	°55 (°13)	5	°60 (°16)	5	°65 (°18)	5	°70 (°21)	4	°76 (°24)	4	°80 (°27)	4	°85 (°29)	4	°90 (°32)	4
°F (°C)	Sikalastic® 918 FS (fl. oz.)																															
°30 (°-1)	9																															
°33 (°1)	8																															
°35 (°2)	7																															
°40 (°4)	6.5																															
°45 (°7)	6																															
°50 (°10)	6																															
°55 (°13)	5																															
°60 (°16)	5																															
°65 (°18)	5																															
°70 (°21)	4																															
°76 (°24)	4																															
°80 (°27)	4																															
°85 (°29)	4																															
°90 (°32)	4																															

## SYSTEM INFORMATION

<b>Systems</b>	Sikalastic® Vehicular Traffic 2900
<b>System Structure</b>	Sikalastic® P 280 FS is mixed 3:1 with Sikalastic® - 908 FS prior to catalyzing with Sikalastic® - 918 FS

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## LIMITATIONS

- Sikalastic® P 280 FS is used exclusively with the Sikalastic® 2900 System.
- If a vapor drive is present or suspected, please consult with your local Sika representative prior to system application.
- Not for use in areas exposed to strong solvents (consult Sika Technical Service).
- Protect or remove food items prior to application to avoid any possible contamination.
- Proper airflow is critical to curing MMA materials. The use of fans is mandatory where airflow is restricted.
- The minimum application temperature is 30 °F (-1 °C).
- Do not apply to concrete that is outgassing.
- Warm temperatures will shorten working time; plan

work accordingly.

- Concrete should have a minimum compressive strength of 3,000 psi (21 MPa) and be cured for a minimum of 28 days.
- Do not apply Sikalastic® Vehicular Traffic 2900 to plywood, concrete slabs on grade, unvented metal pan decks, or split slab applications with a waterproofing membrane between slabs. Contact Sika Technical Services.
- Be sure to allow for movement in the deck by the proper design and use of expansion and control joints.
- Select the proper type and amount of aggregate to achieve the desired slip resistance.
- Contact Technical Service when substrates are over 90 °F (32 °C) or under 30 °F (-1 °C) or when applying to decks containing between slab membranes.
- The best method to ensure the proper wet film thickness is the use of a grid system. Divide the surface to be coated into grids and calculate the square footage of each. Refer to the coverage chart to determine the quantity of coating needed for each grid to arrive at the required mil thicknesses.
- Avoid application when inclement weather is present or imminent.

- Do not apply to damp, wet, or contaminated surfaces.
- Not suitable for use where chained or metal-studded tires will be used.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.
- CAD & PDF deck coating details are available for download from our website, Sika Customer Support can direct you to the site.
- On steep ramps in excess of 15%, contact your local Sika representative. Do not use self-leveling grade products on slopes greater than 15%. Do not coat over expansion joints.

- Use mixture to repair any damaged concrete, or to slope any areas as needed.
- Once cured, the material must be re-primed before the topping system is applied.
- Proceed with the application as usual.
- All units must be within the specified pot life.

#### Aggregate Extension

Overlay Thickness	% by Weight	Grain Size	Weight in Pounds	Per Batch of SikaEmaco®-6000
¼"	–	–	–	12.5
½"	10%	1/16 – 1/8"	4	7.2
¾"	25%	1/16 – 1/8"	8	5.3
1"	50%	3/16 – 3/8"	15	4.4
1-½"	75%	3/16 – 3/8"	25	3.5
2"	100%	¼ – ¾"	35	2.3
≥ 3"	125%	¼ – ¾"	44	2.2

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

#### Concrete

Concrete must be fully cured (28 days), structurally sound, clean, and dry (ASTM D 4263). All concrete surfaces (new and old) must be shot blasted to remove previous coatings, laitance, and all miscellaneous surface contamination and to provide a profile for proper adhesion. Abrasive shot blasting must occur after a concrete repair has taken place. Acid-etching is not permitted. The proper profile should be a minimum of ICRI CSP3 (as described in ICRI document 310.2R - 2013.) For balconies and other pedestrian areas with limited space or access to shot-blasting, alternative mechanical methods can be used to achieve the recommended surface profile.

- Repair voids and delaminated areas with SikaEmaco®-6000. When time permits, SikaEmaco®-1060 or SikaEmaco®-1060 EX may be used for repair purposes. Wait 6-8 hours before applying the Sikalastic® Vehicular Traffic 2900 system.
- Prime with Sikalastic® P 280 FS before applying SikaEmaco®-6000. Measure 3 quarts of resin and 1 quart of Sikalastic®-908 FS into the pail and add the proper amount of powder hardener. See the mixing chart below. Mix with a drill mixer for 30 seconds or until the powder hardener is completely dissolved.
- Apply primer at approximately 100 ft<sup>2</sup> (9.3 m<sup>2</sup>) per mixed gallon.
- Measure, add, and mix the SikaEmaco®-6000 Resin, Powder Component, and necessary aggregate (if required) in the proportions recommended below.

Volume	Cubic Feet
-	0.26
1 – ¼ quarts, 2 – ½ quarts	0.30
2 – ½ quarts	0.33
5 quarts	0.37
2 gallons	0.44
2.5 gallons	0.50
3 gallons	0.55

### SURFACE PREPARATION

#### Surface Pre-stripping And Detailing

1. For non-moving joints and cracks less than 1/16" (1.6 mm) wide, pre-stripe with Sikalastic® P 280 FS 1" (25 mm) beyond all surfaces that require detail work, using a short-nap roller. Just before the application of Sikalastic® P 280 FS, remove all dust, dirt, and contaminants. Allow Sikalastic® P 280 FS to dry tack-free. On the same day, coat primed surfaces with 25 mils of Sikalastic® M 290 FS. Sikalastic® M 290 FS must be applied to fill and overlap the joint or crack 2" (51 mm) on each side. Feather the edges.
2. NOTE: For non-moving joints and cracks, prime the crack before applying Sikalastic® M 290 FS at 25 mils using a notched trowel - for faster detailing.
3. Dynamic cracks and joints over 1/16" (1.6 mm) wide must be routed to a minimum of 1/4 by 1/4" (6 by 6 mm) and cleaned. Install bond breaker tape to prevent adhesion to the bottom of the joint. Prime joint faces only with Sika® Primer-173 and fill with Sikaflex® SL 2 or Sikaflex® NP 2. For joints deeper than ¼" (6 mm), use an appropriate backer rod. For cracks, sealant should be flush with the adjacent surface. For expansion joints, the sealant should be slightly concave.
4. Sealed joints 1" (25 mm) wide or less can be coated over with the Sikalastic® Traffic system. **NOTE: SYSTEM IS NOT TO BE APPLIED ON PLYWOOD**

5. Expansion joints exceeding 1" (25 mm) wide, including the primary wide expansion-joint system, are not to be coated so they can perform independently of the deck coating system.
6. Form a sealant cant into the corner at the junction of all horizontal and vertical surfaces (wall sections, curbs, columns) by priming with Sika® Primer-173 and applying a 1" (25 mm) wide bead of Sikaflex® NP 2. Tool to form a 45° cant. Apply masking tape to the vertical surfaces 4–5" (102–127 mm) above the sealant cant to provide a clean termination of the vertical detail coat. After the sealant has cured, prime with Sikalastic® P 280 FS at 100 SF/gallon. Apply 25 wet mils (0.64 mm) of Sikalastic® M 290 FS over the cured cant up to the masking tape and 4" (102 mm) onto the deck surface. **NOTE:** For a non-moving cant bead, Sikafloor®-100 PAS Pronto can be used for rapid cure.
7. Where the coating system will be terminated and no wall, joint, or other appropriate break exists, cut a 1/8 by 1/8" (3 by 3 mm) keyway into the concrete. Fill and coat the keyway during the application of Sikalastic® M 290 FS.

## MIXING

Measure 3 quarts of Sikalastic® P 280 FS resin and 1 quart of Sikalastic®-908 FS into the pail, blend, and add the proper amount of powder hardener. See the mixing chart below. Mix with a drill mixer for 30 seconds or until the powder hardener is completely dissolved. See Mixing Ratio chart for the required amount of Sikalastic®-918 FS (in volume ounces) for one-gallon mixed resin, based on temperature.

## APPLICATION

Apply the properly mixed Sikalastic® P 280 FS/Sikalastic®-908 FS resin catalized with the Sikalastic® 918 FS to the properly repaired concrete or properly prepared aged coating at approximately 100 ft<sup>2</sup> (9.3 m<sup>2</sup>) per mixed gallon or about 16 mils. Allow the primer to cure tack-free to an even, satin-like gloss and re-prime any dry spots.

## CURING TREATMENT

All components of the Sikalastic® Traffic 2900 system fully cure within one hour when properly installed. Extend the curing time in cool-weather conditions.

## CLEANING OF TOOLS

Clean tools with Sikafloor®-100 CLN Pronto, an MMA

solvent. Other solvents such as xylene or acetone may also be used. Collect and dispose of all site waste.

## MAINTENANCE

See Sikalastic® Traffic maintenance technical bulletin. Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance, and reduce any tendency to retain dirt.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and

Conditions of Sale which are available at  
<https://usa.sika.com/en/group/SikaCorp/termsandconditions.html>  
or by calling 1-800-933-7452.

**Sika Corporation**

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)



**Product Data Sheet**  
Sikalastic® P 280 FS  
December 2024, Version 02.01  
02081300000002025

SikalasticP280FS-en-US-(12-2024)-2-1.pdf

