

PRODUCT DATA SHEET

Sika Boom[®]-180

POLYURETHANE SPRAY FOAM FOR GAPS AND CRACKS UP TO 1"

PRODUCT DESCRIPTION

Sika Boom[®]-180 is a polyurethane, 1-part, self-expanding, foam for easy filling, sealing, and insulating of gaps and cracks up to 1".

USES

Polyurethane expanding foam for:

- Insulating and filling gaps and cracks
- Filling joints around window and door frames
- Insulating against noise, cold and drafts
- Filling around pipes or conduit penetrations

CHARACTERISTICS / ADVANTAGES

- Easy application with nozzle
- Effective sound dampening
- Good thermal insulation
- Forms a permanent weather-tight seal
- Resistant to mold
- Waterproof
- Excellent adhesion to many construction materials (wood, metal, masonry, glass, most plastics)
- 1-part ready to use
- Paintable and sandable
- Tack free as fast as 7 minutes
- Can be cut/trimmed as soon 30 minutes
- Indoor & outdoor use

PRODUCT INFORMATION

Chemical Base	Polyurethane foam		
Packaging	12 cans per box	12 oz (354ml)	
Shelf Life	15 months from date of production		
Storage Conditions	Store properly in the original, unopened, undamaged, sealed packaging. Store in an upright position, in dry conditions, out of direct sunlight and at temperatures between 41 °F and 77 °F.		
Color	Light yellow		
Density	Cured product	~42 kg/m ³	(ASTM D1622)

TECHNICAL INFORMATION

Compressive Strength	4.35 psi (30 kPa) - parallel to rise	(ASTM D1621)
Tensile Adhesion Strength	11.7 ± 0.8	(ASTM D1623)
Dimensional Stability	±10%	(ASTM D2126)
Expansion	~145 %	(ASTM C1663)
Service Temperature	Minimum	-40 °F
	Maximum	176 °F
Thermal Resistance	R-value 4.0 per inch	
Water Absorption	max. 1 vol%	(ASTM D2842)
UV Exposure	Not permanently UV stable (for best results, the cured foam may be painted or coated for outdoor applications)	

APPLICATION INFORMATION

Coverage	12 fl. oz. can yields 28.8 linear ft. of foam (1/4 in. x 1/4 in. bead)	
Product Temperature	Optimal	68 °F
	Minimum	41 °F
	Maximum	86 °F
Ambient Air Temperature	Optimal	68 °F
	Minimum	28 °F
	Maximum	86 °F
Cure Time	24 hours	(ASTM C1620)
Tack Free Time	7 to 10 minutes	(ASTM C1620)
Cutting Time	30-45 minutes	(ASTM C1620)

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- Not resistant to UV rays unless painted, covered, or coated.
- Will not bond to polyethylene (PE), polypropylene (PP), Teflon, and silicone, oil, grease, or release agents.
- Do not use product for mechanical or structural fixing purposes.
- When used for bonding vertical/ horizontal building components, they must be braced until the product has developed sufficient strength.
- Moisture is necessary for curing. Insufficient moisture may lead to subsequent unintended foam expansion (post-expansion).
- Use caution when attaching or removing the nozzle. If pressure is applied to the valve, foam splashes may occur.
- Should be kept at room temperature for at least 12 hours before the application.
- Storage above 77°F and below 41°F shortens shelf life.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, sound, firm, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sika Boom®-180 will adhere without primers or activators to most building materials such as wood, concrete, brick, metal or aluminum. For non-conventional substrates a preliminary adhesion test is recommended.

APPLICATION

1. Pre-dampen the substrate with clean water. This ensures that the foam cures properly and also prevents unwanted foam expansion.
2. Shake the can well for a minimum 20 times before use.
Note: Repeat shaking after long interruptions of use.
3. Remove the cap from the can.
4. Screw the nozzle firmly onto the thread of the valve without pressing the trigger or the valve.
5. **IMPORTANT:** To ensure proper flow, hold the can upside down while dispensing. Dispense the foam by pressing the trigger. **Note:** The amount of foam extruded can be regulated by applying more or less pressure on the trigger.
6. **IMPORTANT:** Allow each layer to expand and harden sufficiently before pre-dampening with water again for next layer application. Fill deep joints in several layers.
Note: Fill voids / cavities only partially as the foam expands during curing. **Note:** Small gaps can be filled using an extension tube, this will however reduce the foam flow rate.
Re-Usable Straw: To ensure that the straw can be re-used: 1) set the can upright and 2) while it is still full of foam, fold back the straw over itself and slide open end onto the plastic tip located above the trigger to a depth of a 1/4 in. This will keep the straw air-free. When you are ready to re-use the product, simply shake the can, unfold the straw, and proceed with spraying.

CLEANING OF TOOLS

Uncured foam can be immediately removed from tools and finished surfaces using an approved solvent (e.g. Acetone, MEK, or Xylene). Cured material can only be removed mechanically. For spillage, collect, absorb, and dispose of in accordance with current, applicable local, state, and federal regulations.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sika Boom®-180
July 2024, Version 04.01
02051406000000306

SikaBoom-180-en-US-(07-2024)-4-1.pdf

