



PRODUCT DATA SHEET

SCOFIELD® Formula One™ SG

A concentrated sodium silicate densifier for improving concrete surface hardness, resistance to dirt pick-up, and ease of polishing.

PRODUCT DESCRIPTION

SCOFIELD® Formula One™ SG is a concentrated VOC free concrete densifier formulated to economically harden, densify, and increase the abrasion resistance of cementitious surfaces. Based on concentrated sodium silicate, it is diluted with water so it can deeply penetrate into concrete pores. It then reacts with cement, pozzolans, and most aggregates to fill microvoids and allow concrete to polish faster while allowing these surfaces to release moisture vapor. It is not a coating, and will not crack, peel, or delaminate from surfaces.

USES

SCOFIELD® Formula One™ SG may only be used by experienced professionals.

Use as an effective concrete polishing aid, or to harden, densify, or dustproof the cementitious surfaces of:

- Interior or exterior floors
- Stairs and walkways
- Ground and polished floors
- Below grade basements

CHARACTERISTICS / ADVANTAGES

- Low odor, non-yellowing water based formulation.
- Breathable non-film forming surface treatment.
- Bonds directly to cement and aggregate silicates.
- Hardens and improves stain and scratch resistance.
- Deeply penetrates, and quickly reacts.
- Shortens concrete polishing times.
- UV light stable and weather resistant.
- Cures to a non-toxic, non-flammable surface.
- Apply by brush, roller, spray or mop.
- Accepts most water repellent surface treatments.

APPROVALS / STANDARDS

SCOFIELD® Formula One™ SG can be used as part of a low VOC concrete polishing system to earn LEED® credits for Indoor Environmental Quality, EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings.

SCOFIELD® Formula One™ SG can be used with Scofield® Formula One™ Guard-W to make floors that exceed the Underwriters Laboratories Safety Standard UL 410, "Slip Resistance of Floor Surface Materials."

PRODUCT INFORMATION

| | |
|---------------------------|--|
| Chemical Base | Sodium Silicate, 24% solids |
| Packaging | 5-gallon (18.9 L) pails and 55-gallon (208 L) drums. |
| Appearance / Color | Clear to slightly cloudy liquid. |

Shelf Life

1 year from the date of manufacture. 1 month after opening.

Storage Conditions

Store in original containers at 40°F to 120°F (4°C - 49°C). DO NOT FREEZE!

APPLICATION INSTRUCTIONS

If using spray equipment, always wear protective respirator. Mask adjacent areas to protect property from splashes and overspray. Dried material will be difficult to remove. Remove overspray immediately with soap and water.

SCOFIELD® Formula One™ SG should always be diluted a minimum of 1:1 by volume with water, and dilutions of 1 part concentrate into 3 parts of water is adequate for most jobs. Dilution rate, surface age, hardness, porosity, substrate moisture content, and purpose will determine the optimum combination of dilution and coverage rate. First time applicators are encouraged to use the product diluted 1:3 with water.

Although successful application can be performed with topical applications, the use of brooms, sponges, or mops to work material into substrate pores have proven to produce superior results. Applicators are encouraged to have consistent application rates and change dilution rates to achieve desired results.

For all uses and applications, apply until surfaces are saturated. Spread or scrub puddles of excess material into surfaces before it is allowed to dry. **Remove and rinse away any obvious excess surface material while it is still wet. Material allowed to dry on surfaces will likely form unsightly salts that are difficult to remove.**

SCOFIELD® Formula One™ SG can be applied to freshly placed concrete as soon as broom or other surface patterns will not be disturbed by the application. Achieving uniform penetration on this young a surface is difficult, and concrete is suggested to be at least 7 days old so that initial concrete cure is complete and product absorption is consistent across surfaces. A 28 day cure so that the slab is fully dry and has consistent absorbance is preferred.

Coverage

Coverage will depend upon dilution rate, method of application, surface porosity, age, moisture, absorption characteristics and the texture of the concrete. Coverage on flat finished concrete with a dilution rate of 1 gallon of concentrate mixed into 3 gallons of water is typically 200–400 ft²/gal (4.9–9.8 m²/L). Old or soft concrete will require more material or less dilution. Slabs ground to expose hard non absorptive aggregates will take less material.

Dilution Rates

Suggested dilution rates are given by volume.
Partially eroded, aged, or coarsely ground concrete to

be polished: 1 part concentrate into 1 part water.
Soft, aged, or lightly ground concrete to be polished: 1 part concentrate into 2 parts water.
Hard, steel troweled, new concrete: 1 part concentrate into 3 parts water.

EQUIPMENT

Apply SCOFIELD® Formula One™ SG by brush, roller, sponge, mop, or pump-spray application. Use rotary floor scrubbers equipped with brushes or pads to assist with large jobs. Always wear protective clothing and equipment proper for the method of application. Use of a wet vacuum equipped with a squeegee-type attachment to remove excess material and rinse water is recommended. All equipment should be washed with soap and water after use.

Spray applicator Guidelines:

Pump Garden Sprayer: Use conical tip and apply with circular motion.

SUBSTRATE PREPARATION

Surfaces must be clean of all prior sealers, curing compounds, oils, or other foreign materials that might prevent penetration. If used as a first stage densifier when polishing concrete, grind to the desired aggregate exposure ending with 80 to 200 grit tools. Use brooms or vacuums to remove all grinding dusts, loose concrete laitance, and powders, or the densifier may permanently adhere them to the surface.

Mixing: Dilution should be performed in non-metallic plastic containers. Mix until uniform prior to beginning the application.

Jobsite Test Sections

Verify and approve suitability and appearance by making jobsite test sections prior to general application. Each individual concrete color, finishing technique, densifier, and sealer combination should be verified. Test sections must be of adequate size to be representative and be produced by the same workers who will apply product to the larger job. Test completed systems for wet and dry slip resistance to ensure they are safe. Do not proceed with products, techniques, or finishing systems that do not meet required safety specifications or site owner approval.

Application

Mask all areas not to be coated to safeguard against splashes, overspray, and runoff from application. Wear all required safety equipment. Take care not to allow tape adhesive to interfere with surfaces to be treated. Surfaces wet with material will be slippery until dry.

Product Data Sheet

SCOFIELD® Formula One™ SG
October 2018, Version 01.02
020815010110000026

Distribute product with a pump garden sprayer to fully saturate the surface. Surfaces should remain wet 5 to 10 minutes. Work material into the surface with a broom, mop, or sponge to ensure product penetrates into substrate pores and microcracks. Take care not to create lap marks as they cannot be removed once the product has dried. If too much material has been applied, and it is puddled or visible after 30 minutes, rinse with water and remove this with a wet vacuum before frosts can form.

When the first application is dry to touch, a second coat can be applied to maximize densification properties. If used as a polishing aid, wet polishing can begin when dry to touch.

Dry times will depend upon the selected coverage rate, penetration into the substrate, and weather conditions. At 70°F (21°C) and 50 % relative humidity with an application rate of 400 sq. ft. per gallon (9.8 m²/L), surfaces should be dry and walkable and ready for the next stage of polishing or rinsing in 1 hour.

If surfaces will not be polished, or they will be sealed with a coating, wash surfaces at this stage with fresh water to remove excess densifier. When completely dry, surfaces can be returned to service or receive stain repellent surface treatments like SCOFIELD® Repello® FPS or SCOFIELD® Formula One™ Finish Coat. If sealing, wait 24 hours to allow the densifier to cure.

Cleaning of Equipment

Clean equipment with warm water and detergent immediately after application.

AVAILABILITY/WARRANTY

Availability

SCOFIELD® Formula One™ SG is marketed nationwide and internationally, directly to the user through strategically located warehouses, dealers, and representatives. Contact Scofield for its nearest representative.

Scofield offers a complete line of engineered systems for coloring, texturing, and improving performance in architectural concrete. Scofield Systems address specialized requirements for interior, exterior and vertical uses with compatible systems of complementary products including coloring admixtures, color hardeners, colored cementitious toppings, stains, curing compounds, sealers, coatings, repair products and texturing tools. Visit the Scofield website at www.scofield.com for further information.

LIMITATIONS

SCOFIELD® Formula One™ SG is not a membrane forming curing compound and does not conform to ASTM C 309 requirements. It is not designed to provide

water or oil resistance to the concrete surface without further treatment.

Do not use in combination with LITHOCHROME® Chemstain® Classic or white surfaces will likely result.

Concrete that has carbonated at the surface may not react properly with this product. If surface carbonation is present it should be removed mechanically. Acid etching is not advised.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

VOC = 0 g/l

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended

use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

SCOFIELD® Formula One™ SG
October 2018, Version 01.02
020815010110000026

SCOFIELDFormulaOneSG-en-US-(10-2018)-1-2.pdf

