

PRODUCT DATA SHEET

Sikafloor® Marine-579

Self-levelling decorative resin

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Sikafloor® Marine-579 (A)	Sikafloor® Marine-579 (B)
Chemical base	Polyurethane	Isocyanate
Color (CQP001-1)	Colored	Transparent
	mixed	Brown colors available (see color design chart)
Density	1.5 kg/l	1.2 kg/l
	mixed	1.4 kg/l
Solid content	100 %	
Mixing ratio	by weight 79 : 21	
Application temperature	substrate / climate 15 – 30 °C ^{A, B}	
Shore D hardness (CQP023-1 / ISO 48-4)	67	
Tensile strength (DIN 53504)	20 MPa	
Elongation at break (DIN 53504)	100 %	
Pot-life	10 °C	30 minutes
	20 °C	21 minutes
	30 °C	18 minutes
Shelf life	9 months ^C	12 months ^C

CQP = Corporate Quality Procedure ^{A)} Substrates must be 3 °C above the dew point^{B)} max. 80 % r.h.^{C)} stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight**DESCRIPTION**

Sikafloor® Marine-579 is a self-levelling 2-component polyurethane decorative floor resin. It is part of the Sikafloor® Marine Deco systems.

PRODUCT BENEFITS

- Good working characteristics
- Very low VOC emission
- Good mechanical resistance
- Solvent-free (ISO 16001-6)
- Longterm elastic

AREAS OF APPLICATION

Sikafloor® Marine-579 is designed as a component of the Sikafloor® Marine Deco systems. It is designed for mechanical resistant external flooring in ship and boat construction and as final compound in the Sikafloor® Marine Deco system for exterior use.

This product is suitable for experienced professional users only.

Tests with actual substrates and conditions have to be performed ensuring workability, adhesion and material compatibility.

CURE MECHANISM

The curing of Sikafloor® Marine-579 takes place by a chemical reaction of the two components. Higher temperatures speed up and lower temperatures slow down the curing process.

CHEMICAL RESISTANCE

For advice contact the Technical Department of Sika Industry.

METHOD OF APPLICATION

Surface Preparation

Sikafloor® Marine-579 is installed on top of the deck levelling compound.

Metallic decks need to be prepared to SA 2.5 (ISO 8501). Aluminum decks must not be shot blasted. The prepared metallic surfaces need to be clean, free of dirt, grease, oil and loose particles before the SikaCor® ZP Primer is applied.

The application area must be protected against weather and direct sunlight.

Mixing process

Prior to mixing, stir part A. Add part B and mix continuously for 2 minutes until a homogeneous mix has been obtained.

Pour material into another container and mix again for at least 1 minute.

Use double mixing paddles not higher than 300 rpm to minimize air entrapment.

For areas with cambers or slopes between 1 % and 3 % use Sikafloor® Marine Liquid PU Thickener. The dosage is between 1 % and 2 % in weight depending on the actual situation. For areas with higher cambers it may be required to add additional 1 % to 2 % of Sika® Extender T or Aerosil by weight to the mix. Alternatively, it is possible to reduce the layer thickness and apply multiple layers.

Note: By increasing the viscosity de-airing properties can be affected.

Application

Sikafloor® Marine-579 is poured and spread evenly by means of a notched trowel, flat trowel or pin-rake. In critical areas a spike roller can be used to improve levelling and de-airing. For deeper sections (e.g. unevenness), it might be necessary to pre-level these sections. Ensure the pre-leveled sections have achieved "foot traffic" cure level prior to proceeding.

For liquid application on cambers and slopes multiple applications steps may be needed. Curing speed depends on temperature and layer thickness. Always consider the pot life to keep a wet edge.

Curing

Indications regarding curing details see table below.

Temperature	Foot traffic	Light traffic ^A	Full cure
10 °C	24 hours	48 hours	72 hours
20 °C	18 hours	24 hours	60 hours
30 °C	16 hours	18 hours	48 hours

^{A)} food trolleys and light rolling equipment on soft wheels

Removal

Uncured Sikafloor® Marine-579 can be removed from tools and equipment with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

Application Limits

Freshly applied Sikafloor® Marine-579 must be protected from damp, condensation and water for at least 1 days. Uncured material reacts in contact with water (foaming).

STORAGE CONDITIONS

Both components of Sikafloor® Marine-579 have to be kept between 5 °C and 30 °C in a dry place. Do not expose it to direct sunlight. After opening of the packaging, the contents need to be protected against moisture. Minimum temperature during transportation is 5 °C.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheet

PACKAGING INFORMATION

Sikafloor® Marine-579 (A)

Pail	15.8 kg
------	---------

Sikafloor® Marine-579 (B)

Pail	4.2 kg
------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by contacting SIKA's Technical Service Department via email at tsmh@us.sika.com. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product. SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling +1 800-933-7452.

PRODUCT DATA SHEET

Sikafloor® Marine-579
Version 04.01 (07 - 2024), en_US
012119015794001000

Sika Corporation

30800 Stephenson Highway
Madison Heights, MI 48071
U.S.A.
Telephone: +1 248-577-0020
Email: tsmh@us.sika.com
www.sikausa.com

