



PRODUCT DATA SHEET

Sikafloor®-165 FS

FAST SETTING EPOXY PRIMER / BASECOAT FOR HIGH PERFORMANCE FLOOR COATINGS

PRODUCT DESCRIPTION

Sikafloor®-165 FS is a two part, epoxy resin used as a primer/basecoat.

USES

Sikafloor®-165 FS may only be used by experienced professionals.

Sikafloor®-165 FS is designed as a fast setting primer/basecoat for Sikafloor epoxy and urethane coatings, as well as for broadcast and troweled systems.

CHARACTERISTICS / ADVANTAGES

- Low VOC
- Excellent penetration and adhesion
- Ease of application
- Reduced recoat times
- High solids as supplied

PRODUCT INFORMATION

Packaging	Component A: 3.0 US gal. (11.4 L) Component B: 2.0 US gal. (5.7 L) Components A+B: 5.0 US gal. (17 L) (Ready to mix unit)
Appearance / Color	Available in Clear, Oxford Grey, and Beige Rose. It can be pigmented with Sikafloor Epoxy Pigment Pack, one [1] quart pigment per 5 US gallon mix unit. White, Safety Yellow, and Tile Red may require two [2] quarts per mixed unit.
Shelf Life	24 months in original unopened container under proper storage conditions.
Storage Conditions	Store dry between 40 °F (4 °C) and 90 °F (32 °C)
Solid Content	~ 100 % (by volume) / ~ 100 % (by weight)

TECHNICAL INFORMATION

Shore D Hardness	85	ASTM D2240 at 73 °F (23 °C) and 50% R.H
Abrasion Resistance	-0.095g (CS-17) 1000 rotations/1000g	ASTM D4060 at 73 °F (23 °C) and 50% R.H
Compressive Strength	10,877 psi (75 MPa)	ASTM D695 at 73 °F (23 °C) and 50% R.H
Flexural Strength	13,053 psi (91 MPa)	ASTM D790 at 73 °F (23 °C) and 50% R.H
Tensile Strength	8,412 psi (75 MPa)	ASTM D638 at 73 °F (23 °C) and 50% R.H
Tensile Adhesion Strength	425 psi (2.93 MPa) (Concrete failure)	ASTM D4541 at 73 °F (23 °C) and 50% R.H
Indentation	1.5%	MIL-PRF-24613 at 73 °F (23 °C) and 50% R.H
Water Absorption	1.51%	ASTM C413 at 73 °F (23 °C) and 50% R.H
Elongation at break	2.4%	ASTM D638 at 73 °F (23 °C) and 50% R.H

APPLICATION INFORMATION

Mixing Ratio	1.5 : 1 by volume		
Coverage	160–320 ft ² / US gal (3.9–7.8 m ² / L) at 5–10 mils (0.13–0.25 mm) wet film thickness.		
Pot Life	Material Temperature	Time	
	50 °F (10 °C)	~ 20 minutes	
	68 °F (20 °C)	~ 15 minutes	
	86 °F (30 °C)	~ 10 minutes	
Pot life is visible. Do not apply after indicated pot life is exceeded.			
Waiting / Recoat Times	Before applying second coat, Sikafloor Epoxy or Polyurethane on Sikafloor®-165 FS allow:		
	Substrate Temperature	Minimum	Maximum
	50 °F (10°C)	8 hours	24 hours
	68 °F (20°C)	3 hours	18 hours
	86 °F (30°C)	2 hours	12 hours

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

Substrate Moisture Content

Moisture content of concrete substrate must be ≤ 4 % by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines).

Do not apply to concrete substrate with moisture levels > 4 % mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate is > 4 % by mass (pbw – part by weight) but <6% as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor®-1620. If values are ≥ 6%, use Sikafloor®-22 NA PurCem or Sikafloor®-24 NA PurCem.

When relative humidity tests for concrete substrate are conducted per ASTM F2170, values must be ≤ 85 %. If values are > 85% but <96% according to ASTM F2170,

use Sikafloor®-1620. If values are ≥ 96%, use Sikafloor®-22 NA or 24 NA PurCem.

Material Temperature: Precondition material for at least 24 hours between 65 °F and 75 °F (18–24 °C)

Ambient Temperature: Minimum/Maximum 50/85 °F (10/30 °C)

Substrate Temperature: Minimum/Maximum 50/85 °F (10/30 °C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application must adhere to Material, Ambient and Substrate temperatures listed above or a decrease in product workability and slower cure rates will occur.

Ambient Relative Humidity: Maximum ambient humidity 85% (during application and curing)

Dew Point: Beware of condensation!

The substrate must be at least 5 °F (3 °C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

Mixing

Do not hand mix Sikafloor materials. Mechanically mix only. Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty. Improper mixing procedure or incorrect mixing ratio may result in moisture sensitivity, whitening, slow cure, soft spots, and other defects.

Application

Apply the primer to the prepared substrate using a squeegee and back roll to provide uniform coverage.

Ensure that the substrate is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate. If necessary, apply an additional coat to ensure the substrate is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur.
- Do not use with PurCem urethane cement topping systems.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings
- Do not apply Sikafloor to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- This product is not designed for negative side waterproofing.
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Beware of air flow and changes in air flow. Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.
- For professional use only by experienced applicators.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be removed to achieve a level surface prior to the application.

Concrete should be cleaned and prepared to achieve a laitance-free and contaminant-free, open textured surface by shot blasting or equivalent mechanical means (CSP-3 to CSP-4 as per ICRI guidelines).

Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate.

Whenever “shot-blasting” is utilized, be careful to leave concrete with a uniform texture. “Over-blasting” will result in reduced coverage rates of the primer and/or subsequent topcoats. The “shotblast” pattern may show through the last coat, known as “tracking”.

The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) with a minimum pull off strength of 218 psi (1.5 MPa) in tension at the time of application. For other substrates, please contact Sikafloor Technical Services.

MIXING

Mixing Ratio - 1.5 : 1 by volume.

Primer

Premix each component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 3 minutes using a low speed drill (300–450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air while mixing.

Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge tool at least once to ensure complete mixing.

Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

Apply primer/basecoat by squeegee at the rate of 160–320 ft² / US gal (3.9–7.8 m² / L) at 5–10 mils (0.13–0.25 mm) wet film thickness (w.f.t.) and back roll with pressure. Coverage will vary depending on the

porosity of the prepared floor. Product has a limited Pot Life, see Typical Data.

Do not apply by dipping roller into mixing container. Pour a bead of product in the form of a ribbon on the surface to be coated, then spread with squeegee and back roll. Ensure that the coating is pore-free and pinhole free and provides uniform and complete coverage over the entire concrete substrate.

If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF**

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikafloor®-165 FS
January 2025, Version 02.01
020811020010000076

MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sikafloor-165FS-en-US-(01-2025)-2-1.pdf

