



PRODUCT DATA SHEET

Sikafloor® QuartzTop-115

(formerly MTop 115)

RAPID-SETTING SURFACE FINISHING UNDERLAYMENT

PRODUCT DESCRIPTION

Sikafloor® QuartzTop-115 is used to finish and smooth fully cured concrete, wood underlayments, linoleum (residential), ceramic tile, and adhesives including cutback. Combined with water, Sikafloor® QuartzTop-115 mixes to a creamy smooth consistency for ease of application. Designed around a Portland cement-based matrix, Sikafloor® QuartzTop-115 is a rapid-setting, aggregate-free, polymer-modified cement-based finishing underlayment.

USES

- Skim coating and smoothing rough concrete
- For filling minor voids, holes, and cracks in concrete and underlayments
- Leveling and smoothing wood underlayment seams and joints
- Leveling and filling embossed sheet goods
- Skim coating over ceramic tile
- Skim coating over adhesive residue (cutback included) that is thin, well bonded, structurally sound, and non-water soluble

CHARACTERISTICS / ADVANTAGES

- Can be feather-edged
- Rapid setting minimizing downtime
- Compatible with most flooring adhesives
- Primerless
- Can be mixed with SikaLatex® A 100 to increase adhesion to embossed material

PRODUCT INFORMATION

Packaging	10 lb (4.5 kg) bags; 4 bags per case
Shelf Life	6 months in original, unopened packaging
Storage Conditions	Protect from moisture and dampness. Store in a cool, dry area. Do not expose packaging to sun. Roll bag of unused portion tightly to remove air and retain freshness.

APPLICATION INFORMATION

Product Data Sheet
Sikafloor® QuartzTop-115
September 2024, Version 02.01
02081500000002038

Coverage

10 lb (4.5 kg) unit yields:

- over concrete: 100–150 ft² (9.3–14 m²)
- over plywood: 200–250 ft² (18.6–23.3 m²)

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

NOTES ON INSTALLATION

Sikafloor® QuartzTop-115 is used to smooth substrate transitions and ridges and to fill cracks, knots, and joints in wood underlayment. Sikafloor® QuartzTop-115 is also used for a true featheredge skimcoat over all types of interior concrete, masonry, wood, terrazzo, quarry, and ceramic tile.

Sikafloor® QuartzTop-115 is used as an embossing filler for embossed sheet vinyl when mixed with SikaLatex® A 100. Sikafloor® QuartzTop-115 can be used over structurally sound, permanently bonded, properly prepared residues of thin cutback and non-water soluble adhesives that may exist on concrete installations. When using Sikafloor® QuartzTop-115 over cutback residue, substitute full-strength SikaLatex® A 100 in place of water. Adhesive residue on concrete must be inert to the new adhesive being installed, and the chosen floor covering must not be sensitive to adhesive migration. Consult Sika Technical Service for specific installation recommendations.

For Best Performance

- Subfloors to receive Sikafloor® QuartzTop-115 must be a minimum of 50° F (10° C).
- All subfloors must be free of surface moisture and within the flooring manufacturer's recommended moisture content and vapor drive. Consult the chosen flooring manufacturer for recommended installation temperatures and the maximum allowable moisture content test methods and vapor drive of the substrate for installation of their flooring product.
- Applications over cutback adhesive residue must be exclusively on concrete.
- Do not use in areas subjected to constant moisture or intermittent water exposure.

- Sikafloor® QuartzTop-115 is not designed as the final wearing surface.
- Using more water than recommended will weaken the Sikafloor® QuartzTop-115 and extend the cure time.
- Make certain the most current versions of the product data sheet and SDS are being used.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

SUBSTRATE PREPARATION

1. Areas to be finished or repaired must be clean, structurally sound, and free of all loose, dirty, oily and scaly material, or any material that may affect proper bonding. Dust, dirt, oil, or other contaminants must be thoroughly vacuumed and extracted from concrete.
2. Remove all curing compounds, sealers, waxes, paints, and patching compounds. Mechanical abrasion may be required for thorough removal.
3. Do not use acid etching, solvents, or sweeping compounds for surface preparation.
4. Sikafloor® QuartzTop-115 is for interior installations only. Do not use in areas of constant or intermittent water exposure. Do not apply over press board, gypsum-based substrates, or similar unstable substrates.
5. Subfloors to receive Sikafloor® QuartzTop-115 must be a minimum of 50° F (10° C). All subfloors must be free of surface moisture and excessive vapor drive within the flooring manufacturer's recommended moisture content. Consult the chosen flooring manufacturer for recommended installation temperatures and the maximum allowable moisture content and vapor drive of the substrate for installation of their flooring product when tested according to the flooring manufacturer's recommendations.
6. Before the application of Sikafloor® QuartzTop-115, all existing adhesive residues over concrete must be tested for water solubility to ensure they will not react with the new flooring adhesive. Also, the new flooring adhesive must not be sensitive to bleed-through of the cutback adhesive. Wet scrape the existing adhesive to a well-bonded residue using the technique outlined by the Resilient Floor Covering Institute. Existing patches must be completely removed by mechanical means.

MIXING

1. The mixing ratio is two parts Sikafloor® QuartzTop-115 to one part water by volume with small adjustments to achieve the installer's preferred consistency.
2. Note: When using Sikafloor® QuartzTop-115 as an embossing filler, substitute full-strength SikaLatex® A 100 in place of water.
3. In a clean mixing container pour approximately enough

Product Data Sheet

Sikafloor® QuartzTop-115

September 2024, Version 02.01

02081500000002038

- powder to place in 20 minutes. Add water while slowly mixing with a margin trowel or Jiffy mixer.
- Vigorously mix to a smooth, lump-free consistency.
 - Note: Mechanical mixing with a portable drill and Jiffy mixer at low RPM will produce a creamier (fluffier) and smoother consistency.
 - To mix an entire bag, use approximately 2.5 quarts (2.4 L) water with a 10 lb (4.5 kg) unit.

APPLICATION

Installation

- Steel trowel to desired thickness and finish, making sure the product is properly keyed into the subfloor substrate. Apply enough pressure to fill all voids and defects. Feather out where a seamless interface is desired. Sikafloor® QuartzTop-115 may be applied from feather edge to ½" (13 mm) in thickness. When using Sikafloor® QuartzTop-115 with un-diluted Acrylic Additive, the maximum thickness is ¾" (6.35 mm).
- Sikafloor® QuartzTop-115 does not require a minimum thickness. Use the least amount of material to achieve the desired surface smoothness.
- Over large areas, Sikafloor® QuartzTop-115 can be installed from a true feather edge up to ½" (13 mm) thick in one application. Thicker applications can be placed in small, well-defined areas such as transitions, thresholds, and birdbaths.
- Pot life is 15 to 20 minutes at 70° F (21° C). Pot life will vary with ambient and substrate temperature. When setting in the pail, remix to regain workability if the material stiffens. Do not add additional water or SikaLatex® A 100.

Flooring Installation

- Floor coverings may be installed as soon as the surface is sufficiently hard and is not damaged by the application of the flooring adhesive. This can be in as little as 15 to 20 minutes for skimcoat applications depending on temperature, relative humidity, and subfloor conditions. Thicker sections will require more time.
- Flooring and flooring adhesives that are sensitive to moisture can be installed after 16 hours. These include wood flooring, athletic flooring, and those that require epoxy or urethane adhesives.
- Sikafloor® QuartzTop-115 is compatible with all adhesives that are compatible with concrete.

Embossing Filler

All existing felt-backed embossed sheet vinyl must be clean and free of any dressings and waxes. The sheet vinyl must be installed over a suitable structurally sound substrate and be free of moisture and friable particles.

Do not use over-perimeter bonded sheet vinyl or cushion back flooring that is thicker than .080" (2 mm) thick.

Application

Using the flat side of a trowel, apply a very thin layer of Sikafloor® QuartzTop-115 mixed with SikaLatex® A 100 to fill in the existing pattern on the prepared residential sheet vinyl.

Allow the embossing filler to dry before installing the residential sheet vinyl (approximately 90 minutes).

When a twist of a shoe does not affect the bond of the embossing filler, the surface is ready for installation.

NOTE: The filled vinyl is considered a nonporous substrate when dried. Select an adhesive that is appropriate for nonporous substrates.

APPLICATION METHOD / TOOLS

- Plastic mixing pail
- Clean mix water
- Margin trowel
- Steel trowel

For best results, use a ½" (13 mm) portable drill with a Jiffy mixer at low RPM. Razor scrapers (for cutback residue removal), vacuum, and other equipment may be needed for subfloor preparation.

CLEANING OF TOOLS

Clean tools and equipment immediately with water. Cured material can be removed by mechanical means only.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the

current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikafloor® QuartzTop-115
September 2024, Version 02.01
02081500000002038

SikafloorQuartzTop-115-en-US-(09-2024)-2-1.pdf

