

PRODUCT DATA SHEET

SikaTile®-910 Floor Mud

PROFESSIONAL-GRADE PORTLAND CEMENT MORTAR BED UNDERLAYMENT

PRODUCT DESCRIPTION

SikaTile®-910 Floor Mud is a factory-premixed blend of specially grounded sand and Portland cement for thick-bed mortar installations. SikaTile®-910 Floor Mud can be used to flatten, level or slope over existing substrates before the installation of tile and stone.

USES

SikaTile®-910 Floor Mud as a bonded or non-bonded, conventional thick mortar bed on horizontal surfaces

- Provides a solid foundation substrate prior to the installation of tile and stone
- Float shower pans and dry pack mixes
- Can be directly bonded or used as a detached mortar bed over a waterproofing membrane
- Both residential and commercial applications in dry and wet areas
- For increased performance and reduced porosity, mix with Sika® Latex R admixture

SUITABLE SUBSTRATES

SikaTile®-910 Floor Mud can be installed in most interior and exterior residential and commercial installations on floors over the following recommended substrates:
Brick Masonry • Concrete • Exterior Grade Plywood¹ • Gypsum Drywall¹ • SikaLevel® Products

¹ Interior Use Only.

CHARACTERISTICS / ADVANTAGES

- Easy to install by screed or trowel
- Excellent bond to concrete and wood with minimal preparation
- Trowels to a smooth, uniform finish
- Cures in 24 hours

- Crack resistant and fire retardant
- Good thermal and acoustical insulating properties
- Excellent adhesion to most common substrates
- Use as a dry pack mix
- May be installed from 1/2 to 2"
- Easy to mix with the addition of water. For increased performance and reduced porosity, mix with Sika® Latex R admixture

ENVIRONMENTAL INFORMATION

Environmental Consideration

Sika® is committed to environmental responsibility in both products produced and in manufacturing practices. Complete the LEED Product Data Request Form at SikaTile.com for detailed information based on project location. Use of this product can contribute toward LEED® v4.1 certification:

- Up to 2 points toward MR Credit 5, Regional Materials
- Up to 1 point towards IEQ Credit 4.1, Low-Emitting Materials – Adhesives & Sealants

APPROVALS / STANDARDS

American National Standards Institute (ANSI) — ANSI A108.01 of the American National Standards for the Installation of Ceramic Tile ASTM International (ASTM)

- ASTM C109 Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- ASTM C627 Standard Test Method for Evaluating Ceramic Floor Tile Installation Systems Using the Robinson-Type Floor Tester
- Resilient Floor Covering Institute - (RFCI) Recommended Work Practices for Removal of Resilient Floor Coverings
- Tile Council of North America (TCNA) - TCNA Handbook for Ceramic Tile Installation, TCNA F125, F125A and

Product Data Sheet

SikaTile®-910 Floor Mud

April 2026, Version 01.01

021790101000000032

Property	Test Method	Results
Weight	--	1.2 lb. per sq.ft. at 1/8"
Indentation	MIK-D-3135d	< 3%
Shear to Concrete	--	> 550 psi
Compressive Strength 28 day	ASTM C109	6,000 psi
VOC content	--	0 g per L

PRODUCT INFORMATION

Chemical Base	Portland cement, selected aggregates, water retention additives
Packaging	5- lb. (22.68-kg.) bag; 48 bags per pallet
Color	Gray
Shelf Life	18 months from date of production when stored in original, sealed package
Storage Conditions	Store in undamaged, original, sealed package, in dry conditions at 73° F (23° C)

APPLICATION INFORMATION

Coverage	~6.25 sq.ft. at 3/4" thickness per 50 lb. bag
-----------------	---

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- Do not use below 40°F (4°C) or above 95°F (35°C).
- Do not allow mortar to freeze for the first 72 hours.
- Cool and wet weather may delay set times.
- Do not use over Masonite®, cement asbestos board, metal, glass, plastic, gypsum mortar beds or other unstable substrates. Improperly cured or wet plywood, particle board or strip wood are not suitable substrates.
- Do not use as a finished surface.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

NOTES ON INSTALLATION

SikaTile® underlayments, when properly installed in accordance with the following installation guidelines, provide years of protection for finished floor installations. In addition to these instructions, installers shall also reference the most current edition of American National Standards Institute (ANSI), Tile Council of North America (TCNA) Handbook for Ceramic Tile Installations, The Marble Institute of America (MIA) Dimension Stone Design Manual, NWFA (National Wood Flooring Association) and manufacturer's instructions of selected setting materials, substrates, sub-floors, or other materials being used in total, or any part of, an installed floor system with SikaTile®. Consult your selected manufacturer of these previously mentioned components to ensure products are compatible with SikaTile® underlayments.

SUBSTRATE PREPARATION

All surfaces must be between 40°F (4°C) and 90°F (32°C) and structurally sound (deflection not to exceed L/360 for ceramic and porcelain tiles and L/720 for natural stone), dry, clean, and free from oil, grease, wax, paint, old adhesives, sealers, and curing compounds. Any contaminants that inhibit proper bond must be removed. Substrate preparation should be completed following ANSI A108 AN-2 "General Requirements for Sub-surfaces." All substrates should be plumb and true; surface deviation should not exceed 1/4" in 10' or 1/8" in 10' for large format tiles. Patching, leveling or areas requiring a mortar bed should be prepared using Sika® underlayments. Movement (expansion) joints should be

provided to comply with TCNA method EJ171. Concrete must be free of any negative hydrostatic pressure and/or excessive moisture.

MIXING

Dry Pack Mix: In a clean container, add approximately 3.5 quarts (3.3 liters) of clean, cool potable water. Then add the contents of the 50-lb (22.7-kg) SikaTile®-910 Floor Mud. Mix thoroughly by hand in a mud box or wheelbarrow or with a slow speed mixer to a semi-dry, thick, trowelable consistency. Mixed material should be able to be formed into a ball without crumbling apart. Do not temper with additional water.

APPLICATION

Read and follow manufacturer's instructions before installation.

For concrete floors, first broom a uniform, bond coat of Portland cement paste onto the floor. Immediately apply mixed SikaTile®-910 Floor Mud by packing and screeding the material into place. It may be installed from 1/2 to 2". SikaTile®-910 Floor Mud can be applied over most clean, dry sub-surfaces. It has an initial set in two hours and final set in five hours based on thickness and ambient conditions. Consult job specifications and industry standards for final thickness application. For wood floors and counters, first apply roofing felt or building paper followed by minimum 2.5-lb. metal lath overlapping both the paper and the lath. Lath should be fastened every 8 inches. For unbonded mud bed, install the lath between the mortar bed. Apply SikaTile®-910 Floor Mud same as for concrete floors, ensuring to press the mortar through lath with pressure to a final thickness of 1/2 to 2".

Refer to ANSI A108.1 industry standard for details on mortar bed installations.

CLEANING OF TOOLS

Water is all that is needed to remove any uncured mortar from tiles, tools and equipment.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

SikaTile®-910 Floor Mud
April 2026, Version 01.01
021790101000000032

SikaTile-910FloorMud-en-US-(04-2026)-1-1.pdf

