

PRODUCT DATA SHEET

Sika® Ucrete® TCCS

(formerly Ucrete® TCCS)

Heavy-duty, color-stable, encapsulation resin for enhanced aesthetics

PRODUCT DESCRIPTION

Sika® Ucrete® TCCS is a three-part, heavy-duty, fast-cure encapsulation resin. It provides a highly aesthetic, color-stable, matt sheen finish for the Sika® Ucrete® CS range of flooring systems.

USES

Sika® Ucrete® TCCS is used as a top coat for Sika® Ucrete® flooring systems.

Please note:

- The Product may only be used by experienced professionals.

CHARACTERISTICS / ADVANTAGES

- Expert installation by fully trained applicators
- Very good resistance to staining from a specific range of chemicals and food industry products
- Very good resistance to UV exposure
- Good yellowing resistance provides long-term color stability
- Fast curing
- Non-tainting after curing
- Good temperature resistance

APPROVALS / STANDARDS

- Halal Certification Europe (HCE), Sika® Ucrete®, WHFC, Certificate No. 21453-2/1/1/Y1
- Food and Beverage Facilities Suitability, Sika® Ucrete®, HACCP, Test Report No. I-PE-769-SA-2-RG-06b
- Indoor Air Comfort Gold EN 16516, Sika® Ucrete®, eurofins, Certificate No. IACG-321-01-01-2023

PRODUCT INFORMATION

Chemical Base	Acrylic	
Packaging	7.35 kg Refer to the current price list for available packaging variations.	
Shelf Life	Always refer to the best-before date of the individual packaging.	
Storage Conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 41 °F and 86 °F. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.	
Color	Cured color	Grey, Light Grey, Cream, Yellow, Bright Yellow, Green, Light Green, Green/ Brown, Red, Orange, Blue, Light Blue.

TECHNICAL INFORMATION

Tensile Adhesion Strength	>290 psi (concrete failure)	(EN 1542)
Chemical Resistance	Laboratory-defined resistance to many individual chemicals. Before proceeding, contact Sika Technical Service for specific information.	

APPLICATION INFORMATION

Coverage	Approximately 150 ft ² / kit @ 10-11 mils Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply the Product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.	
Product Temperature	Maximum	71.6 °F
	Minimum	53.6 °F
Ambient Air Temperature	Maximum	71.6 °F
	Minimum	53.6 °F
Dew Point	Beware of condensation. The substrate and uncured applied product must be at least 37.4 °F above the dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and high humidity conditions increase the probability of blooming.	
Substrate Temperature	Maximum	71.6 °F
	Minimum	50 °F
Cure Time	The floor can be returned to service after 2 hours. Note: Times are approximate and will be affected by changing ambient and substrate conditions.	
Waiting / Recoat Times	Minimum	2–3 hours
	Maximum	48 hours
	Note: Times are approximate and will be affected by changing ambient	

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

APPLICATION

Application must be undertaken by a fully trained Sika® Ucrete® applicator.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sika® Ucrete® TCCS
August 2024, Version 01.02
02081400000002019

SikaUcreteTCCS-en-US-(08-2024)-1-2.pdf

