

PRODUCT DATA SHEET

Sikalastic® EP Primer Rapid

TWO COMPONENT, FAST CURING UNIVERSAL PRIMER FOR SIKALASTIC® ROOFPRO AND SIKALASTIC® DECKPRO SYSTEMS

PRODUCT DESCRIPTION

Sikalastic® EP Primer Rapid consists of two components an epoxy resin (Part A), and an activator (Part B). In its wet mixed state, it is red in color.

USES

Versatile and fast curing universal primer for use with:

- Sikalastic® RoofPRO Systems
- Sikalastic® DeckPRO Systems

Suitable for use on most sound substrate surfaces where both a penetrative and surface-lying effect is required.

CHARACTERISTICS / ADVANTAGES

- Low odor, low VOC formulation
- Fast curing
- Compatible with most common substrate and flashing materials
- Corrosion protection in industrial and marine environments
- Enhances adhesion to a broad range of metallic substrates
- Protects against migration of volatile bitumen or plasticizers
- Easy application by brush or roller

PRODUCT INFORMATION

Chemical Base	Epoxy	
Packaging	1 gal. kit (0.63 gal. Part A, 0.37 gal. Part B)	
Appearance / Color	Red	
Shelf Life	24 months	
Storage Conditions	Store dry between 40 °F and 95 °F (2–35 °C) Condition material to 50–77 °F (10–25 °C) before using for ease of application.	
Solid Content	94.5 % by volume	(ASTM D-2697)
Volatile organic compound (VOC) content	74.24 g/l	(ASTM D-2369-81))
Service Temperature	-22–176 °F (-30–80 °C) intermittent	
Mixing Ratio	Component A : Component B = 1.7 : 1.0 (by volume)	
Coverage	Coverage: 200 - 250 ft ² /gal. on non-absorbent smooth substrates.	

150 - 200 ft²/gal. on prepared, dry concrete.
 75 - 100 ft²/gal. on mineral surfaced modified bitumen.

Note: Rough, porous, or absorbent surfaces will require additional primer and will reduce yield.

Ambient Air Temperature	41 °F (5 °C) min. / 95 °F (35 °C) max.																		
Relative Air Humidity	80 % R.H. max.																		
Dew Point	Beware of condensation. The substrate and uncured coating must be ≥ 5 °F (3 °C) above dew point.																		
Substrate Temperature	41 °F (5 °C) min. / 140°F (60°C) max.																		
Substrate Moisture Content	≤ 4 % moisture content Test method: Sika®-Tramex meter No rising moisture according to ASTM (Polyethylene-sheet).																		
Pot Life	30 minutes																		
Cure Time	<p>Before applying any recommended Sikalastic® resin on Sikalastic® EP Primer Rapid, allow:</p> <table border="1"> <thead> <tr> <th>Ambient temperature</th> <th>Mimimum waiting time</th> <th>Maximum waiting time</th> <th>Touch dry</th> </tr> </thead> <tbody> <tr> <td>50 °F</td> <td>7 hours</td> <td>72 hours</td> <td>5 hours</td> </tr> <tr> <td>68 °F</td> <td>5 hours</td> <td>72 hours</td> <td>3 hours</td> </tr> <tr> <td>88 °F</td> <td>3 hours</td> <td>72 hours</td> <td>2 hours</td> </tr> </tbody> </table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity. Ideally, membrane resin will be applied within 24 hours of primer application. Maximum primer exposure is 72 hours. Primer exposed longer than 72 hours, and primer exposed to water during curing and exhibiting a chalky appearance, must be reprimed. Deteriorated primer must be mechanically removed before primer reapplication.</p>			Ambient temperature	Mimimum waiting time	Maximum waiting time	Touch dry	50 °F	7 hours	72 hours	5 hours	68 °F	5 hours	72 hours	3 hours	88 °F	3 hours	72 hours	2 hours
Ambient temperature	Mimimum waiting time	Maximum waiting time	Touch dry																
50 °F	7 hours	72 hours	5 hours																
68 °F	5 hours	72 hours	3 hours																
88 °F	3 hours	72 hours	2 hours																

SUBSTRATE PREPARATION

Always perform an adhesion test before applying Sikalastic® EP Primer Rapid. All substrate surfaces shall be clean, dry and sound. Acceptable substrates include: sound concrete and masonry, wood and plywood, modified bitumen membrane, mineralized asphaltic cap sheet, asphalt and asphalt mastic, ferrous metals, galvanized, lead, copper, aluminum, brass, and stainless steel. Reference separate System Data Sheet for specific surface preparation requirements.

MIXING

Mix ratio is 1.7 : 1.0 (A:B) by volume. Add Part B into Part A and mix with stir stick or mechanical mixer (Jiffy) at low speed. Avoid adding air into the primer during mixing. When fully mixed, the primer should be free from streaks and of a uniform red color. Do not break down kits into smaller quantities.

APPLICATION

Apply by brush or phenolic resin core roller at the recommended rate. Correct amount of primer will saturate the substrate and leave a slight film on the substrate top surface. Apply evenly without puddling.

CLEANING OF TOOLS

Remove wet primer with MEK, xylene, or oxygenated solvents. Once cured, primer can only be removed by mechanical means. Strictly follow solvent manufacturer’s warnings and instructions for use.

LIMITATIONS

- Do not apply on substrates with moisture content greater than 4 % by weight, measured by Tramex® Concrete Moisture Encounter Meter.
- Minimum age of concrete must be 28 days depending on curing and drying conditions.
- Do not thin with solvents.
- Sikalastic® EP Primer Rapid is not suitable for application over single ply membranes (PVC, TPO, EPDM)
- Do not store materials outdoors exposed to sunlight and moisture for prolonged periods.
- Do not apply to substrate surfaces where moisture vapor transmission will occur during application and cure.
- This condition may be checked using ASTM D-4263 (Polyethylene Sheet method).
- Substrate must be dry prior to application. Do not apply to a frosted, wet or damp surface. Allow



sufficient time for the substrate to dry after rain or inclement weather, as there is the potential for bonding problems.

- On substrates likely to exhibit outgassing apply during falling ambient and substrate temperature. If applied during rising temperature pinholing may occur.
- Precautions should be taken to prevent vapors and/or odors from entering the building/structure, including but not limited to turning off and sealing air intake vents and through-wall air conditioners, and other means of ingress during application and cure.
- Any repairs required to achieve a level surface must be performed prior to application (consult a Sika representative for guidance on various product solutions). Surface irregularities may reflect through the cured system.
- When applying over new or existing coatings, membranes and substrates; compatibility and adhesion testing and subsequent approval by Technical Services is required.
- On grade concrete decks should not be covered with Sikalastic® membrane systems.
- Unvented metal pan, split/sandwich slab with encapsulated membrane and/or insulation, cinder fill decks, and lightweight insulating concrete overlays should not be covered with Sikalastic® membrane systems without deck evaluation and subsequent approval by Technical Services.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Sarnafil

100 Dan Road
Canton, MA 02021
Phone: +1 800-451-2504
Fax: +1 781-828-5365
usa.sarnafil.sika.com
webmaster.sarnafil@us.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

SIKA CORPORATION – ROOFING

100 Dan Road
Canton, MA 02021
Phone: +1-800-451-2504
Fax: +1-781-828-5365



Product Data Sheet

Sikalastic® EP Primer Rapid
October 2019, Version 01.02
02091595100000067

SikalasticEPPrimerRapid-en-US-(10-2019)-1-2.pdf

