


Product Data Sheet

Edition 6.16.2017

Identification no.

SikaWrap 600C

	✓	ICC	ESR-3288
	✓	IBC	2015 Compliance

SikaWrap® 600C ± 45

Double Bias Carbon Fiber Fabric for Structural Strengthening

Description SikaWrap 600C ± 45 is a high strength, bi-directional ± 45 carbon fiber fabric. Material is field laminated using Sikadur Hex 300 or Sikadur 330 epoxy to form a carbon fiber reinforced polymer (CFRP) used to strengthen structural elements.

- Where to Use**
- Loading Increases
 - Increasing the live loads
 - Increasing traffic volumes on bridges
 - Installation of heavy machinery in industrial buildings
 - Vibrating structures
 - Changes of building utilization
 - Seismic Strengthening
 - Column wrapping
 - Masonry walls
 - Damage to Structural Parts
 - Aging of construction materials
 - Vehicle impact
 - Fire
 - Blast Resistance
 - Change in Structural System
 - Removal of walls or columns
 - removal of slab sections for openings
 - Design or Construction Defects
 - Insufficient reinforcements
 - Insufficient structural depths

- Advantages**
- Approved by ICC ESR-3288.
 - Provides high strength in multiple directions
 - Used for shear, confinement or flexural strengthening
 - Flexible, can be wrapped around complex shapes
 - High Strength
 - Light Weight
 - Non-corrosive
 - Alkali Resistant
 - Low Aesthetic Impact

Packaging Rolls: 50" x 225 ft

Typical Data

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Storage Conditions	Store dry at 40°-95°F (4°-35°C)
Shelf Life	10 years
Product Conditioning	Condition fabric to same temperature as recommended for conditioning the specified Sikadur epoxy adhesive(s)
Color	Black
Primary Fiber Direction	+45/-45° (bidirectional)
Areal Weight	17.11 osy (580 gsm) Total

Typical Dry Fiber Properties

Property	Typical Test Value
Tensile Strength	711 ksi (4,900 MPa)
Tensile Modulus	33.4 msi (230 GPa)
Elongation at Break	2.1%
Areal Weight	17.11 osy (580 gsm) total
Density	0.065 lb./in. ³ (1.80 g/cm ³)
Nominal Fiber Thickness	0.0063 in. (0.161 mm) each fiber direction
Fiber Direction	bidirectional (+/-45)



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

Cured Laminate Properties

Property, each fiber direction (+45, -45)	Average Ultimate Value	Design Value	ASTM Method
Tensile Strength	173.2 ksi (1,194 MPa)	144.4 ksi (996 MPa)*	D3039
Tensile Modulus (E_T)		12.52 msi (86.3 GPa)	D3039
Tensile % Elongation	1.39%	1.09%*	D3039
Nominal laminate thickness		0.0195 in. (0.50 mm) each fiber direction	
Tensile strength per unit width		2.8 kips/in./ply	D7565
Stiffness ($E_T \cdot A$) per unit width		244 kips/in./ply	D7565

*Average ultimate value minus 3 standard deviations

How To Use

Surface Preparation

Surface must be clean and sound. It may be dry or damp, but free of standing water and frost. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles, disintegrated materials, and other bond inhibiting materials from the surface. Existing uneven surfaces must be filled with an appropriate repair mortar. The adhesive strength of the concrete must be verified after surface preparation by random pull-off testing (ASTM D4541) at the discretion of the engineer. Minimum tensile strength, 200 psi (1.4 MPa) with concrete substrate failure.

Concrete - Blast clean, shotblast or use other approved mechanical means to provide a roughened, open-textured surface. In certain applications and at the engineer's discretion, the intimate contact between the substrate and the fabric may be determined to be non-critical. In these cases, a thorough cleaning of the substrate using low pressure sand blasting or water blasting is sufficient.

Mixing

Consult the current product data sheet(s) for recommendations on the specified Sikadur epoxy adhesive(s) needed.

Application

Prior to placing the fabric, the concrete surface is primed and sealed using the appropriate Sikadur epoxy adhesive (e.g. Sikadur Hex 300 or Sikadur 330 US). Material may be applied by spray, brush or roller.

SikaWrap 600C ±45 can be impregnated using Sikadur Hex 300 epoxy. For best results on larger projects, the impregnation process should be accomplished using Sikadur Hex 300 and a mechanically driven saturator or similar device. In special cases where the size of the project does not justify the use of a saturator, the fabric may be saturated by hand using a ruler prior to placement. In either case, installation of this system should be performed only by a specially trained contractor.

For overhead and vertical applications, prime concrete with Sikadur 30 or Sikadur 330 US to improve tack. Saturate fabric with Sikadur Hex 300. Coat the exposed surface of final fabric layer using Sikagard 670W or Sikagard 62.

Tooling & Finishing

Cutting SikaWrap

Fabric can be cut to appropriate length by using a commercial quality, heavy duty scissor. Since dull or worn cutting implements can damage, weaken or fray the fiber, their use should be avoided.

Limitations

- DESIGN CALCULATIONS MUST BE MADE AND CERTIFIED BY AN INDEPENDENT LICENSED PROFESSIONAL ENGINEER
- SYSTEM IS A VAPOR BARRIER. CONCRETE SHOULD NOT BE ENCAPSULATED IN AREAS OF FREEZE/THAW
- Sika cannot and will not determine the location, spacing, and orientation of the SikaWrap system installation on actual projects.
- Do not place carbon fiber in direct contact with steel. Must be isolated (e.g. glass fabric) to protect against corrosion.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

