

LITHOTIQUE™ Antiquing Agent

Secondary Color Accent for Hardened Stamped Concrete or Cementitious Overlays

■ Contractor Sheet 11.1341.8 ■



Protect Your Concrete with Scofield Sealers

Scofield sealers protect the surface, enhance the appearance of colored concrete, and may provide protection against contamination and chemical attack by imparting a film-forming layer on the surface of the concrete. Consult a Scofield Concrete Cures & Sealers Guide.

LITHOTIQUE™ Antiquing Agent is a proprietary blend of powders that, when mixed with water and properly applied to a stamped or imprinted concrete surface, will impart a secondary color to the surface, visually enhancing its texture.

LITHOTIQUE™ Antiquing Agent

Secondary Color Accent for Hardened Stamped Concrete or Cementitious Overlays

■ Contractor Sheet 11.1341.8 ■

LITHOTIQUE™ Antiquing Agent can be applied to hardened newly stamped concrete, unsealed existing stamped concrete and unsealed SCOFIELD® Texturetop® Pro Stamp Grade. LITHOTIQUE™ Antiquing Agent is inventoried in 14 standard colors that can be found on our LITHOCHROME® Antiquing Release Pro color chart. LITHOTIQUE™ Antiquing Agent is designed for use on stamped textured surfaces and should not be used on untextured surfaces.

Colors:

- Available in 14 standard colors. See color chart A-136LA

Packaging:

- 1 gallon plastic container filled with 3 lb. of powder

Coverage:

- 2,000-3,000 sq. ft. per 3 lb. of powder

Ideal uses:

- Used to add an accent color to unsealed hardened textured concrete and unsealed overlaid textured surfaces
- Once the surface has been coated, the solids in the LITHOTIQUE™ Antiquing Agent will settle and concentrate in the low areas, giving a natural accent color to the textured surface

Keys to Success:

- Concrete surface must be free of grease, oil residue, curing or sealing compound residue, and any other potential bond breakers
- Add 3/4 cup (6 oz.) of LITHOTIQUE™ Antiquing Agent per gallon of clean potable water in a plastic vessel that leaves adequate room for mixing. Mix vigorously with drill and mixing paddle until all the powder has been incorporated into the water
- Use a pump-up sprayer and apply an even coat to the surface
- During application keep the material agitated to avoid settling in the container
- The amount of LITHOTIQUE™ Antiquing Agent added to water can be increased or decreased depending on the amount of antiquing that you desire. The maximum amount of LITHOTIQUE™ Antiquing Agent that can be used is 1.5 cups per gallon of water
- When applying over recently poured concrete or overlay, a mild acid wash of 10 parts water to 1 part muriatic acid is recommended to remove any residual release agent and open up the surface to accept LITHOTIQUE™ Antiquing Agent
- LITHOTIQUE™ Antiquing Agent must be sealed to maintain longevity. LITHOTIQUE™ Antiquing Agent can be sealed with the following sealers: SCOFIELD® Cureseal™ 700 or SCOFIELD® Cureseal™ 350

