

PRODUCT DATA SHEET

Ply Sheet TA 87

PLY SHEET TA 87 IS A TORCH APPLIED SBS MODIFIED BITUMEN FIBER-GLASS REINFORCED PLY SHEET

PRODUCT DESCRIPTION

Ply Sheet TA 87 is a 87 mil (2.2 mm) thick torch applied SBS modified bitumen fiberglass reinforced ply sheet for use within Sarnafil® hybrid roofing systems. Ply Sheet TA 87 can also be used as a vapor retarder in Sarnafil® and Sikaplan® roofing systems. It can be left exposed for up to six (6) months.

USES

- Ply sheet within Sarnafil® hybrid roofing systems
- Vapor retarder within Sarnafil® and Sikaplan® roofing systems

Areas of Application

- Sarnafil hybrid roofing systems over light weight insulating concrete, cementitious wood fiber deck and metal deck
- Vapor retarder direct to structural concrete deck and approved primd gypsum boards

CHARACTERISTICS / ADVANTAGES

- Torch application allows for installation without low temperature restrictions
- Fiberglass reinforcement provides dimensional stability
- Fine mineral aggregate (sand) topside accepts approved urethane adhesives for membrane attachment
- Weathering surface allows for exposure for up to six (6) months

APPROVALS / STANDARDS

- FM Global
- Underwriters Laboratories
- Florida Building Code
- Meets ASTM D6163, Type I, Grade S
- Tested according to ASTM E108
- Tested according to ANSI/FM 4474 for wind uplift
- Tested according to Miami-Dade TAS 114 for wind uplift

PRODUCT INFORMATION

Chemical Base	SBS polymer modified bitumen with a fiberglass mat reinforcement and fine mineral aggregate (sand) topside and polyolefin burn-off film underside	
Packaging	39.4" (1 m) x 49.2 ft (15 m) roll, 101 lbs (45.8 kg) per roll, 30 rolls per pallet	
Shelf Life	N/A	
Storage Conditions	Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture.	
Overall Thickness	87 mil (2.2 mm)	(ASTM D-5147)
Mass per Unit Area	62.6 lb/100ft ² (3054 g/m ²)	(ASTM D-5147)

TECHNICAL INFORMATION

Tensile Strength	Peak Load @ 0°F (-18°C)		(ASTM D-5147)
	Machine Direction	Cross Machine Direction	
	100 lbf/in (17.5 kN/m)	90 lbf/in (15.8 kN/m)	
	Peak Load @ 73.4°F (23°C)		
	Machine Direction	Cross Machine Direction	
	50 lbf/in (8.8 kN/m)	40 lbf/in (7.0 kN/m)	
Elongation	Elongation at Peak Load @ 0°		(ASTM D-5147)
	Machine Direction	Cross Machine Direction	
	4 %	4 %	
	Elongation at Peak Load @ 73.4°F (23°C)		
	Machine Direction	Cross Machine Direction	
	5 %	4 %	
	Ultimate Elongation @ 73.4°F (23 °C)		
	Machine Direction	Cross Machine Direction	
	45 %	45 %	
Dimensional Stability	Machine Direction	Cross Machine Direction	(ASTM D-5147)
	<0.1 %	<0.1 %	
Tear Strength	Machine Direction	Cross Machine Direction	(ASTM D-5147) at 73.4°F (23°C)
	60 lbf (267 N)	60 lbf (267 N)	
Low Temperature Bend	Machine Direction	Cross Machine Direction	(ASTM D-5147)
	-15°F (-26°C)	-15°F (-26°C)	
Water Vapor Transmission	0.010 perms (0.565 ng/(Pa·s·m ²))		(ASTM E-96)

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All surfaces must be clean, sound, dry, and free of loose materials or contaminants such as water, frost, ice, oil and grease that would interfere with proper adhesion and compromise the performance of the product. Prepare concrete surfaces to achieve a Concrete Surface

Profile CSP 2 to CSP 6 in accordance with the International Concrete Repair Institute (ICRI) Technical Guideline No. 310.2R-2013.

Application to structural concrete surfaces and DensDeck Prime require priming with Vapor Retarder Primer TA or Vapor Retarder Primer BE. See Vapor Retarder Primer TA or Vapor Retarder Primer BE product data sheet for additional information.

APPLICATION

Torch applied products should only be installed by trained personnel. It is imperative that the NRCA safety guidelines, as outlined in their Certified Roofing Torch Applicator Program (CERTA), and good industry practices be followed.

Chalk a line on the deck to align the first sheet. Unroll Ply Sheet TA 87 and allow the sheet to relax. Align the side lap with the chalk line. Back roll the sheet halfway. Begin torching the bottom side of Ply Sheet TA 87. Maintain a majority of the torch flame directly on the roll. As the bitumen begins to soften pull the roll forward with a metal pole. When heated properly there should be a bleed out of approximately ½" (1.3 cm). Back roll the other half of the roll and repeat the process.

MAINTENANCE

Standard maintenance of Sarnafil® or Sikaplan® systems should include inspections of flashings, drains, and termination sealants at least twice a year and after each storm.

AVAILABILITY/WARRANTY

Availability

From Sika Corporation – Roofing Authorized Applicators for use within Sarnafil or Sikaplan systems.

Warranty

Upon successful completion of the installed roof by the Sika Authorized Applicator, Sika Corporation will provide a warranty to the Building Owner via the Sika Authorized Applicator

LIMITATIONS

- Do not install Ply Sheet TA 87 when it is raining, snowing, or on wet/humid surfaces.
- Do not torch apply Ply Sheet TA 87 to combustible substrates or substrates with a combustible backing.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must

read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Sarnafil
100 Dan Road
Canton, MA 02021
Phone: +1 800-451-2504
Fax: +1 781-828-5365
usa.sarnafil.sika.com
webmaster.sarnafil@us.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Ply Sheet TA 87
September 2019, Version 04.01
020945051000000026

PlySheetTA87-en-US-(09-2019)-4-1.pdf

