

## PRODUCT DATA SHEET

# SikaEmaco<sup>®</sup> 440

(formerly MasterEmaco<sup>®</sup> S 440)

LOW DUST, POURABLE, AND PUMPABLE PRE-EXTENDED SELF-CONSOLIDATING REPAIR MORTAR

### PRODUCT DESCRIPTION

SikaEmaco<sup>®</sup> 440 is a low dust one-component, shrinkage-compensated, self-consolidating repair mortar. It is designed for large volume repairs, including structural elements in applications from 1.5" (38 mm) to full depth.

### USES

- Interior and exterior
- Large-volume structural repairs
- Repair or replacement of concrete elements
- Formed horizontal, vertical, and overhead repairs

### Substrates

- Concrete

### CHARACTERISTICS / ADVANTAGES

- The dual expansion system compensates for shrinkage in plastic and hardened states
- Low-dusting for added worker comfort and safety
- High early strength allows early form removal
- Low permeability protects against carbon dioxide and chloride intrusion
- Excellent freeze/thaw resistance for durability in cold, wet environments
- Flowability makes it ideal for placement by pumping or pouring into congested locations
- Self-consolidation minimizes honeycombing without vibration

### PRODUCT INFORMATION

<b>Chemical Base</b>	SikaEmaco <sup>®</sup> 440 is a proprietary blend of cement, graded aggregate, shrinkage-compensating agents, and additives.	
<b>Packaging</b>	55 lb (25 kg) polyethylene-lined bags	
<b>Shelf Life</b>	1 year when properly stored	
<b>Storage Conditions</b>	Store in unopened containers in cool, clean, dry conditions	
<b>Density</b>	Fresh wet density 142lb/ft <sup>3</sup> (2,275kg/m <sup>3</sup> )	(ASTM C 138)

### TECHNICAL INFORMATION

<b>Compressive Strength</b>	2" (51 mm) cubes
-----------------------------	------------------

	1 day	2,500psi (17.2MPa)	(ASTM C 109)
	7 days	5,000psi (34.5MPa)	
	28 days	6,000psi (41.4MPa)	
	3 by 6" (76 by 152 mm) cylinders		
	28 days	5,000 (34.5)	(ASTM C 39)
<b>Flexural Strength</b>	28 days	1,150psi (7.9MPa)	(ASTM C 348)
<b>Splitting tensile strength</b>	28 days	500psi (3.4MPa)	(ASTM C 496)
<b>Shear Strength</b>	Slant shear bond strength at 28 days	3,000psi (20.7MPa)	(ASTM C 882, (modified1))
<b>Shrinkage</b>	28 days	350 $\mu$ strain	(ASTM C 157, (unmodified))
	21 days	611 $\mu$ strain	(ASTM C 157, (modified))
<b>Coefficient of Thermal Expansion</b>	5.5in/in/ $^{\circ}$ F x 10 <sup>-6</sup> (9.9cm/cm/ $^{\circ}$ C x 10 <sup>-6</sup> )		(CRD C 39)
<b>Freeze-Thaw Stability</b>	100% Relative Dynamic Modulus		(ASTM C 666)
<b>Design Considerations</b>	Dust reduction for SikaEmaco <sup>®</sup> 440 vs. control	70%	(DIN55992-2)
	Potential Alkali-Silica Reactivity	<0.10% Aggregate (Innocuous expansion)	(ASTM C 1260)

## APPLICATION INFORMATION

<b>Coverage</b>	0.43 ft <sup>3</sup> (0.012 m <sup>3</sup> ) per 55 lb (25 kg) bag		
<b>Flowability</b>	Slump Flow*	25in (63.5cm)	(ASTM C1611)
	Visual Stability Index	0 (Highly Stable - No Bleeding)	
	J-Ring Slump Flow*	24.5in (62.5cm)	(ASTM C1621)
	Passing Ability	0.5in (1cm) No visible blocking	
	*2.75 qts water / 55 lb bag (Minimum water addition)		

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must

read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

### NOTES ON INSTALLATION

- Minimum ambient, surface, and material temperature is 40 °F (4 °C) and rising.
- Do not mix for longer than 5 minutes.
- The minimum application thickness is 1.5" (38 mm). When the depth is less than 1.5", use SikaEmaco<sup>®</sup> 440 MC.
- Do not mix partial bags.

- Do not use to make overlay repairs where the surface of fresh, wet SikaEmaco® 440 will remain unrestrained during cure.
- Do not vibrate
- Do not add plasticizers, accelerators, retarders, or other additives.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of the product data sheet and SDS are being used.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

## SURFACE PREPARATION

### Concrete

1. Concrete must be structurally sound and fully cured (28 days).
2. Saw cut the perimeter of the area being repaired into a square with a minimum depth of ½" (13 mm).
3. Refer to current ICRI Guideline no. 310.2R for surface prep requirements to permit proper bond.

### Reinforcing Steel

1. Remove all oxidation and scale from the exposed reinforcing steel in accordance with ICRI Technical Guideline No. 310.1R.
2. For additional protection from future corrosion, coat the prepared reinforcing steel with Sikagard® P 8100 AP.

## MIXING

1. Ensure that SikaEmaco® 440 is thoroughly mixed; a forced-action mixer is essential. Mixing in a suitably sized container using an appropriate paddle with a slow-speed (400–500 rpm) heavy-duty drill is acceptable. Do not use free-fall mixers.
2. Measure 2.7 quarts (2.6 L) of potable water and pour 2 quarts into the mixer. With the machine in operation, add 1 full 55 lb (25 kg) bag of SikaEmaco® 440 and mix for 1 minute before adding the rest of the water. Always add powder to the water. The quantities mixed may be scaled up as required.
3. Mix for a further 2–3 minutes to obtain a smooth consistency.
4. When using the drill-and-paddle mixing method, place the complete 2.7 quarts (2.6 L) of water in the mixing drum. With the paddle rotating, add 1 full 55 lb (25 kg) bag of SikaEmaco® 440 and mix for 3 minutes to reach a smooth, even consistency.
5. Depending on the ambient temperatures and the desired consistency, additional water may be added. The total water content should not exceed 2.9 quarts (2.7 L) per 55 lb (25 kg) bag.

## APPLICATION

1. Build forms in accordance with ACI 347R. Keep the unrestrained surface area of the repair to a minimum.
2. Saturate the prepared concrete substrate by filling the prepared formwork with clean water 24 hours before placement.
3. Immediately before the placement of SikaEmaco® 440, completely drain this water and seal the drainage outlets, leaving the substrate saturated surface-dry (SSD) with no ponded water remaining.
4. In jobsite circumstances where the formwork cannot be filled with water to achieve an SSD surface, the prepared concrete substrates must be thoroughly hosed down with clean water to achieve an equal level of saturation. Apply the repair material with sufficient pressure to ensure intimate contact with the substrate.
5. A long open-time bonding agent such as SikaEmaco® P 124 may be used in place of a saturated substrate. In such a case, place the SikaEmaco® 440 before the bonding agent becomes tack-free.
6. Immediately after mixing, pump or pour the SikaEmaco® 440 into the formed area. The material does not require vibrating.
7. The recommended application range of SikaEmaco® 440 is from 40 to 85 °F (4 to 29 °C). Follow ACI 305 and 306 for hot or cold weather guidelines.

## CURING TREATMENT

1. Leave the formwork in place until the compressive strength reaches 2,500 psi (17.2 MPa) or a strength specified by the engineer.
2. Cure with an approved curing compound compliant with ASTM C 309 or preferably ASTM C 1315. If the repair area will receive a coating, wet curing is recommended

## CLEANING OF TOOLS

Clean tools and equipment with clean water immediately after use. Cured material must be removed mechanically.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the

current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)



**Product Data Sheet**

SikaEmaco® 440  
June 2024, Version 01.01  
02030200000002187

SikaEmaco440-en-US-(06-2024)-1-1.pdf

