



PRODUCT DATA SHEET

SCOFIELD® SelectSeal™ Plus

A high-solids, low-odor, self-crosslinking, urethane fortified acrylic sealer designed to protect interior or bare or colored concrete

PRODUCT DESCRIPTION

SCOFIELD® SelectSeal™ Plus is a high-solids, low-odor, self-crosslinking, urethane fortified acrylic sealer designed to protect interior bare or colored concrete.

SCOFIELD® SelectSeal™ Plus utilizes unique proprietary waterborne technology that provides superior wet slip resistance while forming a tough stain and abrasion-resistant gloss finish that is superior to most solvent-based sealers. It can be tinted to deliver a multitude of translucent colored effects, and can be used to create floors compliant to various ANSI, ASTM, NFSI, and UL traction standards.

SCOFIELD Selectseal Plus can be applied by traditional, foam, or microfiber applicators, as well as by conventional, air-assisted, airless, or HVLP spray equipment. It can be applied over a wide range of temperature and humidity conditions without cracking, crazing, frosting, or gumming.

USES

- Ideal for food courts, pools, entry and walkways
- Seals in color of antiquing stamp releases and stains
- Abrasion resistant topcoat over stains and dyes
- As a concrete curing compound to reduce spider cracking and efflorescence
- Prevents dusting of new or aging concrete
- Can be used on cementitious overlays

CHARACTERISTICS / ADVANTAGES

- For interior use only
- High-solids, low odor water-based formulation
- Enhances concrete and chemical stain colors
- Self-Crosslinking resin system delivers superior stain, abrasion, and chemical resistance
- Apply by brush, roller, or spray
- Can be thinned for use as a clear primer
- Will not gum or spider-web in hot conditions

APPROVALS / STANDARDS

SCOFIELD® SelectSeal™ Plus can be used to make floors that exceed the Underwriters Laboratories Safety Standard UL 410, "Slip Resistance of Floor Surface Materials."

Meets the moisture retention requirements of ASTM C309 Standard Specification for Liquid Membrane-Forming Compounds for Curing Concrete.

PRODUCT INFORMATION

Chemical Base	Urethane fortified self-crosslinking acrylic copolymer, 30% solids
Packaging	1-gallon (3.8L) cans or 5-gallon (19L) pails.
Shelf Life	24 months
Storage Conditions	Store at 40°F to 120°F (4°C - 49°C). Do not freeze.

APPLICATION INFORMATION

Coverage	Coverage will depend upon thinning, method of application, surface porosity, and the texture of the substrate. Full strength prime-coat coverage on flat finished concrete is typically 300–400 sq. ft./gal. (7.4–9.8 sq. m/L), and will yield a dry film thickness of 1.3–1.1 mils. Thinned with 1 pint of water per gallon, prime coat coverage is typically 450 sq. ft./gal., and will yield a dry film thickness of 0.85 mils. Porous, broom or textured finishes will require more sealer. As a topcoat or for second coat application, coverage of 600–800 sq. ft./gal. (14.8–19.6 sq. m/L) is typical.
Drying Time	Dry times will depend upon the selected coverage rate, and penetration into the substrate. At 70°F (21°C) and 50 % relative humidity with an application rate of 400 sq. ft. per gallon (10 m ² /L), dry to touch and recoat times of 1–2 hours are expected. Avoid foot-traffic for a minimum of 12 hours, and hard wheel traffic for 72 hours after final application.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- For interior use only
- SCOFIELD® SelectSeal™ Plus is not designed for immersion service, or for use on surfaces subjected to hydrostatic pressure.
- Use only on concrete that is above grade or on ground that is well-drained.
- Do not use on concrete slabs placed on damp ground, or on concrete that will be constantly exposed to moisture.
- Do not apply when air or surface temperatures are below 45 °F (7 °C), or rain, dew, or surface condensation is expected within 4 hours of application.
- Do not allow material to puddle or build-up in cracks or joints during application.
- SCOFIELD® SelectSeal™ Plus may initially turn white, and then dry clear and hard when used on surfaces that have been acid stained or etched and not rinsed well. This whitening may be avoided by rinsing etched surfaces well, and by thinning the prime coat with 1 pint of water per gallon.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

EQUIPMENT

Apply SCOFIELD® Selectseal™ Plus by brush, roller, HVLP sprayer, airless sprayer, or pump-spray/back-roll application.

Spray Applicator Guidelines:

Pump Garden Sprayer	Use conical tip
Airless Sprayer	1500-2500 psi (10-17 MPa) fitted with a fan tip of 0.013-0.015 in. (0.33-0.38 mm)
HVLP Sprayer	5-40 psi (35-275 KPa) 1.3–1.5 mm tip

SURFACE PREPARATION

When used as a Curing Compound

Apply SCOFIELD® Selectseal™ Plus when concrete is walkable and all bleed water has either reabsorbed into the concrete or evaporated.

When used as a Sealer or Dust Proofer

When used on fully cured concrete, surfaces must be dry and clean of all prior sealers, curing compound, oils, or other foreign materials that might prevent penetration or adhesion. If applying directly to cured concrete, maximize adhesion by first creating a Concrete Surface Profile (CSP) of 1, as determined by the International Concrete Repair Institute, (ICRI), Alexandria, VA. Grind, acid etch, power wash, or scrub surfaces with stiff bristle brushes and strong detergents to remove these undesired materials and any loose concrete laitance that may harm adhesion. Always rinse older concrete surfaces and allow them to completely dry prior to application.

If used over solvent-based stain, stain should be allowed to cure a minimum of 12 hours to allow solvents to evaporate.

If used over chemical stain, or acid etched surfaces, the surface must be neutralized and rinsed thoroughly prior to application. Failure to do so can cause SCOFIELD® Selectseal™ Plus to temporarily blush white before drying clear.

MIXING

SCOFIELD® Selectseal™ Plus is iridescent white and will look like a heavy cream. Mix until it is of uniform consistency and appearance prior to use. If tinting, add tint material and mix again until uniform. To increase penetration into acid stained or sandblasted concrete, SCOFIELD® Selectseal™ Plus may be thinned with up to 1 pint of water per gallon of material.

APPLICATION

Mask all areas not to be coated to safeguard against splashes, overspray, and runoff from application. Wear all required safety equipment. Take care not to allow tape adhesive to interfere with surfaces to be coated. Product may appear lighter in color until dry.

Distribute product with a pump garden sprayer fitted with a conical tip, followed by back rolling with a quality 3/8" knap roller. Roll in multiple directions to ensure product penetrates into concrete cracks, joints, and pores. Take care not to create lap marks as they cannot be removed once the product has dried. Dried material will be difficult to remove. Remove overspray immediately with hot water and detergent.

CLEANING OF TOOLS

Clean equipment with warm water and detergent immediately after application.

MAINTENANCE

If used as a concrete curing compound, a second coat of SCOFIELD® SelectSeal™ Plus should be applied after 28 days to maximize stain resistant properties.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT

OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
SCOFIELD® SelectSeal™ Plus
April 2025, Version 03.01
020303110010000085

SCOFIELDSelectSealPlus-en-US-(04-2025)-3-1.pdf

