

Sikadur® Capseal

Description	Rapid cure, non-sag injection port adhesive and surface crack sealer.
Where to Use	Low pressure injection of cracks in structural concrete and masonry.
Advantages	<ul style="list-style-type: none">■ Convenient mix in the nozzle cartridge system.■ Cartridges fit standard caulking guns.
Coverage	Approximately 8 linear ft.
Packaging	300 ml Capseal cartridge.
Cure Mechanism	Free Radical Cure.

Typical Data

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life 18 months in original, unopened containers.

Storage Conditions Store dry at 40°-75°F (5°-24°C). Condition dry at 40°-75°F (5°-24°C).

Temperature	Gel Time (min)	Ready for Injection (min)
41°F	18	145
50°F	10	85
68°F	6	50
77°F	5	40
86°F	4	35

How to Use

Surface Preparation For a successful application, very thorough preparation is a must. The crack to be treated must be dry and free from oil, grease, dust and other contaminants. Any loose material must be blown or brushed clear.

Mixing Open screw cap, cut film to remove metal clip and attach nozzle, extrude a small amount of material until a uniform color is achieved.

Application **For Vertical Cracks (walls, columns, beams)** - The surface of the crack should be sealed with the fast setting Sikadur® Capseal supplied. The Capseal should also be used to affix the injection ports. The distance between the injection ports should be greater than the estimated depth of the crack (typically 1.5 times. If depth is not known, consult technical services).

For Horizontal Cracks (floors, slabs, etc.) - The Sikadur® Capseal and injection ports may not be required as the resin may be introduced into the crack by gravity.

Removal After the resin has been allowed to cure, the injection ports and Capseal should be mechanically removed and any holes or voids should be filled.

Limitations

- Minimum substrate and ambient temperature 40°F (5°C). Maximum substrate temperature 95°F (45°C).
- Minimum age of concrete must be 21-28 days, depending on curing and drying conditions.
- Do not apply over wet, glistening surfaces.
- Not for injection of cracks subjected to osmotic or hydrostatic pressure during application.
- Do not inject cracks greater than 1/4 in (6mm). Consult Sika Technical Services.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikadur are registered trademarks. Printed in Canada.