

**Product Data Sheet**  
Edition 7.2003  
Identification no. H37107  
SikaWrap Hex 107G

# SikaWrap® Hex 107G

Glass fiber fabric for structural strengthening

<b>Description</b>	SikaWrap Hex 107G is a unidirectional E-glass fiber fabric designed for strengthening concrete, timber and masonry. SikaWrap Hex 107G is reinforced in the weft direction with aramid fibers. SikaWrap Hex 107G is field laminated and bonded to the structure using Sikadur 300, Sikadur Hex 300 or Sikadur Hex 306 epoxy to form a glass fiber reinforced polymer (GFRP) used to strengthen structural elements. SikaWrap Hex 107G is pre-qualified for use on California Department of Transportation (Caltrans) projects.
<b>Where to Use</b>	<p><b>Load increases</b></p> <p><b>Seismic strengthening of:</b></p> <ul style="list-style-type: none"> <li>■ Columns</li> <li>■ Masonry walls</li> </ul> <p><b>Damage to structural parts</b></p> <p><b>Temporary strengthening</b></p> <p><b>Change in structural system</b></p> <p><b>Design or construction defects</b></p>
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Approved by ICBO/ICC ER-5558.</li> <li>■ Pre-qualified for use on specific Caltrans projects.</li> <li>■ Used for shear, confinement or flexural strengthening.</li> <li>■ Flexible, can be wrapped around complex shapes.</li> <li>■ Light weight.</li> <li>■ Non-corrosive.</li> <li>■ Acid resistant.</li> <li>■ Low aesthetic impact.</li> <li>■ Economical.</li> </ul>
<b>Possible Applications</b>	<ul style="list-style-type: none"> <li>■ Bridges</li> <li>■ Parking Structures</li> <li>■ Buildings</li> <li>■ Marine Structures</li> <li>■ Civil/Environmental Facilities</li> </ul>
<b>Packaging</b>	Rolls: 50 in. x 150 ft.
<b>How to Use</b>	<p><b>Surface Preparation</b></p> <p>Surface must be clean and sound. It may be dry or damp, but free of standing water and frost. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles, disintegrated materials and other bond inhibiting materials from the surface. Consult Sikadur 300, Sikadur Hex 300/306 and Sikadur 330 technical data sheets for additional information on surface preparation.</p> <p>Existing uneven surfaces must be filled with an appropriate repair mortar. The adhesive strength of the concrete must be verified following surface preparation by random pull-off testing (ACI 503R) at the discretion of the engineer. Minimum tensile strength, 200 psi (1.4 MPa) with concrete substrate failure.</p> <p><b>Surface Levelness/Irregularities:</b> Maximum allowable deviation in 3 ft. (1 m) shall be limited to 1/4" (6 mm) but no greater than 1/8" (3 mm) per foot. Any sharp edges (i.e. fins, form-marks, etc.) must be ground smooth and flush.</p>

## Typical Data

<b>Storage Conditions</b>	Store dry at 40°-95°F (4°-35°C)
<b>Color</b>	White (yellow weft fibers)
<b>Primary Fiber Direction</b>	0° (unidirectional)
<b>Weight per Square Yard</b>	27 oz. (913g/m <sup>2</sup> )
<b>Fiber Properties</b>	
<b>Tensile Strength</b>	3.3 x 10 <sup>5</sup> (2,276 MPa)
<b>Tensile Modulus</b>	10.5 x 10 <sup>6</sup> psi (72,413 MPa)
<b>Elongation</b>	4%
<b>Density</b>	0.092 lbs./in. <sup>3</sup> (2.54 g/cc)



Cured Laminate Properties with Sikadur Hex 300 Epoxy Properties after standard cure followed by standard post cure [70° -75° F (21° -24° C) - 5 days, 48 hours at 140° F (60° C)]

Property	Average Value <sup>1</sup>		Average Value <sup>2</sup>		ASTM Test Method
	US Units psi	SI Units MPa	US Units psi	SI Units MPa	
Tensile Strength*	94,000	648	86,600	597	D-3039
Tensile Modulus*	3,794,100	26,141	3,567,500	24,580	D-3039
Tensile % Elongation*	2.57	2.57	2.33	2.33	D-3039
140F - Tensile Strength	87,500	603	83,300	574	D-3039
140F - Tensile Modulus	3,661,900	25,230	3,496,900	24,094	D-3039
140F - % Elongation	2.55	2.55	2.43	2.43	D-3039
Compressive Strength	83,000	572	71,800	495	D-695
Compressive Modulus	4,281,400	29,499	3,224,600	22,217	D-695
90 deg Tensile Strength	7,200	50	4,600	32	D-3039
90 deg Tensile Modulus	1,245,000	8,578	977,400	6,734	D-3039
90 deg % Tensile Elongation	1.20	1.20	1.08	1.08	D-3039
Shear Strength +/-45 in. Plane	6,500	45	6,300	43	D-3518
Shear Modulus +/-45 in. Plane	345,400	2,380	160,800	1,108	D-3518
Ply Thickness (inch/mm)	0.04	1.016	---	---	---

\* 24 sample coupons per test series; all other values based on 6 coupon test series

<sup>1</sup> Average value of test series

<sup>2</sup> Average value minus 2 standard deviations

Cured Laminate Properties with Sikadur Hex 300 Epoxy Properties after standard cure followed by standard post cure [70° -75° F (21° -24° C) - 5 days, 48 hours at 140° F (60° C)]

Property	Average Value <sup>1</sup>		Average Value <sup>2</sup>		ASTM Test Method
	US Units psi	SI Units MPa	US Units psi	SI Units MPa	
Tensile Strength*	87,600	604	79,000	544	D-3039
Tensile Modulus*	3,706,900	25,541	3,476,900	23,956	D-3039
Tensile % Elongation*	2.43	2.43	2.18	2.18	D-3039
140F - Tensile Strength	72,700	501	67,100	462	D-3039
140F - Tensile Modulus	3,327,700	22,928	3,134,500	21,597	D-3039
140F - % Elongation	2.34	2.34	2.12	2.12	D-3039
Compressive Strength	72,000	496	59,400	409	D-695
Compressive Modulus	4,075,300	28,079	3,576,100	24,639	D-695
90 deg Tensile Strength	6,800	47	3,400	23	D-3039
90 deg Tensile Modulus	1,045,400	7,203	985,200	6,788	D-3039
90 deg % Tensile Elongation	0.78	0.78	0.60	0.60	D-3039
Shear Strength +/-45 in. Plane	9,300	64	8,500	59	D-3518
Shear Modulus +/-45 in. Plane	334,400	2,304	316,600	2,181	D-3518
Ply Thickness (inch/mm)	0.04	1.016	---	---	---

\* 24 sample coupons per test series; all other values based on 6 coupon test series

<sup>1</sup> Average value of test series

<sup>2</sup> Average value minus 2 standard deviations

**Preparation Work: Concrete** - Blast clean, shotblast or use other approved mechanical means to provide an open roughened texture. Corners of structural elements to be wrapped must be rounded to a minimum radius of 1/2" (13 mm).

In certain applications and at the engineer's discretion, the intimate contact between the substrate and the fabric may be determined to be non-critical. In these cases, a thorough cleaning of the substrate using low pressure sand or water blasting is sufficient.

<b>Mixing</b>	Consult either Sikadur 300 or Sikadur Hex 300/306 technical data sheets for information on epoxy resins.
<b>Application</b>	Prior to placing the fabric, the concrete surface is sealed using either Sikadur 300 or Sikadur Hex 300 epoxy. Material may be applied by spray, brush or roller. SikaWrap Hex 107G can be impregnated using either the Sikadur 300, Sikadur Hex 300 or Sikadur Hex 306 epoxy. For best results on larger projects, the impregnation process should be accomplished using a mechanically driven fabric saturator. In special cases where the size of the project does not justify the use of a saturator, the fabric may be saturated by hand using a roller prior to placement. In either case, installation of this system should be performed only by a specially trained, approved contractor. For overhead or vertical applications, prime concrete with Sikadur 30 or Sikadur 330 to improve tack. Saturate fabric with Sikadur 300, Sikadur Hex 300 or Sikadur Hex 306.
<b>Cutting SikaWrap</b>	Fabric can be cut to appropriate length by using a commercial quality heavy duty scissor. Since dull or worn cutting implements can damage, weaken or fray the fiber their use should be avoided. Consult MSDS for proper handling procedures.
<b>Limitations</b>	<ul style="list-style-type: none"> <li>Design calculations must be made and certified by an independent licensed professional engineer.</li> <li>System is a vapor barrier. Concrete should not be encapsulated in areas of freeze/thaw.</li> </ul>
<b>Caution</b>	SikaWrap fabric is non-reactive. However, caution must be used when handling since a fine "glass dust" may be present on the surface. Gloves must therefore be worn to protect against skin irritation. Caution must also be used when cutting SikaWrap fabric to protect against airborne glass dust generated by the cutting procedure. Use of an appropriate, properly fitted NIOSH approved respirator is recommended.

**KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY**  
All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at [www.sikausa.com](http://www.sikausa.com) or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at [www.sikausa.com](http://www.sikausa.com) or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

**LIMITED WARRANTY:** Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEVABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at [www.sikausa.com](http://www.sikausa.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Sika, Sikadur and SikaWrap are registered trademarks. Made in USA. Printed in Canada.

