

## Sika® Epoxy 7300

### General Purpose Epoxy Adhesive Binder Non-Sag Injectable Gel

<b>Description</b>	Sika® Epoxy 7300 is a multi-purpose, two component, solvent-free, moisture insensitive structural epoxy adhesive. It meets ASTM-C-881. Types I and II, Grade 3, Classes B and C for Epoxy Resin Adhesives.
<b>Where to Use</b>	<ul style="list-style-type: none"> <li>■ Structural bonding of concrete, masonry, metals, wood, etc., to maximum glue line of 1/2 inch thick</li> <li>■ Grouting bolts, dowels, pins, vertical and overhead, etc.</li> <li>■ Seals, cracks and around injection ports prior to pressure-injection grouting</li> <li>■ Interior, exterior, vertical and overhead repair of concrete as an epoxy mortar bind</li> </ul>
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Insensitive to moisture before, during and after cure</li> <li>■ High-modulus, high-strength, structural gel adhesive</li> <li>■ Excellent adhesion to concrete, masonry, metals, woods and most structural materials</li> <li>■ Gel consistency ideal for vertical and overhead applications</li> <li>■ Fast-setting and strength-producing adhesive</li> <li>■ Easy to mix 1:1 ratio between components</li> </ul>
<b>Typical Data</b>	
<b>Coverage</b>	<p><b>Bonding Adhesive</b> - 1 gallon yields 231 cu. in. of epoxy gel adhesive</p> <p><b>Epoxy Mortar</b> - 1 gallon of adhesive, when mixed with 1 gallon by loose volume of oven-dried aggregate, yields 346 cu. in. of epoxy mortar</p>
<b>Packaging</b>	<p>1 gallon</p> <p>2 gallons</p>
<b>Cure Mechanism</b>	Once the epoxy is placed it should not be disturbed during the curing process. Cure time depends on air and surface temperature as well as mass of epoxy. Based on environmental conditions, a full cure should take approximately 1 day.

#### Physical Properties

ASTM Test	Results
D-695 Compressive Strength	11,236 psi
D-732 Shear Strength	3,550 psi
D-638 Tensile Strength	2,940 psi
D-790 Flexural Strength	5,582 psi
C-882 Bond Strength	2,460 psi
D-570 Absorption	0.63%
C-883 Shrinkage	Complies
C-884 Thermal Compatibility	Complies
Consistency	non-sag gel, approximately 85,000 cps
Pot life	Above 30 minutes at approximately 70°F
Appearance	Component A = White Component B = Grey

\*Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800-933-7452. NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTION FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

# Waterproofing

<b>Chemical Resistance</b>	Not intended for use in chemical resistant applications.
<b>How to Use</b>	
<b>Surface Prep</b>	Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles and disintegrated materials. Preparation Work Concrete - sandblast or use other approved mechanical means Steel - Sandblast to white metal finish
<b>Mixing</b>	Pre-mix each component thoroughly. Place 1 part by volume of component A and 1 part by volume of component B into a clean pail. Mix thoroughly for 3 minutes with low-speed drill (400-600 rpm) until uniformly blended. Mix only the quantity that can be used within its pot life. To prepare an epoxy mortar, slowly add 1 part by loose volume of an oven-dried aggregate to 1 part of the mixed Sika® Epoxy 7300 and mix until uniform in consistency and color.
<b>Application</b>	<b>As a structural adhesive</b> - Apply the neat Sika® Epoxy 7300 to the mating or non-mating prepared substrates. Work into the substrate for positive adhesion. Secure the bonded unit firmly into place until the adhesion has cured. Glue line should not exceed 1/8 inch thick. <b>To seal cracks for injection grouting</b> - Place the neat mixed material over the cracks to be pressure injected and around each injection port. Allow sufficient time to set before pressure injecting. <b>For interior and overhead patching</b> - Place the prepared mortar in void, working the material into the prepared substrate, filling the cavity. Strike off level. Lifts should not exceed 1 1/2 inch.
<b>Limitations</b>	<ul style="list-style-type: none"><li>■ Minimum surface temperature 40°F</li><li>■ Do not thin. Solvents will prevent proper cure</li><li>■ Use oven-dried aggregate only</li><li>■ Maximum epoxy mortar thickness is 1 1/2 inch per lift</li><li>■ Material is vapor barrier after cure</li><li>■ Minimum age of concrete must be 21-28 days, depending on curing and drying conditions prior to mortar applications</li><li>■ Porous substrates must be tested for moisture-vapor transmission prior to mortar applications</li><li>■ Not for sealing cracks under hydrostatic pressure</li><li>■ Do not expose stored product to cold or freezing temperature (below 35°F, 2°C) for any length of time.</li></ul>
<b>Shelf Life</b>	2 years in original unopened container.
<b>Storage</b>	Store at 40°- 95°F. Condition material to 65°-85°F before using.
<b>Conditioning</b>	Condition materials to 65°-85°F before using.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY • FOR PROFESSIONAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at <http://usa.sika.com/> or by calling 800-933-7452.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

**Sika Greenstreak Sales Office**  
3400 Tree Court Industrial Blvd.  
St. Louis, MO 63122  
Tel: (636) 225-9400  
Fax: (636) 225-2049  
[usa.sika.com](http://usa.sika.com)

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: (201) 933-8800  
Fax: (201) 933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Canada Inc.**  
601, Delmar Avenue  
Pointe-Claire, QC H9R 4A9  
Phone: (514) 697-2610  
Fax: (514) 697-3087  
[can.sika.com](http://can.sika.com)

The Sika logo consists of the word "Sika" in a bold, yellow, sans-serif font, set against a red triangular background. A registered trademark symbol (®) is located to the right of the word.

**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800-933-7452. NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTION FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**