

## PRODUCT DATA SHEET

# Sikacrete®-752 F 3D

### 1-PART MICRO-CONCRETE FOR 3D PRINTING

#### PRODUCT DESCRIPTION

Sikacrete®-752 F 3D is a 1-Part Micro-Concrete for use with 3D robot or gantry printers. Suitable for hot and tropical climate condition use.

#### USES

For concrete printing of 3D objects and components of the following:

- Buildings
- Civil engineering structures
- Molds and forms
- Art, craft, and visual displays
- Interior and exterior use

#### CHARACTERISTICS / ADVANTAGES

##### Fast absorbing

- Suitable for continuous and static mixers

##### 1-part

- Mix with water
- Adjustable consistency

##### Low viscosity

- For easy pumping

##### Thixotropic consistency

- Maintains shape after extrusion
- Good buildability

##### Fast setting

- For building up layers
- Print line stability and accuracy
- Printing at angles
- Moving objects sooner

##### Low shrinkage

- Good crack resistance

##### Optimised grading

- For smooth appearance
- Reduced equipment wear
- Good durability

##### Reduced Permeability / Low water penetration

#### PRODUCT INFORMATION

<b>Chemical Base</b>	Modified cement based Micro-Concrete with selected aggregates and additives
<b>Packaging</b>	<ul style="list-style-type: none"> <li>▪ 55 lb bag</li> <li>▪ 2000 lb Super Sack</li> </ul>
<b>Shelf Life</b>	9 months from date of production

<b>Storage Conditions</b>	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions. For consistent printing quality it is recommended to store the material at temperatures between 41 °F - 86 °F (5 °C - 30 °C). Always refer to packaging.
---------------------------	---

<b>Appearance / Color</b>	White powder
---------------------------	--------------

<b>Maximum Grain Size</b>	Approx. 0.08 in (2 mm)
---------------------------	------------------------

## TECHNICAL INFORMATION

<b>Compressive Strength</b>		<b>ASTM C109</b>
	<b>1 day</b>	2900 psi (20 MPa)
	<b>7 day</b>	5800 psi (40 MPa)
	<b>28 day</b>	7250 psi (50 MPa)

\*Tested at 74 °F (23 °C) with Water : Powder ratio of 0.16

<b>Flexural Strength</b>		<b>ASTM C348</b>
	<b>28 day</b>	1200 psi (8.2 MPa)

\*Tested at 74 °F (23 °C) with Water : Powder ratio of 0.16

<b>Service Temperature</b>	Maximum 212 °F (100 °C)
----------------------------	-------------------------

<b>Water Penetration under Pressure</b>	Approx. 0.8 in (20 mm)
	*Tested at 74 °F (23 °C) with Water : Powder ratio of 0.16

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	15% – 17% of water by weight of powder
---------------------	--

<b>Fresh mortar density</b>	Approx. 137 lb/ft <sup>3</sup> (2.20 kg/L)
-----------------------------	--

<b>Coverage</b>	Approx. 3.20 US gal per 55 lb bag (12.1 L per 25 kg bag)
	*This figure is theoretical and does not allow for any lost material during the mixing or pumping process, additional material due to surface porosity, surface profile, variations in level or wastage etc.

<b>Layer Thickness</b>	Approx. 0.4 – 2.0 in (10 – 50 mm)
	Layer thicknesses are subject to the equipment and printing procedure and it is recommended to make a test to check suitability

<b>Ambient Air Temperature</b>	<b>Minimum</b>	41 °F (5 °C)
	<b>Maximum</b>	86 °F (30 °C)

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## USES

- 3D concrete printing is a manufacturing process using mixing, pumping and robotic placement to apply the printed concrete. All these factors play a significant role in achieving optimal results of the finished concrete component and therefore pre-trials and tests must be carried out before final manufacturing of the finished components.

- In the event of blockages, rinse equipment and pump lines immediately with clean water.
- Sika is not responsible for deviated performances due to external circumstances beyond our control.
- Continuously monitor the pot life of the mixed material.
- Do not allow mixed material to stand in warm temperatures.
- Keep pump lines wetted and cool.
- Use warm water at low temperatures and cold water at high temperatures to maintain application performance.
- Condensation due to certain curing methods and curing agents may cause some discoloration to the surface appearance.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

### MIXING

#### Static Mixers (Small volume quantities)

1. Mix with an electric single or double paddle mixer (<500 rpm) or using a forced action mixer capable of mixing 2 to 3 bags at a time.
2. Add the recommended amount of clean water in a suitable mixing container.
3. Stir slowly, add the powder to the water and mix thoroughly for a minimum of 3 minutes. Check the corners of the mixer for no dry powder.
4. Add more water during the mixing time if necessary to the maximum specified amount to achieve a smooth consistent homogeneous mix.
5. Stir gently if required.

#### Continuous Mixer (High volume quantities)

The mixing ratio shall be determined using a pan test heating method or microwave technique (according to Austrian Standard) to determine the equivalent flowrate/m<sup>3</sup> on the equipment.  
Contact Sika Technical Services for additional information.

### APPLICATION

Pumping and printing is usually a continuous process. The application specification of the extrusion and printing speed must be optimized between the mixer, pump, pump line length, and printer head.

### CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

#### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
usa.sika.com



#### Product Data Sheet

Sikacrete®-752 F 3D  
October 2023, Version 01.02  
021404090100000013

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sikacrete-752F3D-en-US-(10-2023)-1-2.pdf

