

## PRODUCT DATA SHEET

# Sikaflex®-950

Two component STP adhesive sealant

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Properties	Sikaflex®-950 A	Sikaflex®-950 B
<b>Chemical base</b>	2-component silane terminated polymer (STP)	
<b>Color (CQP001-1)</b>	White	Grey
	mixed	Grey
<b>Density (uncured)</b>	1.3 kg/l	1.6 kg/l
	mixed, calculated	1.5 kg/l
<b>Mixing ratio</b>	A:B by volume	1:1
	A:B by weight	1:1.2
<b>Non-sag properties (CQP061-1)</b>	Fair	
<b>Application temperature</b>	5 – 40 °C (41 – 104 °F)	
<b>Open time (CQP526-1)</b>	30 minutes <sup>A</sup>	
<b>Curing speed (CQP046-1)</b>	See table 1	
<b>Shore A hardness (CQP023-1 / ISO 48-4)</b>	35	
<b>Tensile strength (CQP036-1 / ISO 527)</b>	2.0 MPa	
<b>Elongation at break (CQP036-1 / ISO 527)</b>	500 %	
<b>Tensile lap-shear strength (CQP046-1 / ISO 4587)</b>	1.2 MPa	
<b>Service temperature (CQP513-1)</b>	-50 °C – 80 °C (-58 – 176 °F)	
<b>Shelf life (CQP016-1)</b>	12 months <sup>B</sup>	
<b>Mixer</b>	Drums	Statomix® MS 13-18-G

CQP = Corporate Quality Procedure

<sup>A)</sup> 23 °C (73 °F) / 50 % r. h.<sup>B)</sup> stored below 25 °C (77 °F)
**DESCRIPTION**

Sikaflex®-950 is a 2-component Silane Terminated Polymer (STP) adhesive sealant which cures by chemical reaction of the two components. It is well suited for bonding larger surfaces and where pumping over long distances is required.

**PRODUCT BENEFITS**

- Excellent pumpability
- Bonds well to a wide variety of substrates without the need for special pre-treatment
- Meets highest EHS standards
- Low assembly forces yet good non-sag properties
- Very low emission
- Isocyanate, solvent, PVC and phthalate free
- Meets EC1+ classification

**AREAS OF APPLICATION**

Sikaflex®-950 is suitable for bonding large components due to its good compressibility and since it is pumpable over long distances. Suitable substrate materials include metals, particularly aluminum (incl. anodized), steel (incl. phosphated, chromated, zinc plated), metal primers and paint coatings (2-component systems), XPS/EPS, ceramic materials, composites and plastics.

Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-950 on materials prone to stress cracking.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

**PRODUCT DATA SHEET**

Sikaflex®-950

Version 04.01 (02 - 2025), en\_US  
012301219500001000

## CURE MECHANISM

The curing of Sikaflex®-950 takes place by chemical reaction of the two components. Information regarding strength build-up can be seen in the table below.

Time [h]	Strength [MPa]
2	0.2
4	0.4
6	0.6

Table 1: Lap shear strength (CQP 046-1) at 23 °C / 50 % r.h.

## CHEMICAL RESISTANCE

Sikaflex®-950 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

### Application

Sikaflex®-950 need to be processed with an adequate dispensing system. The mixer type needs to be respected (see table Typical Product Data). Sikaflex®-950 can be applied between 5 °C and 40 °C (41 °F and 104 °F) but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between 15 °C and 25 °C (59 °F and 77 °F).

The open time is significantly shorter in hot and humid climate. The parts must always be joint within the open time.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Removal

Uncured Sikaflex®-950 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes or a suitable industrial hand cleaner and water. Do not use solvents on skin.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

## PACKAGING INFORMATION

Sikaflex®-950 A

Drum	195 l
------	-------

Sikaflex®-950 B

Drum	195 l
------	-------

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by contacting SIKA's Technical Service Department via email at [tsmh@us.sika.com](mailto:tsmh@us.sika.com). Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling +1 800-933-7452.

## PRODUCT DATA SHEET

Sikaflex®-950  
Version 04.01 (02 - 2025), en\_US  
012301219500001000

**Sika Corporation**  
30800 Stephenson Highway  
Madison Heights, MI 48071  
U.S.A.  
Telephone: +1 248-577-0020  
Email: [tsmh@us.sika.com](mailto:tsmh@us.sika.com)  
[www.sikausa.com](http://www.sikausa.com)

