

Sika Fastwall® 100 with Sika Thoroseal® -581 Wall System - Section 09 24 23

Direct applied cement stucco system for concrete and CMU featuring SikaWall Fastwall Stucco Base and Sika Thoroseal-581 waterproof cement-based coating.

INTRODUCTION

This specification has been assembled to enable the design professional to select or delete sections to suit the project requirements and is intended to be used in conjunction with Sika typical details, product bulletins, technical bulletins, etc.

DESIGN RESPONSIBILITY

It is the responsibility of both the specifier and the purchaser to determine if a product is suitable for its intended use. The designer selected by the purchaser shall be responsible for all decisions pertaining to design, detail, structural capability, attachment details, shop drawings and the like. Sika Corporation US (herein referred to as "Sika") has prepared guidelines in the form of specifications, typical application details, and product bulletins to facilitate the design process only. Sika is not liable for any errors or omissions in design, detail, structural capability, attachment details, shop drawings or the like, whether based upon the information provided by Sika or otherwise, or for any changes which the purchasers, specifiers, designers or their appointed representatives may make to Sika published comments.

Designing and Detailing a Sika Fastwall 100 with Sika Thoroseal-581 Wall System

General: The system shall be installed in strict accordance with current recommended published details and product specifications from the system's manufacturer.

A. Wind Load:

1. Maximum deflection not to exceed L/360 under positive or negative design loads.
2. Design for wind load in conformance with local code requirements.

B. Substrate Systems:

1. Acceptable substrates are poured concrete (precast, cast-in-place, etc) and unit masonry.
2. The substrate systems shall be engineered with regard to structural performance by others.

C. Moisture Control:

1. Flashing shall be provided per project design detailing and as required by local code.
2. The SIKA THOROSEAL-581 must be installed over the substrate according to manufacturer's specifications and applicable building code requirements.
3. Air Leakage Prevention: provide continuity of air barrier system at foundation, roof, windows, doors and other penetrations through the system with connecting and compatible air barrier components to minimize condensation and leakage caused by air movement.

D. Color Selection: The use of dark colors over EPS insulation trim shapes must be considered in relation to wall surface temperature as a function of local climate conditions. Select Finish Coat color with a light reflectance value (LRV) of 20% or higher. The use of dark colors (LRV less than 20%) is not recommended with trim shapes that incorporate expanded polystyrene (EPS). EPS has a sustained service temperature limitation of approximately 160°F (71°C).

E. Grade Condition: Stucco is not intended for use below grade or on surfaces subject to continuous or intermittent immersion in water or hydrostatic pressure. Ensure a minimum 4" (101.6mm) clearance above grade or as required by code, a minimum 2" (50.8mm) clearance above finished grade (sidewalk/concrete flatwork).

F. Trim, Projecting Architectural Features

- G. NOTE TO SPECIFIER:** Installation of the Sika Fastwall 100 with Sika Thoroseal-581 system with trim shapes that incorporate expanded polystyrene (EPS) outside the slope guidelines referenced in this

Sika Fastwall 100 with Sika Thoroseal-581 System

specification may still qualify for a standard warranty; however, increased maintenance and premature deterioration of the trim shapes that incorporate expanded polystyrene (EPS) shall be expected and any deleterious effects caused by the lack of slope will not be the responsibility of Sika. The design professional has the option to build according to his/her project needs. The design professional must also consider geography, climate, building orientation, wall orientation and adjacent building components when designing with trim shapes that incorporate expanded polystyrene (EPS). The slope guidelines referenced below are provided to offer assistance to the owner and/or design professional. Final design of any building is the responsibility of the design professional.

1. Minimum slope for all projections shall be 1:2 (27°) with a maximum length of 12" (30.5 cm) [e.g. 6" in 12" (15 cm in 30.5cm)]. Increase slope for northern climates to prevent accumulation of ice/snow on the surface.
2. The Sika Fastwall 100 with Sika Thoroseal-581 system was designed and tested to be applied to vertical surfaces. As the slope of the wall system application decreases, the chance for premature deterioration of any wall system increases.
3. Low sloping conditions are subject to more extreme heat. Low sloped areas are known to produce an increase in wall surface temperature which can lead to accelerated weathering of the low sloped surface.

H. System Joints

1. Expansion joints in the system are required at building expansion joints, at prefabricated panel joints, where substrates change and where structural movement is anticipated. Detail specific locations in construction drawings.
 2. The spacing of control joints is less critical than in framed walls. Additional joints may be required to create a stop/start point where long runs cannot be completed in the course of a typical workday. Install expanded wing casing beads at all penetrations and terminations. Regular plaster accessories may be used provided they are striped with lath. Foundation weep screeds are not required in direct applied systems. Detail specific locations in construction drawings.
 3. It is the sole responsibility of the project design team, including the architect, engineer, etc., to ultimately determine specific expansion and control joint placement, width and design.
 4. Sealant joints are required at all penetrations through the Sika Fastwall 100 with Sika Thoroseal-581 system (windows, doors, lighting fixtures, electrical outlets, hose bibs, dryer vents, etc.).
 5. For a list of acceptable sealants refer to *Acceptable Sealants for use with Sika EIFS and Stucco Systems* technical bulletin.
- I. **Decks:** Wood decks must be properly flashed prior to system application. The Sika Fastwall 100 with Sika Thoroseal-581 wall system must be terminated a minimum of 2" (50mm) above all decks, patios, sidewalks, etc.

J. Coordination with Other Trades:

1. Evaluate adjacent materials such as windows, doors, etc. for conformance to manufacturer's details. Adjacent trades shall provide scaled shop drawings for review.
2. Air Seals at any joints/gaps between adjoining components (penetrations, etc.) are of primary importance to maintain continuity of an air barrier system and must be considered by the design professional in the overall wall assembly design. Install an air seal between the primary air/water-resistive barrier and other wall components (penetrations, etc.) in order to maintain continuity of an air barrier system.
3. Install copings and sealant immediately after installation of the Sika Fastwall 100 with Sika Thoroseal-581 system and when SikaWall coatings are completely dry.

TECHNICAL INFORMATION

Consult Sika Facades' Technical Services Department for specific recommendations concerning all other applications. Consult the Sika website, usa.sika.com, for additional information about products, systems and for updated literature.

Sika Fastwall 100 with Sika Thoroseal-581 System

PART 1 GENERAL

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized.

1.01 SECTION INCLUDES

- A. Refer to all project drawings and other sections of this specification to determine the type and extent of work therein affecting the work of this section, whether or not such work is specifically mentioned herein.
- B. System Description: Composite wall system consisting of SIKA THOROSEAL-581 waterproofing, SIKAWALL FASTWALL STUCCO BASE, and SikaWall finish coat.
- C. Sika products are listed in this specification to establish a standard of quality. Any substitutions to this specification shall be submitted to and receive approval from the Architect at least 10 days before bidding. Proof of equality shall be borne by the submitter.
- D. The system type shall be Sika Fastwall 100 with Sika Thoroseal-581 system as manufactured by Sika Corporation US, Lyndhurst, NJ.

1.02 RELATED SECTIONS

- A. Section 03 00 00 Concrete substrate
- B. Section 04 00 00 Masonry substrate
- C. Section 07 27 00 Air barriers
- D. Section 07 62 00 Sheet Metal Flashing and Trim
- E. Section 07 65 00 Flexible flashing
- F. Section 07 90 00 Joint protection
- G. Section 08 00 00 Openings

1.03 REFERENCES

- A. ASTM C150 Standard Specification for Portland Cement
- B. ASTM C926 Standard Specification for Application of Portland Cement-Based Plaster
- C. ASTM D1784 Standard Specification for Rigid Poly (Vinyl Chloride) (PVC) Compounds and Chlorinated Poly (Vinyl Chloride) (PVC) Compounds
- D. ICC-ES AC11 ICC-ES Acceptance Criteria Cementitious Exterior Wall Coatings
- E. ICC-ES ESR-2564 ICC-ES Evaluation Services Report (SIKAWALL FASTWALL STUCCO BASE SANDED / STUCCO BASE CONCENTRATE).

1.04 SUBMITTALS

- A. Submit under provisions of Section [01 33 00]
- B. Product Data: Provide data on Sika Fastwall 100 with Sika Thoroseal-581 wall system materials, product characteristics, performance criteria, limitations and durability.
- C. Code Compliance: Provide manufacturer's applicable code compliance report.
- D. Samples: Submit [\[two\]](#) [\[x \]](#) [\[millimeter\]](#) [\[inch\]](#) size samples of Sika Fastwall 100 with Sika Thoroseal-581 wall system illustrating SikaWall finish coat color and texture range.
- E. Certificate: System manufacturer's approval of applicator.
- F. Sealant: Sealant manufacturer's certificate of compliance with ASTM C920.
- G. System manufacturer's current specifications, typical details, system design guide and related product literature which indicate preparation required, storage, installation techniques, jointing requirements and finishing techniques.

1.05 QUALITY ASSURANCE

- A. Manufacturer: More than 10 years in the cement plaster stucco industry, with more than 1000 completed cement plaster stucco projects.
- B. Applicator: Approved by Sika in performing work of this section.
- C. Regulatory Requirements: Conform to applicable code requirements for cement plaster stucco.
- D. Field Samples
 - 1. Provide under provisions of Section [01 43 36] [01 43 39].
 - 2. Construct one field sample panel for each color and texture, [\[x \]](#) [\[meters\]](#) [\[feet\]](#) in size of system materials

Sika Fastwall 100 with Sika Thoroseal-581 System

illustrating method of attachment, surface finish color and texture.

3. Prepare each sample panel using the same tools and techniques to be used for the actual application.
4. Locate sample panel where directed.
5. Accepted sample panel [\[may\]](#) [\[may not\]](#) remain as part of the work.
6. Field samples shall be comprised of all wall assembly components including substrate, SIKATHOROSEAL-581, plaster trim accessories, SIKAWALL FASTWALL STUCCO BASE, SIKAWALL-10 STUCCO PRIME (if specified), SikaWall finish coat and typical sealant/flashing conditions.

E. Testing:

1. Sika Fastwall 100 with Sika Thoroseal-581 Wall System and Component Performance:

SIKAWALL FASTWALL STUCCO BASE:

TEST	METHOD	CRITERIA	RESULTS
Accelerated Weathering	ASTM G153	2000 Hours	No deleterious effect
Freeze-Thaw Resistance	ICC AC 11	10 cycles	Pass
Transverse Wind Load Resistance	ASTM E330	Meet Design Loads	Refer to ICC-ES ESR-2564
Fire Resistance	ASTM E119	One hour fire	Refer to ICC-ES ESR-2564
Drainage	ICC AC 11	90%	Refer to ICC-ES ESR-2564

SIKA THOROSEAL-581:

PROPERTY	RESULTS	TEST METHOD
Initial Set, min at 70 °F (21 °C), 50% rh	10	Lab Method
Final Set, at 70 °F (21 °C), 50% rh	90	Lab Method
Density, (cured), lbs./ft ³ (kg/m ³)	129 (2,080)	Lab Method
Positive resistance to hydrostatic pressure, hrs., at 200 psi (1.4 MPa), 461 head ft, air cured at 70 °F (21 °C), 50% rh	752 No leakage, no softening	CRD C 48, modified
Negative resistance to hydrostatic pressure, hrs., at 200 psi (1.4 MPa), 461 head ft, air cured at 70 °F (21 °C), 50% rh	664 Limit Dampness	CRD C 48, modified
Water absorption, %, boiling water submersion at 24 hours	3.6	ASTM C 67 (Section 7.3)
Compressive strength, psi (MPa)		ASTM C 109
7 days	4,200 (29)	
28 days	6,030 (42)	
Flexural strength, psi (MPa)		ASTM C 348
7 days	360 (2.5)	
28 days	1,027 (7)	
Tensile strength, psi (MPa)		ASTM C 190
7 days	250 (2)	
28 days	440 (3)	
Artificial weathering, hrs.		
Xenon Arc	5,000 = No failure	ASTM G 26
Carbon Arc	500 = No failure	ASTM G 23
Adhesion strength, psi (MPa)	418 (2.9)	Test by tensile bond
Artificial weathering, 500 hours	No cracking, loss of adhesion, checking, or other defect	Atlas Type DMC weatherometer
Freeze/thaw resistance, 200 cycles	No change	ASTM C 666 (Procedure B)
Salt spray resistance, 300 hours	No defect	ASTM B 117
Carbon Dioxide (CO ₂), in (mm)	1/16 (1.6) Equivalent to 3/4" (19 mm) new concrete	Lab Method Diffusion
Permeance, perms	12 (0.10698) 8 x 10 ³ resistance	ASTM E 96 (water-vapor transmission) Swedish standard SS-02-15-82
Wind-driven rain, hrs	8 = excellent	Fed. Spec. TT-P-0035 (Para 4.4.7)
Coefficient of thermal expansion, in/in/°F (mm/mm/°C), at 28 days	6.99 x 10 ⁻⁶ (5 x 10 ⁻⁷)	ASTM C 531
Impact strength (Gardener impact tester)	No chipping	Fed. Spec. TT-P-0035 (Cement paints para. 3.4.8)
Hardness, (Barber Coleman Impressor) Requirement min = 30, max = 60		Fed. Spec. TT-P-0035 (para 4.4.9)
7 days		
14 day	35	
21 days	47	
	52	
Abrasion resistance, 3,000 L sand	Passed	Fed. Spec. TT-P-141B

Sika Fastwall 100 with Sika Thoroseal-581 System

Standard Reflectance		
Gray Thoroseal-581	64.2	ASTM D 2244 using Hunterlab D-25 meter
White Thoroseal-581	88.1	
Fungus resistance, at 21 days	No growth; meets all requirements	Fed. Spec. TT-P-29B
Surface burning characteristics		ASTM E 84
Flame Spread	0	
Smoke developed	5	
Fire Propagation	Index = 1.5	BS476: Part 6:1981
Flame spread	Class 1	BS476: Part 7:1971

Acrylic Finish:

TEST	METHOD	CRITERIA	RESULTS
Accelerated Weathering	ASTM G153 (ASTM G 23) ASTM G154	No deleterious effects at 2000 hours when viewed under 5x magnification	2000 Hours: no deleterious effect
Freeze/Thaw Resistance	ASTM E2485	No deleterious effects at 10 cycles when viewed under 5x magnification	60 cycles: no deleterious effect
Fungus Resistance	MIL STD 810B	No Requirement	28 days: no growth
Mildew Resistance	ASTM D3273	No growth supported during 28 day exposure period	Pass
Moisture Resistance	ASTM D2247	No deleterious effects at 14 day exposure	Pass
Salt Fog Resistance	ASTM B117	No deleterious effects at 300 hours	500 hours: no deterioration

SIKAWALL-6200 MAXLASTIC FINISH:

TEST	METHOD	CRITERIA	RESULTS
Elongation	ASTM D 412 (modified*)	Report Value	> 300%
Surface Burning	ASTM E84	Report Value	<25 Flame Spread <450 Smoke Developed
Accelerated Weathering	ASTM G 155 Cycle 1	No deleterious effects after 2000 hrs.	Pass
Water Vapor Transmission	ASRM E 96 B	Report Value	> 10 perms
Flexibility	ASTM D 522	Report Value	No cracking ½" mandrel
Wind Driven Rain Resistance	ASTM D 6904	Resists pressure equivalent to a 98-mph wind velocity without exhibiting water leaks or weight gain	Pass
Adhesion	ASTM D 4541	Min. 15.9 psi (110 kPa) or substrate failure	> 125 psi (862 kPa)

1.06 DELIVERY, STORAGE AND HANDLING

- Deliver, store and handle products under provisions of Section [01 65 00] [01 66 00] [].
- Deliver Sika materials in original unopened packages with manufacturer's labels intact.
- Protect Sika materials during transportation and installation to avoid physical damage.
- Store Sika materials in a cool, dry place protected from freezing. Store at no less than 40°F/4°C (50°F/10°C GRANITE & STONE finish).
- Store insulation boards flat and protected from direct sunlight and extreme heat.

1.07 PROJECT/SITE CONDITIONS

- Do not apply Sika material in ambient temperatures below 40°F/4°C (50°F/10°C for GRANITE & STONE Finish). Provide properly vented, supplementary heat during installation and drying period when temperatures less than 40°F/4°C (50°F/10°C for GRANITE & STONE Finish) prevail. Do not apply in ambient temperature above 100°F (38°C) or surface temperature above 120°F (49°C).
- Do not apply materials to frozen surfaces.
- Maintain ambient temperature at or above 40°F/4°C (50°F/10°C for GRANITE & STONE Finish) during and at least 24 hours after material installation and until dry.
- Under average conditions [70 °F (21 °C), 50% Relative Humidity] finish will be dry within 24 hours. Drying time is dependent on humidity, air temperature, sun exposure, surface conditions and finish thickness. Lower

Sika Fastwall 100 with Sika Thoroseal-581 System

temperature, higher humidity and application in shaded areas will extend drying time. Protect finish from rain or other precipitation and temperatures less than 40°F (4°C) for a minimum of 24 hours or until dry.

1.08 SEQUENCING AND SCHEDULING

- A. Coordinate and schedule installation of Sika Fastwall 100 with Sika Thoroseal-581 wall system with related work of other sections.
- B. Coordinate and schedule installation of trim, flashing, and joint sealers to prevent water infiltration behind the system.

1.09 WARRANTY

- A. Provide a Sika standard material warranty for Sika Fastwall 100 with Sika Thoroseal-581 wall system installations under provisions of Section [01 70 00].
- B. Comply with Sika Facades' notification procedures to assure qualification for warranty.

PART 2 - PRODUCTS

2.01 MANUFACTURERS

- A. All components of the Sika Fastwall 100 with Sika Thoroseal-581 wall system shall be obtained from the system manufacturer or through an authorized distributor.

2.02 MATERIALS

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized. Contact Sika Facades' Technical Service Department for further assistance.

- A. SIKATHOROSEAL-581 Waterproof Coating: Portland cement-based coating for concrete and masonry that resists both air infiltration and positive as well as and negative hydrostatic pressure. Polymer-modified with SIKATHOROSEAL ACRYL 60, SIKATHOROSEAL-581 creates a low maintenance and highly durable waterproof barrier
- B. SIKATHOROSEAL ACRYL 60: An acrylic-polymer emulsion which enhances the adhesion, physical properties and durability of SIKATHOROSEAL-581.
- C. **Stucco Base Coat: (Required, Select One)**
 - 1. SIKAWALL FASTWALL STUCCO BASE CONCENTRATE: Factory-blended stucco mixture of Portland cement, reinforcing fibers, and proprietary ingredients, with sand added in the field.
 - 2. SIKAWALL FASTWALL STUCCO BASE SANDED: Factory-blended stucco mixture of Portland cement, reinforcing fibers, sand, and proprietary ingredients.
- D. **Plaster Sand:** (Required if SIKAWALL FASTWALL STUCCO BASE CONCENTRATE is retained): Must be clean and free from deleterious amounts of loam, clay, silt, soluble salts and organic matter. Sampling and testing must comply with ASTM C897. Plaster sand must be graded within the following limits:

Retained on U.S. Standard Sieve	Percent retained by weight $\pm$ 2 percent	
	Minimum	Maximum
No. 4	-	0
No. 8	0	10
No. 16	10	40
No. 30	30	65
No. 50	70	90
No. 100	95	100

- E. **Water:** Clean and potable without foreign matter.
- F. SIKAWALL-520 STUCCO LEVEL COAT: Polymer modified dry- mix leveling and embedment coat for a crack suppression system.
- G. SIKAWALL POLY-BOND (adhesive/base coat for EPS trim shapes) : A dry-mix polymer adhesive and base coat

Sika Fastwall 100 with Sika Thoroseal-581 System

containing Portland cement and requiring only water for mixing.

- H. **SIKAWALL-9000 SRT MESH:** a woven fiber glass mesh with high mechanical strength and dimensional stability for improved crack resistance. Must be used with SIKAWALL-520 STUCCO LEVEL COAT.
- I. **SIKAWALL-9010 FLEXGUARD 4 Reinforcing Mesh (Required if EPS Trim Shapes Are Specified):** A. balanced, open-weave glass, fiber reinforcing mesh, twisted multi-end strands treated for compatibility with SikaWall base coats
- J. **SIKAWALL-10 STUCCO PRIME:** A 100% acrylic-based primer; color [] to closely match the selected SikaWall finish color.

NOTE TO SPECIFIER: SIKAWALL-10 STUCCO PRIME is recommended for R1.5 finish texture. Although optional in other applications, Sika recommends the use of SIKAWALL-10 STUCCO PRIME prior to application of SikaWall finish over applications of Sika Fastwall 100 with Sika Thoroseal-581. The application of SIKAWALL-10 STUCCO PRIME will enhance color uniformity and ease SikaWall finish application and will minimize the likelihood of read-through.

- K. **SIKAWALL-15 TINTED PRIMER (Required if SIKAWALL-4020 GRANITE & STONE finish is selected):** A 100% acrylic-based primer that helps alleviate shadowing. Color to closely match the selected SikaWall finish.

NOTE TO SPECIFIER – a finish is required, select acrylic or cement-based finish option below

L. Acrylic Finish:

1. **SIKAWALL PERMA-FINISH STUCCO ACRYLIC:** 100% acrylic polymer finishes with advanced technology to improve long-term performance and dirt pick-up resistance; air cured, compatible with base coat; finish color [] as selected; finish texture:
 - a. **R1.5:** A medium worm-holed” appearance which is achieved by the random aggregate sizes in the Finish. The “worm-holed” look can be circular, random, vertical or horizontal.
 - b. **F1.0:** Utilizes uniformly sized aggregates for a uniform, fine texture.
 - c. **T0.5:** Can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel
 - d. **M1.5:** Provides a uniform, “pebble” appearance.
2. **SIKAWALL PERMA-FLEX STUCCO ACRYLIC:** 100% acrylic polymer stucco grade finishes; air cured, compatible with base coat; finish color [] as selected; finish texture:
 - a. **R1.5:** A medium worm-holed” appearance which is achieved by the random aggregate sizes in the Finish. The “worm-holed” look can be circular, random, vertical or horizontal.
 - b. **F1.0:** Utilizes uniformly sized aggregates for a uniform, fine texture.
 - c. **T0.5:** Can achieve a wide variety of free-formed, textured appearances, including smooth, stipple and skip-trowel
 - d. **M1.5:** Provides a uniform, “pebble” appearance.
3. **SIKAWALL-6200 MAXLASTIC Finish:** 100% acrylic based; textured elastomeric finish that provides excellent flexibility and breathability, air cured, compatible with base coat; finish color [] as selected; finish texture:
 - a. **R1.5:** A medium “worm-holed” appearance which is achieved by the random aggregate sizes in the finish. The “worm-holed” look can be circular, random, vertical or horizontal.
 - b. **F1.5:** Utilizes uniformly sized aggregates for a uniform, fine texture.
 - c. **T0.5:** Can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel.
 - d. **M1.5:** Provides a uniform, “pebble” appearance.
4. **SIKAWALL-6100 SENERFLEX TERSUS Finish:** Modified acrylic based finish with water repellent properties, compatible with base coat; finish color [] as selected; finish texture:
 - a. **R1.5:** A medium worm-holed” appearance which is achieved by the random aggregate sizes in the Finish. The “worm-holed” look can be circular, random, vertical or horizontal.
 - b. **F1.0:** Utilizes uniformly sized aggregates for a uniform, fine texture.
 - c. **T0.5:** Can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel

Sika Fastwall 100 with Sika Thoroseal-581 System

- d. [M1.5: Provides a uniform, "pebble" appearance.](#)
- 5. [SikaWall Specialty Finishes: 100% acrylic polymer finishes that can be hand-troweled to simulate stone or create a time-honored, mottled tone-on-tone look that achieves a soft and weathered patina over time.](#)
 - a. [SIKAWALL-6260 METALLIC: Has a pearlescent appearance. It utilizes uniformly sized aggregates for a uniform fine texture.](#)
 - b. [SIKAWALL-4020 GRANITE & STONE: Is a factory-mixed, reflective stone finish consisting of colored aggregate and large black mica flakes in a 100% acrylic transparent binder that provides a classic granite or marble-like textured finished appearance.](#)
- 6. [SIKAWALL-6230 CHROMA Finish: 100% acrylic polymer-based finish with integrated high performance colorants for superior fade resistance, compatible with base coat; Senergy Finish color \[\] as selected; finish texture:](#)
 - a. [F1.0: Utilizes uniformly sized aggregates for a uniformly fine texture.](#)
 - b. [M1.5: Provides a uniform "pebble" appearance.](#)
 - c. [R1.5: Has a medium "worm-holed" appearance which is achieved by the random aggregate sizes in the Finish. The "worm-holed" look can be circular, random, vertical or horizontal.](#)

M. [Cementitious Finish:](#)

- 1. [SIKAWALL SANTA BARBARA MISSION FINISH: Traditional smooth stucco finish coat or 30/30 float finish.](#)
- 2. [SIKAWALL EXTERIOR STUCCO COLOR COAT: blend of Portland cement, hydrated lime, aggregates and additives, available in 16/20 and 20/30 aggregates](#)

2.03 ACCESSORIES

Trim: Casing bead, corner bead, expansion joint and weep screed accessories shall meet the requirements of ASTM C1063. Accessories shall be: vinyl, meeting ASTM D1784; galvanized, meeting ASTM A525 and ASTM A526; or zinc, meeting ASTM B69. Vinyl or zinc accessories are recommended where highly humid or salt-laden service conditions exist. Refer to Sika's *Lath and Plaster Trims* bulletin for additional information. Examples of trim accessories include:

- 1. Casing bead: Square edge style.
- 2. Corner bead: Small radius nose style.
- 3. Control joints: W-shaped accordion profile style.
- 4. Expansion joints: [\[Two piece type slip-joint design\]](#) or [\[pair of casing beads spaced for application of sealant bead\]](#)

PART 3 EXECUTION

3.01 EXAMINATION

A. **Site Conditions:** Verify project site conditions under provisions of Section [01 89 00] [].

B. Walls

- 1. Substrates:
 - a. Acceptable substrates are poured concrete and unit masonry.
 - b. Verify concrete/unit masonry is free of dust, dirt, grease, oils, laitance, efflorescence, biological residue, existing paint or coatings, curing compounds, form release agents, or any other contaminants which might affect the bond of SIKATHOROSEAL-581. Properly prepared concrete will have an open texture similar to fine grit sandpaper. Masonry walls should be properly cured to full load bearing capacity, laid true, and with joints tooled.
 - c. Examine surfaces to receive system and verify that substrate and adjacent materials are dry, clean, and sound. Verify substrate surface is flat, free of fins or planar irregularities greater than 1/4" in 10' (6 mm in 3 m).
- 2. Flashings: All flashings are by others and must be installed per project design detailing. Where appropriate, end-dams must be provided.
- 3. Roof: Verify that all roof flashings have been installed in accordance with the guidelines set by the Asphalt Roofing Manufacturers Association (ARMA).

Sika Fastwall 100 with Sika Thoroseal-581 System

4. Kick-out Flashing: Must be installed where required. The kick-out flashing must be leak-proof and angled (min 100°) to allow for proper drainage and water diversion. Do not proceed until all unsatisfactory conditions have been corrected.
- C. Do not proceed until all unsatisfactory conditions have been corrected.

3.02 PREPARATION

- A. Protect all surrounding areas and surfaces from damage and staining during application of Sika Fastwall 100 with Sika Thoroseal-581 wall system.
- B. Protect finished work at end of each day to prevent water penetration.

3.03 MIXING

General: No additives are permitted unless specified in product mixing instructions. Close containers when not in use. Prepare in a container that is clean and free of foreign substances. Do not use a container which has contained or been cleaned with a petroleum-based product. Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

- A. Mix Sika proprietary products in accordance with manufacturer's instructions, including the applicable Sika Fastwall 100 Stucco materials product data sheets.

3.04 APPLICATION

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02. Delete those not to be utilized.

- A. **SIKA THOROSEAL-581 Waterproof Coating:** Dampen concrete or unit masonry (SSD) just prior to SIKA THOROSEAL-581 application. Apply with a stiff bristle brush using a two coat application. Brush apply the first coat vertically and second coat horizontally, as this will allow the SIKA THOROSEAL-581 to act as a scratch coat for the stucco. Allow 24 hours between coats. The total thickness of the 2 coats should not exceed 1/8". Allow second coat of SIKA THOROSEAL-581 to cure minimum 24 hours prior to SIKAWALL FASTWALL STUCCO BASE application; apply SIKAWALL FASTWALL STUCCO BASE over cured SIKA THOROSEAL-581 within 7-10 days. The SIKA THOROSEAL-581 shall be free of any damage such as holes or breaks and must be applied to all surfaces to receive the Sika Fastwall 100 with Sika Thoroseal-581 wall system. Wrap the SIKA THOROSEAL-581 into rough openings (doors, windows, etc.) Coordinate work with other trades to assure proper sequencing, detailing and installation of materials.
- B. **Trim Junction:** When two pieces of trim abut: Set intersection of trim in a minimum 4" (100 mm) bed of acceptable trim sealant. Allow 1/8"-3/16" (3-5 mm) gap between the abutting trim pieces. Do not overlap trim. Attach the trim in accordance with manufacturer's specifications, true expansion joints must be fastened to the structural substrate.
 1. When two or more pieces of trim intersect: The vertical trim piece shall be continuous with all horizontal pieces. Miter all corners at intersections of trim, set intersection of trim in a minimum 4" (100 mm) bed of acceptable trim sealant. Allow 1/8"-3/16" (3-5 mm) gap between the intersecting trim pieces. Do not overlap the trim. Attach the trim in accordance with manufacturers' specifications.

NOTE TO SPECIFIER: It is the sole responsibility of the project design team, including the architect, engineer, etc., to ultimately determine specific expansion and control joint placement, width and design.

- C. **SIKAWALL FASTWALL STUCCO BASE:** Apply the SIKAWALL FASTWALL STUCCO BASE CONCENTRATE OR SANDED mixture to the cured SIKA THOROSEAL-581 by hand troweling to a thickness of 3/8" to 1/2". Use rod and darby to level the applied stucco base coat. After initial set begins and surface has sufficiently hardened, use sponge or hard rubber float as required to fill voids, holes or imperfections, leaving the surface ready to receive SikaWall finish coat. At subcontractor's option, the double back method of application, whereby two coats (scratch and brown) are applied and cured as one system, may be used. If this system is used, the second coat (brown) should be applied as soon as the first coat is rigid and able to support the second coat. For either application method, damp cure for at least 48 hours by lightly and evenly fogging the surface with water at least twice a day. Direct sunlight, hot temperatures, low humidity and windy conditions may make additional fogging necessary. Allow SIKAWALL FASTWALL STUCCO BASE CONCENTRATE OR SANDED to cure a minimum of 6 days prior to application of EPS insulation board shapes, SikaWall base coat and reinforcing mesh, SIKAWALL-10 STUCCO PRIME or SikaWall finish coat.

Sika Fastwall 100 with Sika Thoroseal-581 System

NOTE: SIKAWALL FASTWALL STUCCO BASE application should not exceed 5/8" thickness.

D. SIKAWALL-520 STUCCO LEVEL COAT / SIKAWALL-9000 SRT MESH or FLEXGUARD 4 Reinforcing Mesh:

1. SIKAWALL-520 STUCCO LEVEL COAT shall be applied to achieve SIKAWALL-9000 SET MESH embedment with no reinforcing mesh color visible. Apply mixed base coat to entire surface of stucco base coat with a stainless-steel trowel to embed the reinforcing mesh.
2. Immediately place reinforcing mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges. Lap reinforcing mesh 2 1/2" (64 mm) minimum at edges.
3. Ensure reinforcing mesh is continuous at corners, void of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
4. If required, apply a second layer of base coat to achieve total nominal base coat/reinforcing mesh thickness of 1/16" (1.6 mm).
5. Allow base coat with embedded reinforcing mesh to dry hard (normally 8 to 10 hours) prior to primer or finish application.

E. Decorative Shapes:

1. Apply mixed SIKAWALL POLY-BOND adhesive to entire surface of insulation board using a stainless-steel trowel with 1/2"x 1/2" (13mm x 13mm) notches spaced 1/2" (13mm) apart or 3/8"x 3/8" (10mm x 10mm) notches spaced 3/8" (10 mm) apart.
2. Immediately set shape into place and apply pressure over entire surface of board to ensure positive uniform contact and high initial grab. Do not allow base coat to dry prior to installing.
3. Abut all joints tightly and ensure overall flush level surface.
4. Check adhesion periodically by removing a shape prior to set. Properly installed shapes will be difficult to remove, and SIKAWALL POLY-BOND adhesive will be adhered to both the SIKAWALL FASTWALL STUCCO BASE and the shape.
5. Fill 1/16" (1.6mm) and larger gaps between shapes with slivers of insulation board.
6. Allow application of shapes to dry (normally 8 to 10 hours) prior to application of SIKAWALL POLY-BOND base coat and SIKAWALL-9010 FLEXGUARD 4 reinforcing mesh.
7. Rasp flush any irregularities of the shapes greater than 1/16" (1.6 mm).
8. Apply SIKAWALL POLY-BOND base coat to entire surface of insulation board with a stainless-steel trowel to embed the reinforcing mesh. Immediately place SIKAWALL-9010 FLEXGUARD 4 reinforcing mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
9. Lap reinforcing mesh 2 1/2" (64 mm) minimum at edges and 3" (75 mm) minimum onto stucco base surface.
10. Ensure reinforcing mesh is continuous at corners, void of wrinkles and embedded in base coat so that no reinforcing mesh color is visible. If required, apply a second layer of base coat to achieve total nominal base coat/reinforcing mesh thickness of 1/16" (1.6 mm).
11. Allow base coat with embedded reinforcing mesh to dry hard (normally 8 to 10 hours) prior to primer or finish application.

F. SIKAWALL-10 STUCCO PRIME / SIKAWALL-15 TINTED PRIMER:

1. Apply primer to cured stucco or base coat with a sprayer, 3/8" (10 mm) nap roller, or good quality latex paint brush at a rate of approximately 150-250 sq. ft. per gallon (3.6-6.1 m² per liter). Primer must be dry to the touch before proceeding to the SikaWall finish application.

G. SikaWall Acrylic Finish Coat: SIKAWALL PERMA-FINISH STUCCO ACRYLIC, SIKAWALL PERMA-FLEX STUCCO ACRYLIC, SIKAWALL-6200 MAXLASTIC, SIKAWALL-6100 SENERFLEX TERSUS, SIKAWALL-6260 METALLIC and SIKAWALL-6230 CHROMA.

1. Apply finish directly to the stucco base coat or primed stucco base coat with a clean, stainless steel trowel.
2. Apply and level finish during the same operation to a minimum obtainable thickness consistent with uniform coverage. Maintain a wet edge on finish by applying and texturing continually over the wall surface.
3. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Float finish to achieve final texture.

H. SIKAWALL-4020 GRANITE & STONE Finish:

1. Apply SIKAWALL-15 TINTED PRIMER to the substrate in accordance with the current product bulletin. Primer shall be of the corresponding color for the selected finish color. Allow the primer to dry to the touch before proceeding with finish application.

Sika Fastwall 100 with Sika Thoroseal-581 System

2. Apply a tight coat of finish with a clean, stainless steel trowel. Maintain a wet edge on finish by applying and leveling continually over the wall surface.
3. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Allow first coat to set until surface is completely dry prior to applying a second coat of finish.
4. Use a stainless-steel trowel and apply the second coat of finish. Achieve final texture using circular motions. Total thickness of finish may be between 1/16" (1.6 mm) and 1/8" (3.2 mm).

I. SikaWall Cementitious Finish

1. SIKAWALL SANTA BARBARA MISSION FINISH:

- a. Color coat shall be approximately 1/8" thick.
- b. Hand application over a Portland cement plaster brown coat: Prior to application of SBMF stucco finish, the Portland cement base coat shall be dampened with clean water to control and equalize suction. Allow surface moisture to dissipate prior to the application of the Stucco Finish.
- c. Trowel or float apply an even coat completely covering the base coat and allow it to set although prior to drying out, trowel apply a second tight coat of the same material over the first to the desired finish level.

Traditional Smooth Santa Barbara Mission Finish: Allow the application to set although prior to drying out, trowel the surface to the desired or approved finish level using as little water as possible.

30/30 Float Finish: Before the second coat has set, use a float to bring the aggregate to the surface to achieve the desired sand finish.

- d. During periods of hot or dry weather condition, a light spray (mist) of clean water is recommended over the stucco finish. SIKAWALL LAHABRA SANTA BARBARA MISSION FINISH will normally dry and set the same day. Allow 28 days for curing.
- e. Color and performance may be affected by the addition of field additives. Field additives are not to be used except at the direction of the Sika Facades Technical Support.
- f. Variations in color due to weather, job conditions, and method of application should be expected.

2. SIKAWALL EXTERIOR STUCCO COLOR COAT:

- a. Color coat shall be approximately 1/8" thick.
- b. Hand application over a Portland cement plaster brown coat: Prior to application of exterior stucco finish, the Portland cement base coat shall be dampened with clean water to control and equalize suction. Allow surface moisture to dissipate prior to the application of the Stucco Finish.
- c. Standard (16/20) Sand Float finish: Trowel apply an even coat completely covering the stucco base coat and sponge float the surface with circular motions to the desired or approved finish level, using as little water as possible
- d. Standard (16/20) Skip Trowel textured finish: Trowel or float apply an even coat completely covering the stucco base coat and sponge float the surface with circular motions to a uniform float finish level. Allow the first application-background to set, although prior to drying out. Apply a small amount of the same material over the floated background using the skip trowel method to the desired finish level then lightly trowel over the entire area, "knocking it down" or lightly flattening it out, using random strokes of the trowel.
- e. Fine Float (20/30) sand Float finish: Trowel apply an even coat completely covering the stucco base coat and allow it to set, although prior to drying out. Trowel apply a second tight coat of the same material over the first and sponge float the surface with circular motions to the desired or approved finish level, using as little water as possible.

3.05 CLEANING

- A. Clean work under provisions of Section [01 74 00] [].
- B. Clean adjacent surfaces and remove excess material, droppings, and debris.

3.06 PROTECTION

- A. Protect materials from rain, snow and frost for 48-72 hours following application.
- B. Under average conditions [70 °F (21 °C), 50% Relative Humidity] finish will be dry within 24 hours. Drying time is dependent on humidity, air temperature, sun exposure, surface conditions and finish thickness. Lower

Sika Fastwall 100 with Sika Thoroseal-581 System

temperature, higher humidity and application in shaded areas will extend drying time. Protect finish from rain or other precipitation and temperatures less than 40°F (4°C) for a minimum of 24 hours or until dry.

- C. Protect installed construction under provisions of Section [01 76 00] [].

END OF SECTION

Sika Fastwall 100 with Sika Thoroseal-581 System

WARRANTY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com/ or by calling SIKA Facades' Technical Service Department at 1-800-589-1336. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/>.