

PRODUCT DATA SHEET

Xtra Stop Base Coat

100% acrylic adhesive and base coat

COLOR

Off white prior to the addition of Portland Cement.

PACKAGING

27.2 kg per 19-liter pail
(60 lbs per 5-gallon pail)

COVERAGE PER PAIL*

Adhesive

Notch Trowel: 160 ft² (14.8 m²)

Mesh Embedment

Flexguard 4: 280 ft² (26 m²)

Intermediate 12: 200 ft² (18.5 m²)

Hi-Impact 20 & Flexguard 4: 120 ft² (11 m²)

Adhesive & Flexguard 4

Embedment:

120 ft² (11 m²)

*Coverage rates vary depending on porosity of substrates and application techniques.

SHELF LIFE

Two (2) years, properly stored in original containers.

DESCRIPTION

100% acrylic adhesive and base coat that is field-mixed with Type I or Type II Portland cement. Noted for its water resistant properties.

USES

1. To adhere expanded polystyrene insulation board to the following acceptable substrates: Senershield[®]-R/-RS/-VB; expanded polystyrene insulation board (EPS); cement boards conforming with ASTM C1325 (Type A - exterior) including PermaBase[®] Cement Board; poured concrete/unit masonry; ASTM C1177 type sheathings, including DensGlass[™] or DensElement exterior sheathing (sheathing only), eXP[™] sheathing, GlasRoc[®] sheathing, Securock[™] glass-mat sheathing, Weather Defense[™] Platinum sheathing, GreenGlass[®] sheathing; gypsum sheathing (ASTM C79/C1396); Exposure 1* or exterior plywood* (Grade C/D or better), Exposure 1 OSB*
***Note: Not for use directly over wood-based sheathing, Senershield-R/-RS/-VB required over wood sheathing.**
2. For Senergy reinforcing mesh embedment as part of Senergy wall systems and as a skim coat over masonry and concrete above grade substrates.

ADVANTAGES

Highly water resistant and used to waterproof sloped parapets and window sills.

Smooth, creamy consistency that trowels easily, speeds mesh embedment, reduces applicator arm fatigue, and increases job-site productivity.

Easy to mix 1:1 ratio providing less chance of error.

Water based offering a safer, non-toxic product that cleans up easily with soap and water.

TEST RESULTS

TEST	METHOD	CRITERIA	RESULT
VOC	ASTM D3960 (based in part on EPA method 24)	Report Value	0 grams per liter less water and exempt solvents
Accelerated Weathering	ASTM G 23	No deleterious effects after 2000 hours.	Pass
Accelerated Weathering	ASTM G 53	No deleterious effects after 7500 hours.	Pass
Water Resistance of Coating in 100% R.H.	ASTM D 2247	No deleterious effects after 14 days exposure	Pass
Hydrostatic Resistance	ASTM D751	Report Value	No leakage at 65 psi after five minutes when applied at nominal 1/8" thickness.
Surface Burning Characteristics	ASTM E 84	Report Value	Flame Spread < 25 Smoke Development < 450 (Class A)
Tensile Bond	ASTM C297, E2134	15 psi minimum	> 15 psi

MIXING

In a clean container, mix the contents of the Xtra-Stop Base Coat pail with a low speed drill and paddle mixer until thoroughly blended. Mix one-part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, thoroughly mixing to a homogeneous consistency after each additional increment. Allow base coat to set for 5-10 minutes, then remix/ retemper before use. Small amount of clean potable water can be added to adjust workability.

- Do not use a container which has contained or been cleaned with a petroleum-based product.
- Additives are not permitted.
- Close container when not in use.
- Clean tools with soap and water immediately after use. Dried material can only be removed mechanically.

APPLICATION

ADHESIVE FOR NON-DRAINAGE EIFS

Notched trowel method: Apply base coat to entire surface of insulation board using a stainless steel trowel with 1/2" x 1/2" notches spaced 1/2" apart (13 mm x 13 mm x 13 mm) or 3/8" x 3/8" notches spaced 3/8" apart (10 mm x 10 mm).

ADHESIVE FOR ADHERED SENERGY DRAINAGE EIFS

Apply base coat to entire surface of insulation board using a stainless-steel trowel with 1/2"x 1/2" notches spaced 2" apart (13 mm x 13 mm x 50 mm). Ribbons of adhesive must be applied parallel to the 2' dimension of the EPS insulation board to ensure they are vertical when the EPS insulation board is applied to the substrate. Immediately set board into place and apply pressure over entire surface of board to ensure positive uniform contact and high initial grab. Do not slide board into place. Do not allow base coat to dry prior to installing. Allow application of EPS insulation board to dry (normally 8 to 10 hours) prior to application of Base Coat/ SikaWall Reinforcing Mesh.

BASE COAT FOR REINFORCING MESH EMBEDMENT

Trowel apply base coat to the surface of the insulation board or approved substrate. Fully embed SikaWall® Reinforcing Mesh in to wet base coat, ensure no mesh color is visible. Lap reinforcing mesh a minimum 2 1/2" (64 mm) at edges and 8" (203 mm) around corners. Ensure reinforcing mesh is free

of wrinkles. Allow reinforced base coat to dry hard (normally 8 to 10 hours) prior to application of Senergy Finish or SikaWall Primer.

DRY TIME

Typically, 8 to 10 hours. Protect from rain and from temperatures less than 40°F (4°C) for 24 hours after installation and until dry.

LIMITATIONS

1. Not for use directly over wood-based substrates.
2. Do not exceed applied thickness of 1/8" (3.2mm).
3. Protect from rain and from temperatures less than 40°F (4°C) for a minimum of 24 hours and until dry.
4. Efflorescence of Portland cement-based substrates such as concrete, masonry units and stucco may cause staining or discoloration on the surface of applied base coat.
5. When temperatures less than 40°F (4°C) prevail, provide supplementary heat during installation and drying period for at least 24 hours after installation and until dry. Do not apply in ambient temperature above 100°F (38°C) or surface temperature above 120°F (49°C).

6. Do not apply materials to frozen surfaces.
7. Not for use on damp surfaces, below-grade applications or on surfaces subject to water immersion.

SHIPPING & STORAGE

- Protect materials during transportation to avoid physical damage. Store in a cool, dry place protected from freezing, extreme heat and direct sun. Store at no less than 40°F (4°C).
- Do not stack pallets.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting usa.sika.com/senergy, e-mailing your request to mbsbscst@mbcc-group.com or calling +1 (800) 433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

TECHNICAL SUPPORT

Consult Sika Facades Technical Services Department at +1 (800) 589-1336 for specific recommendations concerning all other applications. Consult the Sika Facades website at usa.sika.com/senergy, for additional information about products and systems and for updated literature.

LIMITED WARRANTY NOTICE

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com/senergy or by calling our Technical Service Department at +1 (800) 589-1336.

Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at usa.sika.com/ or by calling +1 (800) 589-1336.