

## PRODUCT DATA SHEET

## Sika® Ucrete® HS22 NA

## SELF-LEVELING BROADCAST CEMENTITIOUS URETHANE SLURRY

## PRODUCT DESCRIPTION

Sika® Ucrete® HS22 NA is a self-leveling, solid color, three component, cementitious urethane mortar designed to provide excellent resistance to abrasion, impact, and chemical attack. Sika® Ucrete® HS22 NA is broadcast with dried quartz sand and sealed with Sika® Ucrete® TC31 NA to produce a solid color finish. Can be broadcasted with colored quartz aggregate and sealed with Sikafloor resinous flooring products for a decorative finish. The system is typically installed at 3/16" to 1/4" (188 to 250 mils) thickness.

## USES

Sika® Ucrete® HS22 NA may only be used by experienced professionals.

- Sika® Ucrete® HS22 NA is primarily used to protect concrete substrates in aggressive environments.
- Food processing plants, wet and dry process areas, kitchen and oven areas, freezers and coolers, dairies, breweries, wineries, distilleries, laboratories, chemical process plants, pulp and paper plants, warehouses and storage areas, and pharmaceutical facilities.
- When used as a base coat or layer for a MVT system, the minimum thickness of the Sika® Ucrete® HS22 NA is 125 mils. This is the minimum thickness prior to the broadcast of any aggregate. NOTE: Sika® Ucrete® HS22 NA at 1/8" will not level and will have surface imperfections.

## CHARACTERISTICS / ADVANTAGES

- Can be applied on green concrete, typically 7-10 days. Full 28 days cure time is not necessary.
- Can be applied over partially cured concrete substrates (>4% mass (pbw-part by weight)) as measured with Tramex® CME/CMExpert type concrete moisture meter (surface moisture).
- Can be applied to concrete substrates where <100% relative humidity is measured as per ASTM F2170.
- Resists a very wide range of organic and inorganic acids, alkalis, amines, salts and solvents. Consult Sika Technical Service for full details. Refer to the Sika® Ucrete® HS22 NA Chemical Resistance Chart.
- Similar coefficient of thermal expansion to concrete allowing movement with the substrate through normal thermal cycling. It will perform and retain its physical characteristics through a wide temperature range from -40°F (-40°C) up to 248°F (120°C).
- Steam cleanable at 3/16" to 1/4" (188 to 250 mils) thickness.
- Non-tainting, odorless.
- Behaves plastically under impact/deforms but will not crack or debond.
- High abrasion qualities result from its aggregate structure.
- Maintain and extend existing expansion joints up through the Sika® Ucrete® Flooring System.
- Minimal maintenance costs, superior life cycle cost advantage versus tile.
- Meets the requirements of USDA for use in food plants.

## PRODUCT INFORMATION

<b>Packaging</b>	Part 1:	1 US gallon pail (3.78 L) 8.53 lb
	Part 2:	0.70 US gallon pail (2.64 L) 7.33 lb
	Part 3:	43.96 lbs (19.94 kg) in a bag (powder)
	Kits (1+2+3):	59.83 lb (27.14 kg)
<b>Color</b>	RAL 7012 Basalt Gray RAL 3009 Oxide Red RAL 7038 Agate Gray RAL 1001 Beige RAL 7042 Traffic Grey	
<b>Shelf Life</b>	12 months in original unopened packaging	
<b>Storage Conditions</b>	Store dry between 50° - 77°F (10° - 25°C). Protect from freezing. If frozen, discard.	
<b>Density</b>	16.84 lb/US gal. (2.02 kg/L)	ASTM C905 at 73 °F (23 °C) and 50% R.H

## TECHNICAL INFORMATION

<b>Shore D Hardness</b>	80 - 85	ASTM D2240 at 73 °F (23 °C) and 50% R.H
<b>Abrasion Resistance</b>	~0.10 g (0.004 oz) loss CS-17/1,000 cycles/1,000 g ~0.227 g (~0.008 oz) loss H-22/1,000 cycles/1,000 g	at 73 °F (23 °C) and 50% R.H
<b>Impact Strength</b>	5.02 ft-lb (6.81 joules) at 1/8" (3 mm of thickness)	ASTM D2794 at 73 °F (23 °C) and 50% R.H
<b>Compressive Strength</b>	5,657 psi (39 MPa) 28 days	ASTM C579 at 73 °F (23 °C) and 50% R.H
<b>Flexural Strength</b>	2,790 psi (8.9 MPa)	ASTM C580 at 73 °F (23 °C) and 50% R.H
<b>Tensile Strength</b>	1,045 psi (6.5 MPa)	ASTM C307 at 73 °F (23 °C) and 50% R.H
<b>Tensile Adhesion Strength</b>	>400 psi (>2.5 MPa) (substrate failure) Pull-off Strength	ASTM D7234 at 73 °F (23 °C) and 50% R.H
<b>Coefficient of Thermal Expansion</b>	0.89 x 10 <sup>-5</sup> in/in/°F (1.6 x 10 <sup>-5</sup> mm/mm/°C)	ASTM D696 at 73 °F (23 °C) and 50% R.H
<b>Chemical Resistance</b>	Please consult Sikafloor Technical Services	
<b>Microbiological Resistance</b>	Resistance to Fungi Growth Rated 0 (no growth) Resistance to Mold Growth Rated 10 (highest resistance)	ASTM G21 at 73 °F (23 °C) and 50% R.H ASTM D3273 at 73 °F (23 °C) and 50% R.H
<b>Skid / Slip Resistance</b>	~0.77 wet (full broadcast Sikadur®-508, Sika® Ucrete® TC31 NA	ANSI A137.1 / ANSI A326.3 DCOF-BOT 3000e
<b>Indentation</b>	~0%	MIL-PRF-24613 at 73 °F (23 °C) and 50% R.H
<b>Service Temperature</b>	-40 °F (-40 °C) min./248 °F (120 °C) max.	

## APPLICATION INFORMATION

### Coverage

Approx. 50 ft<sup>2</sup> (4.6 m<sup>2</sup>) per unit at 1/8" (3.2 mm) as MVT system only  
 Approx. 37 ft<sup>2</sup> (3.4 m<sup>2</sup>) per unit at 160 mils (4 mm)  
 Approx. 31 ft<sup>2</sup> (2.8 m<sup>2</sup>) per unit at 3/16" (4.7 mm)  
 Approx. 25 ft<sup>2</sup> (2.3 m<sup>2</sup>) per unit at 1/4" (6.3 mm)  
 (The above figures do not allow for surface porosity, profile or waste)

### Ambient Air Temperature

Minimum/Maximum 40°/85 °F (4°/30 °C)

### Substrate Temperature

Minimum/Maximum 40°/85 °F (4°/30 °C)

### Pot Life

#### Material Temperature

#### Time

+50 °F (10 °C)

~ 25 - 30 minutes

+68 °F (20 °C)

~ 15 - 20 minutes

+86 °F (30 °C)

~ 5 - 10 minutes

### Cure Time

#### Temperature

#### Foot Traffic

#### Light Traffic

#### Full Cure

+50 °F (10 °C)

~ 24 hours

~ 48 hours

~ 7 days

+68 °F (20 °C)

~ 18 hours

~ 24 hours

~ 5 days

+86 °F (30 °C)

~ 6 hours

~ 18 hours

~ 3 days

### Waiting / Recoat Times

Before applying Sika® Ucrete® HS22 NA when a scratch primer with broadcast is used allow:

#### Substrate Temperature

#### Minimum

#### Maximum

+50 °F (10 °C)

12 hours

24 hours

+68 °F (20 °C)

3 hours

12 hours

+86 °F (30 °C)

2 hours

8 hours

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## LIMITATIONS

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

- Do not apply to polymer modified cement mortars (PCC) that may expand when sealed with an impervious resin.
- Do not apply to water-soaked, glistening-wet concrete substrates. (i.e standing water)
- Do not apply to un-reinforced sand cement screeds, asphaltic or bitumen substrate, glazed tile or non-porous brick, tile and magnesite, copper,

aluminum, soft wood, or urethane composition, elastomeric membranes, fiber reinforced polyester (FRP) composites.

- Do not apply to cracked or unsound substrates.
- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur.
- Freshly applied material should be protected from dampness, condensation and water for at least 24 hours. Protect substrate during application from condensation from pipes or any overhead leaks.
- Protect applied product from exposure to uncured cement products; masonry mortar, drywall compound. Exposure will result in staining that can not be removed.
- Do not apply to surfaces where moisture vapor can condense and freeze.
- Do not apply to vertical or overhead surfaces. For vertical surfaces refer to Sika® Ucrete® RG29 NA.
- Do not featheredge.
- Applied material will follow undulations, depressions, lines, etc. of the underlying substrate. Visual appearance of the finished floor may vary, including, but not limited to, reflection.
- This product is not designed for negative side

waterproofing

**Material Temperature:** Precondition material for at least 24 hours between 65° to 75°F (18° to 24°C).  
**IMPORTANT:** Product must be protected from freezing. If frozen, discard in a responsible manner in accordance with local, state and federal law.

**Ambient Temperature:** Minimum/Maximum 40°/85 °F (4°/30 °C)

**Substrate Temperature:** Minimum/Maximum 40°/85 °F (4°/30 °C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application must adhere to Material, Ambient and Substrate temperatures listed above or a decrease in product workability and slower cure rates will occur.

**Relative Ambient Humidity:** Minimum ambient humidity 30%

**Dew Point:** Beware of condensation! The substrate must be at least 5 °F (3 °C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature. Calculate Dew Point from the substrate surface temperature, not the ambient temperature.

**Mixing:** Do not hand mix Sikafloor materials. Mechanically mix only. Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Under no circumstance should thinners be added to the mix. Adding thinners will void any applicable Sika warranty.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, forms oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit good bond.

Prepare the surface by any appropriate mechanical

means, in order to achieve a profile equivalent to ICRI CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tensile at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

### Edge Terminations

All free edges of a Sika® Ucrete® floor, whether at the perimeter, along gutters or at drains require extra anchorage to distribute mechanical and thermal stresses. This is best achieved by forming or cutting grooves in the concrete. Grooves should have a depth and width of 2 times thickness of the Sika® Ucrete® floor.

If necessary, protect all free edges with mechanically attached metal strips. Do not featheredge, always turn into an anchor groove.

### Expansion Joints

Expansion joints should be provided in the substrates at the intersection of dissimilar materials. Isolate areas subject to thermal stresses, vibration movements or around load-bearing columns and at vessel sealing rings. Refer to details provided at <http://usa.sika.com>.

### Priming

Substrate priming is normally not required under typical circumstances. However, due to variations in concrete quality, surface conditions, surface preparation and ambient conditions, test areas are recommended to determine whether priming is required to prevent the possibility of outgassing blisters, debonding, pinholes and other aesthetic variations.

Standard primer procedure is a 15-20 mils scratch coat of Sika® Ucrete® TC31 NA or Sika® Ucrete® HS24 NA and light broadcasting of dry quartz sand. This is the preferred method for concrete substrates.

### MIXING

#### Mix Ratio

Parts 1 : 2 : 3 = **Mix full units only**

Mixing will be affected by temperature; condition materials for use to 65 - 75 °F (18 - 24 °C). Premix Parts 1 and 2 separately, make sure all pigment is evenly distributed. Pour Parts 1 and 2 into a clean mixing bucket, and mix for 30 seconds.

Add Part 3 (powder) pouring slowly over a period of 20 seconds. Note: **Do not dump powder into resin!** Allow Part 3 to blend for a further 2-1/2 minutes after all powder is emptied into the resin to ensure complete mixing and that all powders are evenly distributed.

#### Product Data Sheet

Sika® Ucrete® HS22 NA  
March 2025, Version 02.01  
020814020020000092

During the mixing operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing (Parts 1+2+3).

**Note:** Improved flowability on cool substrates and low ambient temperatures (<55 °F) can be achieved by removing a maximum of 2.2 lb (1.0 kg) of Part 3 (powder) per unit. Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

## APPLICATION

### Scratch Coat

Typically not required (see priming instructions)

### Body Coat

Mix and pour Sika® Ucrete® HS22 NA materials on the floor. Spread to the desired thickness (160 mils - 1/4") using a screed gauge rake or trowel. Take care to spread newly mixed materials across the transition of previous applied mixes before the surface begins to set. Immediately spike roll the surface to release trapped air in the matrix. Loop rolling is also acceptable.

Sika® Ucrete® HS22 NA requires the wet surface to be broadcast to rejection with quartz or mineral aggregates. Aggregate must fall vertically to avoid surface defects / do not broadcast up to the transition line of new mixes, always broadcast 2 - 3 feet beyond the wet edge. Allow broadcast surface to cure sufficiently to be able to resist foot traffic without damaging the surface. Remove excess aggregate by sweeping or vacuuming until surface is free of all loose particles and dust.

A topcoat of Sika® Ucrete® TC31 NA can be applied to lock in the aggregate. Allow a minimum 12 hour cure period at 68 °F (20 °C) before foot traffic after the Sika® Ucrete® TC31 NA is applied. Please refer to the individual most current and respective Product Data Sheet for specific and detailed information.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- **KEEP CONTAINER TIGHTLY CLOSED**

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
usa.sika.com



### Product Data Sheet

Sika® Ucrete® HS22 NA  
March 2025, Version 02.01  
020814020020000092

- **KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION**
- **FOR INDUSTRIAL USE ONLY**
- **FOR PROFESSIONAL USE ONLY**

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

SikaUcreteHS22NA-en-US-(03-2025)-2-1.pdf

