

PRODUCT DATA SHEET

Sikalastic® Rapid Mortar WG

High-performance, rapid-setting, resin-mortar

PRODUCT DESCRIPTION

Sikalastic® Rapid Mortar WG is a winter grade, rapid setting, polymethyl methacrylate (PMMA) resin-mortar. Sikalastic® Rapid Mortar WG requires Sikalastic® Rapid Mortar Part B to obtain the correct consistency. Sikalastic® Rapid Mortar WG is then combined with Sikalastic Rapid Catalyst PMMA to induce curing.

USES

Used as a thick concrete patch prior to application of Sikalastic Rapid PPMA systems or Liquid Flashing systems. Also, used as a traffic wear surfacing applied over Sikalastic Rapid PPMA reinforced and unreinforced waterproofing systems

CHARACTERISTICS / ADVANTAGES

- High-performance, UV-stable
- Abrasion-resistant topcoat
- Rapid curing and easy application provides same-day installation
- Excellent chemical and corrosion resistance
- Aggregate-infused formula for added durability for high traffic areas

PRODUCT INFORMATION

Chemical Base	polymethyl methacrylate (PMMA) liquid resin	
Packaging	2.5 gallon (9.4 L) pails, 22lb (10 kg) per pail	
Shelf Life	Sikalastic® Rapid Mortar WG has a shelf life of up to 12 months in the original unopened pail when properly stored, sealed and unmixed.	
Storage Conditions	Store in a tightly closed container in a cool, dry, ventilated area away from heat and oxidizing agent. Do not store in direct sunlight or in temperatures below 55°F (13°C) or above 80°F (27°C). Keep away from open fire, flame or any ignition source.	
Density	53.7 @ 73.4°F (23°C)	ASTM D1475
Flash Point	73.4°F (23°C)	
Volatile organic compound (VOC) content	5.0 g/L	

TECHNICAL INFORMATION

Testing	91 @ 73.4°F (23°C)	ASTM D2240
Abrasion Resistance	203 mg (0.00045 lb)	ASTM D4060 4" disc

Mixing Ratio	Temperature Range	Catalyst required (per Liter of resin)
	23°F - 37° F (-5°C - 3°C)	5 tablespoons (47 g)
	37°F - 50° F (3°C - 10°C)	3 tablespoons (31 g)
	50°F - 68°F (10° - 20°C)	1.5 tablespoons (16 g)

Sikalastic® Rapid Mortar WG requires combining one container of Sikalastic® Rapid Mortar WG (2.5 Gal) with one bag of Sikalastic® Rapid Mortar Part B (255 lb), creating a 72 lb work pack. Catalyst quantity will range from 2 – 6% (by weight), dependent on the ambient temperature.

Coverage	SUBSTRATE PROFILE	COVERAGE PER 72 lb WORK PACK	TOTAL THICKNESS
	Smooth (CPS-3)	80 sqft (7.4 m ²)	79 mils (2.0 mm)
	Typical (CPS-4)	77 sqft (7.2 m ²)	83 mils (2.1 mm)
	Rough (CPS-5)	74 sqft (6.9 m ²)	87 mils (2.2 mm)

All values are nominal. Coverage rates may vary depending on substrate conditions and the application technique. Wet and dry thicknesses are always equivalent.

Ambient Air Temperature	23°F - 68° F (-5°C - 20°C)
Pot Life	10 - 15 minutes All working and cure times are approximate and may vary upon wind, humidity, and ambient/ surface temperatures.

BASIS OF PRODUCT DATA

site conditions and curing conditions.

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual

AVAILABILITY/WARRANTY

AVAILABILITY

From Sika Corporation – Authorized Applicators for use within Hydrotech systems.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All work surfaces should be clean, dry, free of dirt, dust, debris, oils and other contaminants.

MIXING

Thoroughly mix the entire pail of Sikalastic® Rapid Mortar WG (resin) for 2-3 minutes. Remove the Sikalastic® Rapid Mortar Part B from the 7-gallon plastic pail, then pour Sikalastic® Rapid Mortar WG into the 7-gallon plastic pail. Using a slow-speed (200-400 rpm) mechanical mixer with a spiral agitator, slowly add the entire bag of Sikalastic® Rapid Mortar Part B. Continue mixing for 2-5 minutes or until a smooth lump-free mortar is achieved.

APPLICATION

Only catalyze the amount of material that can be applied within 10-15 minutes. Add Sikalastic Rapid Catalyst PMMA based on published catalyst mixing rates. Once the catalyst is added to the mortar, mix for 2-3 minutes. Apply the mortar to clean, prepared and primed substrate at the required coverage rate using a pin roller, stub roller, steel v-notch trowel or steel rake. Mortar should be uniformly spread across the substrate and rolled with a pin roller to knock down any high spots.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
Sikalastic® Rapid Mortar WG
February 2026, Version 01.01
020915402000246435

SikalasticRapidMortarWG-en-US-(02-2026)-1-1.pdf

