



**DIVISION 7 - THERMAL AND MOISTURE PROTECTION**  
**Section 07900 Joint Sealers**  
**Elastomeric and non-Elastomeric sealant**

**Part 1 - General**

**1.01 Summary**

- A. This specification describes the sealing of joints with a one-component, or multi-component, gun-grade, neutral cure, elastomeric silicone sealant.

**1.02 Quality Assurance**

- A. Manufacturing qualifications: The manufacturer of the specified product shall be ISO 9001 certified and have in existence a recognized ongoing quality assurance program independently audited on a regular basis.
- B. Contractor qualifications: Contractor shall be qualified in the field of concrete repair and protection with a successful track record of 5 years or more. Contractor shall maintain qualified personnel who have received product training by a manufacturer's representative.
- C. Install materials in accordance with all safety and weather conditions required by manufacturer or as modified by applicable rules and regulations of local, state and federal authorities having jurisdiction. Consult Material Safety Data Sheets for complete handling recommendations.

**1.03 Delivery, Storage, and Handling**

- A. All materials must be delivered in original, unopened containers with the manufacturer's name, labels, product identification, and batch numbers. Damaged material must be removed from the site immediately.
- B. Store all materials off the ground and protect from rain, freezing or excessive heat until ready for use.
- C. Condition the specified product as recommended by the manufacturer.

**1.04 Job Conditions**

- A. Environmental Conditions: Optimal sealant application temperature: Between 40°F (5°C) and rising.  
Do not apply material if it is raining or snowing or if such conditions appear to be imminent. Minimum application temperature -20°F (-27°C) and maximum application temperature 130 °F (54 °C).
- B. Protection: Precautions should be taken to avoid damage to any surface near the work zone due to mixing and handling of the specified coating.

**1.05 Submittals**

- A. Submit two copies of manufacturer's literature, to include: Product Data Sheet, and appropriate Material Safety Data Sheets (MSDS).

**1.06 Warranty**

- A. Provide a written warranty from the manufacturer against defects of materials for a period of one (1) years, beginning with date of substantial completion of the project.

## Part 2 - Products

### 2.01 Manufacturers

- A. Sikasil®-WS 295 and Sikasil®-WS 295 FPS, as manufactured by Sika Corporation, 201 Polito Avenue, Lyndhurst, NJ 07071 is considered to conform to the requirements of this specification.

### 2.02 Materials

- A. Silicone Sealant:
  - 1. The joint sealant shall be a one-component, or multi-component,,gun grade,neutral cure, silicone material. It shall be for exterior joints in vertical surfaces and non-traffic horizontal surfaces such as, but not limited to most common building materials including glass, aluminum, metal, tile, fibreglass, plastic, ceramic, masonry, concrete, brick, powder coated aluminum, fluoropolymer painted surfaces, vinyl, PVC, granite, limestone, marble and wood.
- B. Any primers, as required, recommended by the manufacturer of the specified product, approved by the Engineer.
- C. Backer rod or bond breaker tape, as approved by the Engineer.

### 2.03 Performance Criteria

- A. Properties of the uncured neutral cure silicone sealant:
  - 1. Tack-Free Time (ASTM C-679) – 50 minutes
  - 2. Final Cure 7 – 14 days
  - 3. Consistency: non-sag
  - 3. Color: 7 architectural standard colors, plus # for Sikasil®-WS 295 FPS
- B. Properties of the cured neutral cure silicone sealant:
  - 1. Tensile Properties (ASTM D-412) at 21 days
    - a. Tensile Stress: 200-psi min.(1.38 MPa)
    - b. Elongation at Break: 800%
    - c. Modulus of Elasticity 100% 55 psi (0.38 MPa)
  - 2. Shore A Hardness (ASTM C-661) at 21 days: 20 +/- 5
  - 3. Tear Strength (ASTM D-624) at 21 days: 50 lb./in.
  - 4. Peel Strength (ASTM C-719) at 21 days: 30
  - 5. The sealant shall conform to Federal Specification TT-S-00230C, Type II, Class A and Federal Specification for Silicones TT-S-001543A, Type non-sag.
  - 6. The sealant shall conform to ASTM C-920, Type S, Grade NS, Class 50.
  - 7. The sealant shall be non-staining.
  - 8. The sealant shall be capable of +50% / -50% joint movement

**Note:** Tests were performed with material and curing conditions at 23°C (75°F) and 45-55% relative humidity.

## **Part 3 - Execution**

### **3.01 Surface Preparation**

- A. The joint and adjacent substrate must be clean, dry, sound and free of surface contaminants. Remove all traces of the old sealant, dust, laitance, grease, oils, curing compounds, form release agents and foreign particles by mechanical means, i.e. – sandblasting, etc., for porous substrates and by two rag solvent wipe method for non porous substrates as approved by the engineer. Blow joint free of dust using compressed air line equipped with an oil trap.

### **3.02 Mixing and Application**

#### **A. Joints:**

1. Placement Procedure: Prime substrate as required based upon the recommendations of the manufacturer of the specified product, when field testing indicates need, as approved by the Engineer.
2. Install approved backer rod or bond breaker tape in all joints subject to thermal movement to prevent three-sided bonding and to set the depth of the sealant at a maximum of 1/2 in., measured at the center point of the joint width. Approval of the backer rod or bond breaker tape shall be made by the Engineer.
3. Joints shall be masked to prevent discoloration or application on unwanted areas, as directed by the Engineer. If masking tape is used, it shall not be removed before tooling, yet must be removed before the initial cure of the sealant. Do not apply the masking tape until just prior to the sealant application.
4. Install sealant into the prepared joints when the joint is at the mid-point of its expansion and contraction cycle. Place the nozzle of the gun, either hand, air, or electric powered, into the bottom of the joint and fill entire joint. Keep the tip of the nozzle in the sealant; continue with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping the sealant to eliminate the entrapment of air. Tool as required to properly fill the joint.
5. Adhere to all limitations and cautions for the neutral cure silicone sealant as stated in the manufacturer's printed literature.


#### **B. Cracks**

1. For best performance sealant should be gunned into crack to a minimum of a 1/4" in depth. Place the nozzle of the gun, either hand, air or electric powered, into the bottom of the crack and fill entire crack. Keep the tip of the nozzle in the sealant. Continue with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping the sealant to eliminate the entrapment of air. Tool as required to properly fill the crack.
2. Adhere to all limitations and cautions for the neutral cure silicone sealant as stated in the manufacturer's printed literature.

### **3.03 Cleaning**

- A. The uncured silicone sealant can be cleaned with an approved solvent. The cured silicone sealant can only be removed mechanically.
- B. Leave finished work and work area in a neat, clean condition without evidence of spillovers onto adjacent areas.

# Sikasil®-WS 295 and Sikasil®-WS 295FPS Expansion Joint Filler



1. Install appropriate backer material to prevent three-sided adhesion and to control sealant depth.
2. **Sikasil®-WS 295 and Sikasil®-WS 295 FPS**, should be gunned into joint at mid-point of designed expansion and contraction cycle.
3. Tool as required to properly fill joints.

Note: **Sikasil®-WS 295 and Sikasil®-WS 295 FPS**, is designed for all types of joints where sealant will not exceed 1/2" in depth.

**Concrete Restoration Systems by Sika Corporation, 201 Polito Avenue, Lyndhurst, NJ 07071**

The preceding specifications are provided by Sika Corporation as a guide for informational purposes only and are not intended to replace sound engineering practice and judgment and should not be relied upon for that purpose. **SIKA CORPORATION MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS OR THE CONTENTS OF THESE GUIDE SPECIFICATIONS.** Sika Corporation assumes no liability with respect to the provision or use of these guide specifications, nor shall any legal relationship be created by, or arise from, the provision of such specifications **SIKA SHALL NOT BE RESPONSIBLE UNDER ANY LEGAL THEORY TO ANY THIRD PARTY FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES OF ANY KIND ARISING FROM THE USE OF THESE GUIDE SPECIFICATIONS.** The specifier, architect, engineer or design professional or contractor for a particular project bears the sole responsibility for the preparation and approval of the specifications and determining their suitability for a particular project or application.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available at [www.sikaconstruction.com](http://www.sikaconstruction.com) or by calling (201) 933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.