

## PRODUCT DATA SHEET

# Sika® Ucrete® BC 9

(formerly Ucrete® BC 9)

Heavy-duty, flow-applied basecoat for 3/8" Sika® Ucrete® flooring systems

### PRODUCT DESCRIPTION

Sika® Ucrete® BC 9 is a fast-curing, flow-applied mortar. It provides a broadcasted base coat for 3/8" Sika® Ucrete® flooring systems.

### USES

Sika® Ucrete® BC 9 is used as a basecoat under Sika® Ucrete® DP and Sika® Ucrete® CS flooring systems  
Please note:

- The Product may only be used by experienced professionals.

### CHARACTERISTICS / ADVANTAGES

- Expert installation by fully trained and licensed applicators
- Suitable for application on to 7-day-old concrete and 3-day-old polymer screed
- Can be accelerated with Sika® Ucrete® Accelerator for fast installation within a 12-hour window
- Non-tainting from the end of mixing

### APPROVALS / STANDARDS

- Halal Certification Europe (HCE), Sika® Ucrete®, WHFC, Certificate No. 21453-2/1/1/Y1
- Food and Beverage Facilities Suitability, Sika® Ucrete®, HACCP, Test Report No. I-PE-769-SA-2-RG-06b
- Indoor Air Comfort Gold EN 16516, Sika® Ucrete®, eurofins, Certificate No. IACG-321-01-01-2023

## PRODUCT INFORMATION

<b>Chemical Base</b>	Water-based polyurethane cement hybrid
<b>Packaging</b>	Refer to the current price list for available packaging variations.
<b>Shelf Life</b>	Always refer to the best-before date of the individual packaging.
<b>Storage Conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 41 °F and 86 °F. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.

## TECHNICAL INFORMATION

<b>Tensile Adhesion Strength</b>	> 2.0 N/mm <sup>2</sup> (concrete failure)	(EN 1542)
<b>Chemical Resistance</b>	Laboratory-defined resistance to many individual chemicals. Before proceeding, contact Sika Technical Service for specific information.	

## APPLICATION INFORMATION

<b>Coverage</b>	3.3-3.7 lb/ft <sup>2</sup>	
<b>Layer Thickness</b>	3/8"	
<b>Product Temperature</b>	Maximum	77 °F
	Minimum	59 °F
<b>Ambient Air Temperature</b>	Maximum	86 °F
	Minimum	46 °F
<b>Dew Point</b>	Beware of condensation. The substrate and uncured applied product must be at least 37 °F above the dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and high humidity conditions increase the probability of blooming.	
<b>Substrate Temperature</b>	Maximum	86 °F
	Minimum	46 °F
<b>Waiting / Recoat Times</b>	<b>Substrate temperature</b>	<b>Waiting time</b>
	46 °F	16–24 hours
	50 °F	4 hours (with Sika® Ucrete® Accelerator)
Note: Times are approximate and will be affected by changing ambient and substrate conditions.		

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

#### IMPORTANT

#### **Reduced service life due to incorrect treatment of cracks**

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

1. For static cracks, ensure the width is suitable for overcoating with Sika® Ucrete® BC 9.
2. For dynamic cracks, ensure the movement is within the movement capacity of Sika® Ucrete® BC 9.

#### TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins. The Product can be applied on green or damp concrete with no standing water. Allow for at least 3 days for early concrete shrinkage to occur to prevent shrinkage cracks from appearing on the wearing surface. Cementitious substrates must be structurally sound and of sufficient compressive strength (minimum 30 N/mm<sup>2</sup>) with a minimum tensile strength of 1.5 N/mm<sup>2</sup>. Substrates must be clean, dry and free of contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

### APPLICATION

Application must be undertaken by a fully trained Sika® Ucrete® applicator.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)



#### Product Data Sheet

Sika® Ucrete® BC 9  
November 2024, Version 01.01  
02081400000002007

SikaUcreteBC9-en-US-(11-2024)-1-1.pdf

