

# Repair Mortars, Grouts & Concrete Selection Guide



Product Line	Packaging	Comp. Strength (psi)		Application Depth				Application Area				Application Method				Consistency			Non Shrink	Fiber Reinforced
		1 day	28 days	Neat		Extended		Interior	Exterior	Horizontal	Vertical	Trowel Screed	Pump & Pour	Form & Pour	Spray	Fluid	Flowable	Plastic		
<b>SikaTop® PLUS</b>																				
				Min	Max	Min	Max													
<b>SikaTop 111 PLUS</b>	1 gal / 61.5 lb bag	2,500	6,500	1/2"	1"	1"	6"	■	■	■	■	■	■	■			■			
<b>SikaTop 121 PLUS</b>	1 gal / 46.5 lb bag	1,250	6,000	1/12"	1/6"	N/A		■	■	■	■	■		■				■		
<b>SikaTop 122 PLUS</b>	1 gal / 61.5 lb bag	2,500	7,000	1/8"	1"	1"	4"	■	■	■	■	■						■		
<b>SikaTop 123 PLUS</b>	1 gal / 44 lb bag	3,000	6,000	1/8"	1 1/2"	N/A		■	■		■	■						■		
<b>SikaQuick®</b>																				
<b>SikaQuick 1000</b>	50 lb bag	4,000	7,000	1/4"	1"	1"	6"	■	■	■		■						■		
<b>SikaQuick 2500</b>	50 lb bag	5,700	8,500	1/4"	1"	1"	6"	■	■	■		■						■		
<b>SikaQuick VOH</b>	44 lb bag	3,000	5,500	1/8"	3"	N/A		■	■		■	■							■	
<b>SikaQuick Smooth Finish</b>	50 lb bag	1,000	>2,000	FE	1/2"	N/A		■	■		■	■							■	
<b>SikaQuick FNP</b>	55 lb bag	4,000	>9,000	1/4"	3"	1"	8"	■	■	■	■		■	■		■			■	
<b>SikaRepair®</b>																				
<b>SikaRepair 222</b>	50 lb bag	>2,000	5,000	1/4"	1"	1"	4"	■	■	■	■	■							■	
<b>SikaRepair 223</b>	50 lb bag	>3,500	>7,500	1/4"	1 1/2"	N/A		■	■		■	■							■	
<b>SikaRepair 224</b>	50 lb bag	4,500	10,000	3/8"	2"	1"	4"	■	■	■	■	■		■					■	
<b>SikaRepair SHB</b>	50 lb bag	2,500	5,000	1/4"	3"	N/A		■	■		■	■		■					■	
<b>SikaRepair SHA</b>	50 lb bag	2,000	4,500	1/4"	3"	N/A		■	■		■	■							■	
<b>Sikacrete®</b>																				
<b>Sikacrete 100 CI</b>	80 lb bag	2,200	5,500	1"	8"	N/A		■	■	■	■		■	■				■		
<b>Sikacrete 211 SCC Plus</b>	65 lb bag	2,500	6,500	1"	8"	N/A		■	■	■	■		■	■				■		
<b>Sikacrete 211</b>	80 lb bag	2,000	5,000	1"	8"	N/A		■	■	■	■		■	■				■		
<b>Sikacrete 321 FS</b>	65 lb bag	5,000	7,500	1"	8"	N/A		■	■	■	■		■	■				■		
<b>Sikacrete 421 CI Rapid</b>	65 lb bag	5,270	8,440	1"	8"	N/A		■	■	■	■		■	■				■		
<b>Sikacem®</b>																				
<b>Sikacem 103</b>	55 lb bag	6,000	8,000	1/4"	2"	N/A		■	■	■	■			■				■		
<b>Sikacem 103F</b>	55 lb bag	6,000	8,000	1/4"	2"	N/A		■	■	■	■			■				■	■	
<b>Sikacem 133</b>	55 lb bag	4,000	8,000	1/4"	2"	N/A		■	■	■	■			■				■		
<b>SikaGrout®</b>																				
<b>SikaGrout 212***</b>	50 lb bag	3,500	6,200	1/2"	2"	1"	****	■	■	■	■	■	■	■		■	■	■	■	
<b>SikaGrout 328***</b>	50 lb bag	4,000	8,000	1/2"	6"	1"	****	■	■	■	■	■	■	■		■	■	■	■	
<b>SikaGrout 428 FS***</b>	65 lb bag	7,000	12,500	1/4"	2"	1"	6"	■	■	■	■	■	■	■		■	■	■	■	
<b>SikaGrout 528 SF</b>	50 lb bag	2,000	8,000	1/8"				■	■	■	■	■				■				
<b>Sika Level®</b>																				
<b>Sika Level 325</b>	55 lb bag	2,000	5,300	1/8"	1.5"	3/8"	3"	■	■	■			■	■		■				
<b>Sika Level 125</b>	50 lb bag	1,250	4,000	1/8"	1"	1"	2 1/2"	■		■			■	■		■				
<b>Sika Level Skimcoat</b>	10 lb bag	-	3,700	FE	1/2"	N/A		■		■		■						■		

\* Less if applying overhead \*\* Deeper in localized applications \*\*\*Data at flowable consistency \*\*\*\*Contact Technical Service (for max. extension depth)

NOTE: Information subject to change. For detailed and up to date information, please consult the current Technical Data Sheet at [www.sikausa.com](http://www.sikausa.com)

©Sika Corporation / Target Market Refurbishment / 06.645.6 / 11.2016