



Sika® AnchorFix-2

High performance, two component adhesive anchoring system



A super strong, two-component anchoring adhesive that exhibits high load capacities and can be used in heavy duty anchoring projects. It is specifically formulated as a high performance, adhesive anchor system for threaded and reinforcing bars in uncracked concrete.



Advantages

- Can be used in subfreezing temperatures
- High strength for vertical and horizontal applications & sets in minutes
- Self mixes in nozzle for a FULL 10 oz. of material
- For use with standard caulk gun & packaged with 2 static mixing nozzles
- ANSI/NSF 61 Certified by UL
- ESR to AC308 by ICC-ES for threaded bars only
- ESR to AC308 by IAPMO-UES for threaded bars only

Typical Data

Shelf Life : 15 months in original unopened packaging

Storage Conditions : Cartridges should be stored in their original packaging, the correct way up, in cool conditions (+41°F to +77°F) out of direct sunlight.

Working & Loading Times

| Cartridge Temperature* | T Work (minutes) | Base Material Temperature | T Load |
|------------------------|------------------|---------------------------|-------------|
| Minimum +41°F | 12 | +14°F to +32°F** | 24 hours |
| | | +23°F to +32°F | 180 minutes |
| +41°F to +50°F | 8 | +41°F to +50°F | 100 minutes |
| +50°F to +68°F | 4 | +50°F to +68°F | 70 minutes |
| +68°F to +77°F | 3 | +68°F to +77°F | 40 minutes |
| +77°F to +86°F | 2 | +77°F to +86°F | 40 minutes |
| +86°F | 1 | +86°F | 40 minutes |

T Work is the typical time to gel at the highest temperature in the range T Load is the typical time to reach full capacity

*Cartridge temperature must be maintained at a minimum of +41°F.

**This application is outside the scope of the ESR or the ETA.

For other informations please refer to the Product Data Sheet



SIKA CORPORATION
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225
Toll Free : 800.933.SIKA
usa.sika.com

SIKA CANADA INC.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

SIKA MEXICANA S.A. DE C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

BUILDING TRUST

