

## PRODUCT DATA SHEET

# Sikament<sup>®</sup> N

### HIGH RANGE WATER REDUCING ADMIXTURE

#### PRODUCT DESCRIPTION

Sikament<sup>®</sup> N is a high range water reducing admixture based on non-polycarboxylate technology. Sikament<sup>®</sup> N meets the requirements of ASTM C494/AASHTO M 194, Type A & F.

#### USES

Sikament<sup>®</sup> N is designed for use in ready mix applications whenever high plasticity and increased strengths are required and is effective in concrete containing Portland Limestone Cement (PLC/Type IL) and supplementary cementitious materials. Sikament<sup>®</sup> N can be used for production of high slump/flow concrete as well as for production of conventional slump concrete.

#### CHARACTERISTICS / ADVANTAGES

Various levels of water reduction can be achieved by adjusting the dosage rate of Sikament<sup>®</sup> N.

When used as a high range water reducing admixture, water reduction up to 30% can be obtained. The superplasticizing action of Sikament<sup>®</sup> N allows for the production of high slump/flow concrete with excellent workability that can typically be placed with minimal vibration even at a low water/cementitious ratio.

#### PRODUCT INFORMATION

<b>Packaging</b>	Available in bulk delivery.
<b>Shelf Life</b>	Shelf life when stored in original packaging in dry warehouse conditions between 40°F and 80°F (5-27°C) is one year from the date of manufacture.
<b>Storage Conditions</b>	Sikament <sup>®</sup> N should be stored above 40°F (5°C). If frozen, thaw and agitate

At lower dosage rates Sikament<sup>®</sup> N is an effective normal water reducing or mid-range water reducing admixture. This application is ideal for use with lean, harsh concrete mixes or concrete containing supplementary cementitious materials.

The combined water reducing and superplasticizing action of Sikament<sup>®</sup> N provides the following benefits:

- Reduced water cement ratios produce more durable, dense concrete,
- Increased slump and workability improves efficiency of labor and reduces labor costs,
- Improved finishing characteristics,
- Increased strengths allow faster structural use of concrete.

Sikament<sup>®</sup> N does not contain intentionally added chlorides.

#### ENVIRONMENTAL INFORMATION

Enables a substantially lower carbon footprint through reduction in cementitious materials. Reduces the amount of water required to produce concrete.

For further information, please visit:  
<https://usa.sika.com/en/sustainability.html>

thoroughly to return to a normal state. Protect from direct sunlight.

---

**Appearance / Color** Dark Brown liquid

---

**Specific gravity** Approx. 1.215

---

## APPLICATION INFORMATION

---

### Recommended Dosage

The typical dosage rate of Sikament® N will vary between 2-20 fl oz / 100 lb. (130-1300 mL / 100 kg) of cement or cementitious materials. Various factors will affect the dosage rates.

Trial mixes with the actual materials should be conducted to determine the required dosage for optimum performance.

To the extent specialized materials are used, extreme ambient temperatures are encountered, or for other unusual project conditions, dosage rates outside the typical range may be required. For dosage rates outside the typical range, please contact your local Sika representative or the Sika Technical Services Department at 1-800-933-7452.

---

### Mixing

Measure the required quantity manually or by automated dispenser. Add Sikament® N directly into the freshly mixed concrete, or as an integral material in the batching cycle. Do NOT mix with dry cement. Sikament® N may be dispensed on-site directly prior to placement. Care must be taken to mix thoroughly. When used in combination with other admixtures dispense each admixture separately into the mix.

**Compatibility:** Sikament® N can be used in combination with other Sika admixtures and can be successfully used in mix designs utilizing supplementary cementitious materials. If used in combination with polycarboxylate based admixtures, including but not limited to Sika® ViscoCrete® and Sika® ViscoFlow® products, it may affect the properties of fresh concrete.

---

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and

to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)



**Product Data Sheet**

Sikament® N  
April 2024, Version 03.01  
021302011000000118

SikamentN-en-US-(04-2024)-3-1.pdf

