

Sikagard® 7600 HG / VG

TWO-COMPONENT POLYURETHANE, BITUMEN MODIFIED WATERPROOFING CHEMICAL RESISTANT MEMBRANE

- Sikagard 7600 HG roller grade
- Sikagard 7600 VG trowel grade
- Economical and easy to apply system
- Flexible and chemical resistant system
- Meets California VOC and AQMD requirements, including SCAQMD Areas
- ANSI / NSF 61 approved for contact with potable water

Available in

4.5 gallon pails (A and B component)





Sikagard® 7600 HG / VG

CHEMICAL RESISTANT FLEXIBLE WATERPROOFING

APPLICATIONS

- Flexible waterproofing membrane
- WWTP protective coating
- Tank Liner
- Pond Liner
- Cooling Tower Liner
- Detailing Solution for SikaProof A+12 Membrane

ADVANTAGES

- Seamless system which bridges cracks and joints
- Abrasion resistant
- UV stable
- Impervious to water and aqueous chemicals

TYPICAL DATA*

@75°F (24°C) and 50% R.H.


- **Shelf Life:** One year from date of manufacture in original, factory-sealed containers
- **Storage Conditions:** Store indoors at a temperature between 60-95°F (15-35°C)
- Colors: Component A: Transparent / Component B: Black
- Total Volume Solids (ASTM D-2697): 89 ± 2%
- Total Volume Weight (ASTM D-236): 95 ± 2%
- **VOC Content (ASTM D-2369-81):** <50 g/L
- Tensile Strength (ASTM D-412): 1000 ± 50 psi 5.86 Mpa ± 0.3 Mpa
- Elongation at Break (ASTM D-412): 450% ± 50%
- Tear Strenght (Die C, ASTM D-624): 180 ± 50 pli
- Hardness (ASTM D-2240): 60 ± 5 Shore A
- Coverage: 25 sf/gal results in standard system 2x30 wet mils (2 coats)
- Pot life: Sikagard 7600HG- 30 min. / Sikagard 7600 VG- 20 min.
- Adhesion to Concrete (Dry) Elcometer: 365 psi
- Permeability to Water Vapor (ASTM D751): 0.03 perms
- * For up to date and accurate information, please consult the current Product Data Sheet at www.usa.sika.com.













FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.usa.sika.com

Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: 201-933-8800 Fax: 201-933-6225

