

PRODUCT DATA SHEET

DRYLOK® HD 9000

Professional grade masonry waterproofer

DESCRIPTION

DRYLOK® HD 9000 is a professional grade masonry waterproofer featuring Flexible Encapsulated Polymers that protects the surface and aesthetic integrity of the masonry, by providing a waterproof barrier to water movement into or out of the structure. HD-9000 is specially formulated to resist mildew growth on the dry paint film with the incorporation of a biocide. This product is ideal for basements, stucco, masonry pools, cinder block, poured concrete, and more. An extensive tintable color palette makes HD-9000 a one-step solution for waterproofing and beautification. Tested to ASTM D-7088 Resistance to Hydrostatic Pressure and ASTM D-6904 Resistance to Wind Driven Rain, when applied properly, HD-9000 resists 15 PSI (33 ft high wall of water) and 140 MPH wind-driven rain penetration on masonry's positive and negative sides.

USES

Waterproofing:

- stucco / cinder block / poured concrete
- basements
- masonry pools

CHARACTERISTICS / ADVANTAGES

- Guaranteed to stop water, even under pressure
- Resists 15 PSI
- Category 4-resists 140 MPH wind-driven rain
- Resists mold & mildew growth on the dry paint film
- White, smooth finish
- Tintable
- Fully transferable 18 year warranty
- Can be used for interior/exterior applications
- Professional grade - easy spray application, brush, roll

PRODUCT DATA SHEET

DRYLOK® HD 9000

August 2025, Version 01.01

020706010010000157

PRODUCT INFORMATION

Composition	Latex base				
Packaging	Size	PC/Case	Color	Order No.	Old Order No.
	1 gal	2	White	832916	90001
	5 gal	1	White	832917	90005
Appearance / Color	Smooth, White				
Shelf life	5 years in unopen container				
Storage conditions	Store between 50° F (10°C) and 85°F (29°C). Extreme heat or freezing temperatures can damage the product, causing it to separate or thicken. Avoid Freezing. Keep away from direct sunlight.				
Density	9.47 ± 0.2 (LBS./US GAL.)				
Wet Film Thickness	Recommended Film Thickness/Coat: 17 wet mils/2 coats (432 microns)				
pH-Value	9.0-9.9				
Viscosity	110-120 Ku @ 77°F				
Solid content by mass	60 ± 2%				

TECHNICAL INFORMATION

Resistance to Hydrostatic Pressure	15 psi	ASTM D-7088
Freeze thaw resistance	3 cycles	
Resistance to Wind-Driven Rain	Resists 140 MPH wind-driven rain	

APPLICATION INFORMATION

Number of Coats	2	
Coverage	1st Coat	75 ft²/gal.
	2nd Coat	75–100 ft²/gal.
Ambient air temperature	50°F (10°C) or higher	

PRODUCT DATA SHEET
DRYLOK® HD 9000
August 2025, Version
01.01
020706010010000157



BUILDING TRUST



Drying time	2-3 hours <ul style="list-style-type: none"> ▪ To recoat: 2 hours ▪ Top coat with latex paint: 24 hours
Surface temperature	50°F (10°C) or higher

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- DRYLOK® HD 9000 may be applied over previous coatings in sound condition, but the warranty is void
- Not recommended for use on horizontal surfaces subject to foot traffic (see see DRYLOK® Floor & Wall Masonry Waterproofers)
- Not for use on fishpond (see DRYLOK® Original Concrete & Masonry Waterproofers)

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surface must be clean and free from dirt, dust, grease, oil, form release compound, or paint.

EFFLORESCENCE, a white, powdery, crystal-like deposit visible on the masonry surface, must be removed. DRYLOK® ETCH, used according to manufacturer's directions, is an effective efflorescence removal agent. Re-apply acid until all visible efflorescence is gone. Rinse thoroughly and allow to dry. Patch all holes or cracks, especially the floor/wall joint, with DRYLOK® FAST PLUG® and smooth the patch evenly with the surface around it.

WET WALL PREPARATION: For best results, apply to a bare, dry surface. If the surface appears wet and is not actively leaking, first apply DRYLOK® Wet Wall Bonding Primer according to the label instructions. Applying DRYLOK® Wet Wall Bonding Primer over a bare masonry wall and top coating with DRYLOK® Masonry Waterproofers will not void the warranty of the DRYLOK® Masonry Waterproofers. Wait for a dry (rain-free) period for application.

WARNING

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

STIR THOROUGHLY BEFORE AND DURING APPLICATION. DO NOT THIN. Air and surface temperatures must be 50°F (10°C) or higher. Apply DRYLOK® HD

PRODUCT DATA SHEET
 DRYLOK® HD 9000
 August 2025, Version
 01.01
 020706010010000157

DRYLOK®

BUILDING TRUST



9000 directly on bare masonry. 2 coat application is required (17 wet mils). For spray specs, visit www.DRYLOK.com. If sprayed or rolled, back brush the first coat to fill any pinholes in the masonry. If brushed, work the DRYLOK® HD 9000 into the pores of the masonry, making sure to fill all pores and pinholes (see COVERAGE). The second coat may be applied by the same methods. When painting the inside of bare concrete swimming pools, allow DRYLOK® HD 9000 to dry at least one week before putting into service. DRYLOK® HD 9000 may be applied over previous coatings in sound condition, but the warranty is void. Not formulated for horizontal surfaces subject to foot traffic (see DRYLOK® Floor & Wall Masonry Waterproofing).

CLEANING OF EQUIPMENT

Soap and water

Dispose of contaminated absorbent, container, and unused contents in accordance with local, state, and federal regulations.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- **KEEP CONTAINER TIGHTLY CLOSED**
- **KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION**

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at www.drylok.com or by calling SIKA's Technical Service Department at 1-800-272-3235. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for eighteen (18) years from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EX-**

PRODUCT DATA SHEET

DRYLOK® HD 9000

August 2025, Version

01.01

020706010010000157

DRYLOK®

BUILDING TRUST



PRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-272-3235.

DRYLOKHD9000-en-USDRYLOK-(08-2025)-1-1.pdf

PRODUCT DATA SHEET

DRYLOK® HD 9000

August 2025, Version

01.01

020706010010000157

5 / 5

DRYLOK®

BUILDING TRUST

